



US 20180006271A1

(19) **United States**

(12) **Patent Application Publication**
Tang

(10) **Pub. No.: US 2018/0006271 A1**

(43) **Pub. Date: Jan. 4, 2018**

(54) **FLEXIBLE DISPLAY AND METHOD OF FORMING THE SAME**

Publication Classification

(71) Applicant: **Wuhan China Star Optoelectronics Technology Co., Ltd., Wuhan (CN)**

(51) **Int. Cl.**
H01L 51/52 (2006.01)
H01L 51/56 (2006.01)

(72) Inventor: **Yuejun Tang, Shenzhen (CN)**

(52) **U.S. Cl.**
CPC *H01L 51/5256* (2013.01); *H01L 51/56* (2013.01); *H01L 2251/5338* (2013.01)

(73) Assignee: **Wuhan China Star Optoelectronics Technology Co., Ltd., Wuhan (CN)**

(57) **ABSTRACT**


(21) Appl. No.: **15/272,831**

The present disclosure proposes a flexible display and a method of forming the flexible display. The flexible display includes a flexible base, an OLED element disposing on the flexible base, an encapsulation layer disposed on the OLED element, with the flexible base and/or the encapsulation layer comprising one or more patterned inorganic layers and two or more organic layers, which are configured to wrap the inorganic layers. Therefore, when the stress focuses on the inorganic layer and leads to fractures and peeling-offs, the organic layers that wrapped the inorganic layer prevent the expansion of the fractures and peeling-offs, therefore extend the life of the flexible display being flexible and pliable.

(22) Filed: **Sep. 22, 2016**

(30) **Foreign Application Priority Data**

Jul. 1, 2016 (CN) 2016105128316



10




Fig. 1




Fig. 2




Fig. 3




Fig. 4




Fig. 5

FLEXIBLE DISPLAY AND METHOD OF FORMING THE SAME

BACKGROUND

1. Field of the Invention

[0001] The present disclosure relates to display technology, and especially to a flexible display and method of forming the same.

2. Description of the Related Art

[0002] Organic light-emitting diode (OLED) display equipped with thin-film transistor (TFT) can be applied to displays of mobile device, such as smart phones, digital cameras, mobile video-recorders, mobile information terminals, ultra-thin laptops or tablet personal computers, and to displays of electronic device such as ultra-thin TV. OLED display has a wide viewing angle, high contrast ratio and rapid responsiveness. Studies on how to produce thinner display device have been conducted recently, and found that flexible display is easily portable and could be applied to device of a variety of shapes. Therefore, it attracts more attention as it is considered the next-generation display device. More specifically, flexible display with OLED has been considered as a display solution. A flexible display with OLED usually includes a thin-film encapsulation layer that covers the OLED element and a flexible base layer that supports the light-emitting part. An inorganic layer is added in between the thin-film encapsulation layer and flexible base layer.

[0003] Therefore, the thin-film encapsulation layer and flexible base layer can prevent the entry of vapor and oxygen to a satisfactory degree. However, adding the inorganic layer makes the display device thicker and the stress larger, leading to stratification. In addition, when the flexible display bends, the stress focuses on the interface between the organic layer and inorganic layer, leading to fractures and peeling-offs, and therefore affects the life of the flexible display device.

SUMMARY

[0004] One object of the present disclosure is to provide a flexible display and a method of forming the same that can extend the life of the flexible display.

[0005] According to the present disclosure, a flexible display includes a flexible base, an organic light-emitting diode (OLED) element disposed on the flexible base, an encapsulation layer disposed on the OLED element, with the flexible base and/or the encapsulation layer comprising one or more patterned inorganic layers and two or more organic layers, which are configured to wrap the inorganic layers.

[0006] Furthermore, the flexible base and/or the encapsulation layer includes a plurality of patterned inorganic layers.

[0007] Furthermore, the inorganic layers include a plurality of patterned areas, with gaps formed between the plurality of patterned areas. The two or more organic layers are disposed above and below the patterned inorganic layers, and are connected through the gaps.

[0008] Furthermore, positions of gaps in the inorganic layers are not aligned with that in neighboring inorganic layers.

[0009] Furthermore, the organic layers are made of polyethylene terephthalate (PET), polyimide (PI), polycarbonate (PC), epoxy, polyethylene, and/or polyacrylate, formed in single or stacked layers.

[0010] Furthermore, the inorganic layers are made of silica, silicon nitride, silicon oxynitride, aluminum oxide, aluminum nitride, or titanium oxide.

[0011] According to the present disclosure, a method of forming a flexible display includes: providing a flexible base; disposing an OLED element on the flexible display; and disposing an encapsulation layer on the OLED element. The flexible base and/or the encapsulation layer includes one or more patterned inorganic layers and two or more organic layers, which are configured to wrap the inorganic layers.

[0012] Furthermore, the method further includes: providing a supporting base; forming an organic layer on the supporting base and/or the OLED element; producing inorganic layers on the organic layer, and patterning the inorganic layers, so that the inorganic layers comprise a plurality of patterned areas and form patterned inorganic layers, with gaps formed among the plurality of patterned areas; forming an organic layer on the inorganic layers so that the two organic layers are disposed above and below the patterned inorganic layers respectively, and connected through the gaps; and repeating the forming procedure of the patterned inorganic layers and organic layers when necessary.

[0013] Furthermore, the flexible base and/or the encapsulation layer includes a plurality of patterned inorganic layers.

[0014] Furthermore, positions of gaps in the inorganic layers are not aligned with that in neighboring inorganic layers.

[0015] Different from the current technology, the present disclosure provides a flexible display and a method of forming the same. The flexible display includes a flexible base, an OLED element and an encapsulation layer. The OLED element is disposed on the flexible base, and the encapsulation layer is disposed on the OLED element. The flexible base and/or the encapsulation layer include one or more patterned inorganic layers and two or more organic layers, which are used to wrap the inorganic layer. Therefore, when the stress focuses on the inorganic layer and leads to fractures and peeling-offs, the organic layers that wrapped the inorganic layer prevent the expansion of the fractures and peeling-offs, therefore extend the life of the flexible display being flexible and pliable.

BRIEF DESCRIPTION OF THE DRAWINGS

[0016] FIG. 1 is a schematic diagram of a flexible display of an embodiment of the present disclosure.

[0017] FIG. 2 shows a schematic diagram of an inorganic layer and organic layer according to the present disclosure.

[0018] FIG. 3 shows a schematic diagram of OLED element according to the present disclosure.

[0019] FIG. 4 is a flow chart on the production method of the flexible display.

[0020] FIG. 5 is a flow chart on the production of the inorganic and organic layers.

DETAILED DESCRIPTION OF PREFERRED EMBODIMENTS

[0021] Please refer to FIG. 1. FIG. 1 is a structural diagram of a flexible display of an embodiment of the present disclosure. The flexible display 10 of the present

embodiment includes a flexible base **11**, an OLED element **12** and an encapsulation layer **13**.

[0022] The flexible layer **11** is composed of any flexible insulating materials. For example, materials for the flexible base **11** can include one or more polymeric materials, such as polyimide (PI), polycarbonate (PC), polyether sulfone (PES), polyethylene terephthalate (PET), polyethylene naphthalate (PEN), polyarylate (PAR) and fiber-reinforced plastic (FRP). The flexible base **11** can be transparent, translucent or opaque.

[0023] The OLED element **12** is disposed on the flexible base **11**. In the present embodiment, the OLED element **12**, preferably, is an OLED element that is formed on the TFT. Please also refer to FIG. 3. The OLED element **12** is disposed on the flexible base **11**. Specifically, the OLED layer **12** includes a first electrode **122**, an OLED layer **123** and a second electrode **124**. The OLED layer **123** includes a plurality of stacked layers, from bottom to top: a hole injection layer (HIL) **125**, a hole transport layer (HTL) **126**, an emitting layer **127**, an electronic transport layer (ETL) **128** and an electronic injection layer (EIL) **129**.

[0024] The present embodiment does not impose limitations on the structure of TFTs. For example, a TFT can be but is not limited to a top gate type TFT. A TFT with another structure, such as a bottom gate type TFT, can also be disposed. For example, a semi-conductor active layer can change amorphous silicon (a-Si) into polysilicon (p-Si) through the crystallization of a-Si. In order to crystallize a-Si, methods such as rapid thermal annealing (RTA), solid phase crystallization (SPC), excimer laser annealing (ELA), metal-induced crystallization (MIC), metal-induced lateral crystallization (MILC) or sequential lateral solidification (SLS) can be adopted.

[0025] The encapsulation layer **13** is disposed on the OLED element **12**. The encapsulation layer **13** can encapsulate the OLED element **12** so that the OLED element **12** is immune from external influences, thus deterioration of the OLED due to vapor and oxygen can be reduced.

[0026] In the present embodiment, the flexible base **11** and/or encapsulation layer **13** include one or more layers of patterned inorganic layer **14** and two or more layers of the organic layers **15**. The two or more organic layers **15** are used to wrap the inorganic layer **14**.

[0027] Specifically, the present embodiment takes the patterned inorganic layer **14** disposed in the flexible base **11** as an example. It should be understood that the example do not impose limitations on the position or number of the patterned inorganic layer **14** in the present disclosure. The patterned inorganic layer **14** and organic layers **15** of the present disclosure can also be disposed in the encapsulation layer **13**, or be disposed in the flexible base **11** and encapsulation layer **13** concurrently.

[0028] Please refer to FIG. 2. The flexible base **11** includes two patterned inorganic layers **141** and **142**. Organic layers **15** are disposed above and below both the patterned inorganic layers **141** and **142**. An organic layer **151** is disposed on one side of the inorganic layer **141** and an organic layer **152** is disposed on the other side of the inorganic layer **141**, while the organic layer **152** is disposed on one side of the inorganic layer **142** and an organic layer **153** is disposed on the other side of the inorganic layer **142**. The organic layer **151** provides a flat surface on the top side of a supporting base **110**.

[0029] The patterned inorganic layer **14** includes a plurality of patterned areas. Gaps are formed among the plurality of patterned areas. The patterned inorganic layer **141** includes patterned areas **1411** to **1413**. The patterned inorganic layer **142** includes patterned areas **1414** to **1416**. A gap **G1** is formed between the patterned areas **1411** and **1412**, a gap **G2** is formed between the patterned areas **1412** and **1413**, a gap **G3** is formed between the patterned areas **1414** and **1415**, a gap **G4** is formed between the patterned areas **1415** and **1416**.

[0030] In the present embodiment, the organic layers **15** disposed above and below the patterned inorganic layers are connected through the abovementioned gaps. Take the patterned inorganic layer **141**, and organic layers **151** and **152** as an example. The organic layer **151** connects the organic layer **152** through gaps **G1** and **G2**. Therefore, the patterned areas **1411**, **1412**, and **1413** of the patterned inorganic layer **141** are wrapped individually by the organic layers **151** and **152**, so that they are not connected to each other. When the stress focuses on a specific area of the inorganic layer, such as the patterned area **1412** shown in FIG. 2, and leading to fractures and peeling-offs, the organic layers **151** and **152** that wrap the patterned area **1412** can prevent fractures and peeling-offs to extend to a next area, such as the patterned areas **1411** and **1413** shown in FIG. 2. Therefore, it extends the life of the flexible display **10** being flexible and pliable.

[0031] The protection of the organic layers **152** and **153** offered to the patterned inorganic layer **142** is the same as that mentioned above. No further explanation is provided here.

[0032] Furthermore, positions of gaps of the patterned inorganic layer **14** are not aligned with that of gaps of a neighboring inorganic layer. Please refer to FIG. 2. The gaps **G1** and **G2** of the patterned inorganic layer **141** are not aligned with the gaps **G3** and **G4** of the patterned inorganic layer **142**. Therefore, the design can effectively prevent the entry of vapor when the inorganic layers **14** are partially fractured or peeled off.

[0033] The abovementioned example is a flexible base **11** including patterned inorganic layers **14** and organic layers **15**. The inorganic layers of the present embodiment are all patterned inorganic layers, such as the patterned inorganic layers **141** and **142** shown in FIG. 2. In other embodiments, the flexible base **11** can include, in addition to one or more patterned inorganic layers, flat and connected organic layers. For example, the flexible base **11** includes a patterned inorganic layer and a connected inorganic layer.

[0034] Other embodiments may have an encapsulation layer **13** including patterned inorganic layers **14** and organic layers **15**, or a flexible base **11** and an encapsulation layer **13** that both include patterned inorganic layers **14** and organic layers **15**. And, the number of layers of patterned inorganic layers **14** and organic layer **15** can be other numbers.

[0035] In the present embodiment, materials for the organic layers **15** include PET, PI, PC, epoxy, polyethylene, and/or polyacrylate, formed in single or stacked layers. Materials for the patterned inorganic layers **14** include metal oxides or metal nitrides, such as silica, silicon nitride, silicon oxynitride, alumina, aluminum nitride, or titanium oxide, shaped in single or stacked layers. The patterned inorganic layer **14** can prevent vapor, oxygen or impurity from extending to the OLED element **12** through the flexible base **11** and/or the encapsulation layer **13** to a satisfying extent.

[0036] Following the same line, a flexible display **10** of the present embodiment includes a patterned inorganic layer **14** composed of a single or plurality of layers. The organic layers **15** are connected through gaps in the patterned inorganic layers, so to wrap the inorganic layers. When the stress focuses on a specific area on the inorganic layer, leading to fractures and peeling-offs, the organic layers that wrapped the inorganic layers prevent the fractures and peeling-offs from expanding to a next area, and therefore extend the life of the flexible display being flexible and pliable.

[0037] The embodiment of the present disclosure further provides a method of forming the flexible display to be applied to the production of the abovementioned display. For more specific details, please refer to FIG. 4 and FIG. 5. FIG. 4 is a flow chart on the production method of the flexible display. FIG. 5 is a flow chart on the production of the inorganic and organic layers. The method of forming the flexible display of the present embodiment includes following steps:

[0038] Step S1: a flexible base is provided.

[0039] Step S2: an OLED element on the flexible base is disposed.

[0040] Step S3: an encapsulation layer on the OLED element is disposed.

[0041] The flexible base and/or the encapsulation layer include one or more patterned inorganic layers and two or more organic layers, which are used to wrap the inorganic layers.

[0042] The present embodiment provides detailed explanation with an example composed of a flexible base including one or more patterned inorganic layers and two or more organic layers. Please refer to FIG. 5 for a specific illustration of the production procedure of inorganic layers and organic layers.

[0043] First, a supporting base **110** is provided. The supporting base **110** is fixed and extended for the convenience of a production procedure afterwards.

[0044] Furthermore, an organic layer **153** is formed on the supporting layer **110**.

[0045] Furthermore, an inorganic layer **142** is formed on the organic layer **153**. The inorganic layer **142** is further patterned by different areas, so that it includes a plurality of patterned areas, such as patterned areas **1414-1416** in FIG. 5, forming a patterned inorganic layer. Gaps, such as G3 and G4 in FIG. 5, are formed among the plurality of patterned areas. These gaps expose the organic layer **153**. Shape of the pattern can be rectangles, as shown in FIG. 5, or rounds or pentagons. The present embodiment does not impose limitations on the shape of the pattern.

[0046] Furthermore, an organic layer **152** is formed on the inorganic layer **142**. The organic layers **152** and **153** are disposed below and above the inorganic layer **142** respectively. The organic layer **152** is connected to the organic layer **153** through gaps in the inorganic layer **142**. At this point, the inorganic layer **142** is wrapped by the organic layers **153** and **152**.

[0047] Furthermore, an inorganic layer **141** is formed on the organic layer **152**. The inorganic layer **141** is further patterned by different areas, so that it includes a plurality of patterned areas, such as patterned areas **1411-1413** in FIG. 5, forming a patterned inorganic layer. Gaps, such as G1 and G2 in FIG. 5, are formed among the plurality of patterned

areas. These gaps expose the organic layer **152**. Positions of the gaps in the inorganic layers **142** and **141** are not aligned.

[0048] Furthermore, an organic layer **151** is formed on the inorganic layer **141**. The organic layer **151** connects the organic layer **152** through gaps in the inorganic layer **141**. At this point, the inorganic layer **141** is wrapped by the organic layers **151** and **152**.

[0049] A structure of inorganic layers and organic layers of a flexible base can be formed through the abovementioned method.

[0050] The illustration above takes an example composed of a flexible base including one or more patterned inorganic layers and two or more organic layers to explain the production procedure in detail. If the encapsulation layer includes one or more patterned inorganic layers and two or more organic layers, the flexible base and OLED element are formed sequentially by following steps S1 and S2. Then, an organic layer **153** is formed on the OLED element, and the inorganic layer **142**, organic layer **152**, inorganic layer **141** and organic layer **151** are formed sequentially following the abovementioned forming method.

[0051] The organic layers are not limited to the abovementioned three-layer structure, whereas the inorganic layers are not limited to the abovementioned two-layer structure. An entire surface of inorganic layer can be added to the foundation of inorganic layers including patterned areas.

[0052] To sum up, the flexible display **10** of the present embodiment includes a single layer or plurality layers of patterned inorganic layer **14**. The organic layers **15** are connected through the gaps in the patterned inorganic layers so to wrap the inorganic layers. When the stress focuses on a specific area of the inorganic layer and leads to fractures and peeling-offs, the organic layers that wrapped the inorganic layers prevent the next area on the inorganic layer from fracturing and peeling off as well. Therefore, it extends the life of the flexible display being flexible and pliable.

[0053] Although the present invention has been explained by the embodiments shown in the drawings described above, it should be understood to the ordinary skilled person in the art that the invention is not limited to the embodiments, but rather various changes or modifications thereof are possible without departing from the spirit of the invention. Accordingly, the scope of the invention shall be determined only by the appended claims and their equivalents.

1. A flexible display, comprising:

a flexible base;

an organic light-emitting diode (OLED) element, disposed on the flexible base;

an encapsulation layer, disposed on the OLED element, with the flexible base and/or the encapsulation layer comprising one or more patterned inorganic layers and two or more organic layers, the two or more organic layers are configured to wrap the inorganic layers.

2. The flexible display of claim 1, wherein the flexible base and/or the encapsulation layer comprises a plurality of patterned inorganic layers.

3. The flexible display of claim 2, wherein the inorganic layers comprise a plurality of patterned areas, with gaps formed between the plurality of patterned areas; the two or more organic layers are disposed above and below the patterned inorganic layers, and are connected through the gaps.

4. The flexible display of claim 3, wherein positions of gaps in the inorganic layers are not aligned with that in neighboring inorganic layers.

5. The flexible display of claim 1, wherein the organic layers are made of polyethylene terephthalate (PET), polyimide (PI), polycarbonate (PC), epoxy, polyethylene, and/or polyacrylate, formed in single or stacked layers.

6. The flexible display of claim 1, wherein the inorganic layers are made of silica, silicon nitride, silicon oxynitride, aluminum oxide, aluminum nitride, or titanium oxide.

7. A method of forming a flexible display, comprising:

providing a flexible base;

disposing an OLED element on the flexible display;

disposing an encapsulation layer on the OLED element;

wherein the flexible base and/or the encapsulation layer comprises one or more patterned inorganic layers and two or more organic layers, which are configured to wrap the inorganic layers.

8. The method of claim 7, further comprising:

providing a supporting base;

forming an organic layer on the supporting base and/or the OLED element;

producing inorganic layers on the organic layer, and patterning the inorganic layers, so that the inorganic layers comprise a plurality of patterned areas and form patterned inorganic layers, with gaps formed among the plurality of patterned areas;

forming an organic layer on the inorganic layers so that the two organic layers are disposed above and below the patterned inorganic layers respectively, and connected through the gaps;

repeating the forming procedure of the patterned inorganic layers and organic layers when necessary.

9. The method of claim 8, wherein the flexible base and/or the encapsulation layer comprises a plurality of patterned inorganic layers.

10. The method of claim 9, wherein positions of gaps in the inorganic layers are not aligned with that in neighboring inorganic layers.

* * * * *

专利名称(译)	柔性显示器及其形成方法		
公开(公告)号	US20180006271A1	公开(公告)日	2018-01-04
申请号	US15/272831	申请日	2016-09-22
[标]申请(专利权)人(译)	武汉华星光电技术有限公司		
申请(专利权)人(译)	中国武汉恒星光电科技有限公司.		
当前申请(专利权)人(译)	中国武汉恒星光电科技有限公司		
[标]发明人	TANG YUEJUN		
发明人	TANG, YUEJUN		
IPC分类号	H01L51/52 H01L51/56		
CPC分类号	H01L51/5256 H01L2251/5338 H01L51/56		
优先权	201610512831.6 2016-07-01 CN		
其他公开文献	US9905804		
外部链接	Espacenet USPTO		

摘要(译)

本公开提出了一种柔性显示器和一种形成柔性显示器的方法。柔性显示器包括柔性基底，设置在柔性基底上的OLED元件，设置在OLED元件上的包封层，柔性基底和/或包封层包括一个或多个图案化无机层和两个或更多个有机层，它们被配置为包裹无机层。因此，当应力集中在无机层上并导致断裂和剥落时，包裹无机层的有机层防止了断裂和剥离的扩展，因此延长了柔性显示器的柔韧性和柔韧性的寿命。

