



US 20180351114A1

(19) **United States**

(12) **Patent Application Publication**

Kim et al.

(10) **Pub. No.: US 2018/0351114 A1**

(43) **Pub. Date: Dec. 6, 2018**

(54) **ORGANIC ELECTROLUMINESCENT
COMPOUND AND ORGANIC
ELECTROLUMINESCENT DEVICE
COMPRISING THE SAME**

(71) Applicant: **Rohm and Haas Electronic Materials
Korea Ltd., Cheonan (KR)**

(72) Inventors: **Hyun Kim, Suwon (KR); Ga-Won
Lee, Hwaseong (KR); Sung-Woo Jang,
Suwon (KR)**

(21) Appl. No.: **15/779,607**

(22) PCT Filed: **Dec. 9, 2016**

(86) PCT No.: **PCT/KR2016/014435**

§ 371 (c)(1),

(2) Date: **May 29, 2018**

(30) **Foreign Application Priority Data**

Dec. 10, 2015 (KR) 10-2015-0176262

Dec. 7, 2016 (KR) 10-2016-0165699

Publication Classification

(51) **Int. Cl.**
H01L 51/00 (2006.01)
C07F 15/00 (2006.01)
C09K 11/06 (2006.01)

(52) **U.S. Cl.**
CPC **H01L 51/0085** (2013.01); **C07F 15/0033**
(2013.01); **H01L 51/5016** (2013.01); **C09K**
2211/185 (2013.01); **C09K 2211/1029**
(2013.01); **C09K 11/06** (2013.01)

(57) **ABSTRACT**

The present disclosure relates to an organic electroluminescent compound and an organic electroluminescent device comprising the same. The organic electroluminescent compound according to the present disclosure is capable of producing an organic electroluminescent device with reasonably improved color purity and efficiency.

**ORGANIC ELECTROLUMINESCENT
COMPOUND AND ORGANIC
ELECTROLUMINESCENT DEVICE
COMPRISING THE SAME**

TECHNICAL FIELD

[0001] The present disclosure relates to organic electroluminescent compounds and an organic electroluminescent device comprising the same.

BACKGROUND FIELD

[0002] Among display devices, an electroluminescent device (EL device) is a self-light-emitting device which has advantages in that it provides a wider viewing angle, a greater contrast ratio, and a faster response time. The first organic EL device was developed by Eastman Kodak, by using small aromatic diamine molecules and aluminum complexes as materials for forming a light-emitting layer [Appl. Phys. Lett. 51, 913, 1987].

[0003] An organic electroluminescent device (OLED) has a structure comprising an anode, a cathode, and an organic layer between the anode and the cathode, wherein the organic layer may comprise a hole injection layer, a hole transport layer, an electron blocking layer, a light-emitting layer, a hole blocking layer, an electron transport layer, an electron injection layer, etc. In the organic electroluminescent device, when a voltage is applied, holes and electrons are injected from the anode and the cathode, respectively, to the light-emitting layer, in which excitons having high energies are formed by a recombination of the holes and the electrons. The exciton's energy puts the organic luminescent compound in an excited state, and light is emitted by energy released while returning from the excited state to a ground state. Accordingly, the most important factor determining luminous efficiency in an organic electroluminescent device is a light-emitting material.

[0004] The EL material can be categorized into a host material and a dopant material according to their functions. Generally, a device having the most excellent EL characteristic has a structure comprising a light-emitting layer formed by doping a dopant to a host. A host/dopant system is for increasing light-emitting efficiency by energy transfer from a host to a dopant. The host and dopant materials greatly influence the efficiency and lifespan of the EL device when using a dopant/host material system.

[0005] Until now, iridium(III) complexes have been widely known as a dopant of phosphorescent materials, and bis(2-(2'-benzothienyl)-pyridinato-N,C3')iridium(acetylacetonate) ((acac)Ir(btp)₂), tris(2-phenylpyridine)iridium (Ir(ppy)₃) and bis(4,6-difluorophenylpyridinato-N,C2)picolinate iridium (Firpic) as red, green, and blue light-emitting material, respectively.

[0006] However, considering EL characteristic requirements for a middle or large-sized panel of OLED, a development of a dopant compound of iridium complexes providing more excellent EL performance, such as long lifespan, high efficiency and high color purity, is still needed.

[0007] In particular, in order to realize full color display, to which an organic EL device is applied, a pixel configured to emit a particular color called "saturated" color is required. In particular, saturated red, green, and blue pixels are required. These saturated colors can be measured by using a CIE coordinate publicly known in the art.

[0008] In order to express more various colors, a color purity of each of red, green, and blue should be high. In case of red color, the closer to the red color coordinate near 0.680 (CIE X-coordinate standard), the higher the color purity is. Accordingly, a requirement for a suitable dopant compound is increased.

[0009] U.S. Pat. No. 7,951,472 discloses iridium complexes having 2-phenylquinoline-based ligand as a dopant compound of OLED, but iridium complexes having fused azabenzofluorene is not disclosed.


DISCLOSURE OF THE INVENTION

Problems to be Solved

[0010] The object of the present disclosure is first, to provide compounds capable of producing an organic electroluminescent device with excellent color purity and efficiency, and second, to provide an organic electroluminescent device comprising the compounds.

Solution to Problems

[0011] As a result of intensive studies to achieve the technical objects above, the present inventors found that the object can be achieved by an organic electroluminescent compound represented by the following formula 1:



[0012] wherein

[0013] X represents CR₁₁R₁₂, O or S;

[0014] R₁ to R₃, each independently, represent hydrogen, deuterium, a substituted or unsubstituted (C1-C10)alkyl, or a substituted or unsubstituted (C6-C30)aryl;

[0015] R₄ represents hydrogen, or a substituted or unsubstituted (C1-C10)alkyl;


[0016] R₁₁ and R₁₂, each independently, represent a substituted or unsubstituted (C1-C10)alkyl, or a substituted or unsubstituted (C6-C30)aryl;

[0017] m and n, each independently, represent an integer of 0 to 4;


[0018] o represents an integer of 0 to 2;

[0019] where m, n or o is an integer of 2 or more, each of R₁, each of R₂, or each of R₃ may be the same or different;

[0020] L represents




[0021] where L is



[0022] R_5 to R_7 , each independently, represent hydrogen, deuterium, a substituted or unsubstituted (C1-C10)alkyl, or a substituted or unsubstituted (C6-C30)aryl;

[0023] where L is



[0024] R_8 to R_{10} , each independently, represent hydrogen, deuterium, a substituted or unsubstituted (C1-C10)alkyl, or a substituted or unsubstituted (C6-C30)aryl; or may be linked to an adjacent substituent to form a substituted or unsubstituted 9- to 20-membered heteroaryl including the pyridine ring linked to R_5 to R_{10} ; and

[0025] the heteroaryl may comprise one or more hetero atoms selected from a nitrogen, an oxygen, and a sulfur, in addition to the nitrogen atom of the pyridine ring.

Effects of the Invention

[0026] By using a compound according to the present disclosure, an organic electroluminescent device showing significant improvement in color purity and efficiency can be prepared.

EMBODIMENTS OF THE INVENTION

[0027] Hereinafter, the present disclosure will be described in detail. However, the following description is intended to explain the invention, and is not meant in any way to restrict the scope of the invention.

[0028] The present disclosure relates to a compound represented by formula 1 above, an organic electroluminescent

material comprising said compound, and an organic electroluminescent device comprising said compound.

[0029] Hereinafter, the compound represented by formula 1 of the present disclosure will be specifically described in detail.

[0030] Herein, “(C1-C10)alkyl” indicates a linear or branched alkyl having 1 to 10 carbon atoms, in which the number of carbon atoms is preferably 1 to 5, and more preferably 1 to 4, and includes, as a specific example, methyl, ethyl, n-propyl, isopropyl, n-butyl, isobutyl, sec-butyl, tert-butyl, n-pentyl, 1-methylbutyl, 2-methylbutyl, 3-methylbutyl, 1,1-dimethylpropyl, 1,2-dimethylpropyl, 2,2-dimethylpropyl, and 1-ethylpropyl. Herein, “(C6-C30)aryl” indicates a monocyclic or fused ring radical derived from an aromatic hydrocarbon having 6 to 30 ring backbone carbon atoms, in which the number of ring backbone carbon atoms is preferably 6 to 20, more preferably 6 to 15, and includes, as a specific example, phenyl, biphenyl, terphenyl, naphthyl, binaphthyl, phenyl-naphthyl, naphthyl-phenyl, phenyl-terphenyl, fluorenyl, phenylfluorenyl, benzofluorenyl, dibenzofluorenyl, phenanthrenyl, phenylphenanthrenyl, anthracenyl, indenyl, triphenylenyl, pyrenyl, tetracenyl, perylenyl, chrysenyl, naphthacenyl, fluoranthrenyl, etc.

[0031] Herein, “3- to 30-membered heteroaryl” indicates an aryl group having 3 to 30 ring backbone atoms, including at least one hetero atom selected from the group consisting of B, N, O, S, Si, and P, in which, the number of ring backbone atoms is preferably 9 to 20, and more preferably 9 to 16, and the number of hetero atoms is preferably 1 to 4. Herein, heteroaryl may be a monocyclic ring, or a fused ring condensed with at least one benzene ring; may be partially saturated; and the heteroaryl may be one formed by linking at least one heteroaryl or aryl group to a heteroaryl group via a single bond(s); and includes a monocyclic ring-type heteroaryl such as furyl, thiophenyl, pyrrolyl, imidazolyl, pyrazolyl, thiazolyl, thiadiazolyl, isothiazolyl, isoxazolyl, oxazolyl, oxadiazolyl, triazinyl, tetrazinyl, triazolyl, tetrazolyl, furazanyl, pyridyl, pyrazinyl, pyrimidinyl, pyridazinyl, etc., and a fused ring-type heteroaryl such as benzofuranyl, benzothiophenyl, isobenzofuranyl, dibenzofuranyl, dibenzothiophenyl, benzoimidazolyl, benzothiazolyl, benzoisothiazolyl, benzoisoxazolyl, benzoxazolyl, isoindolyl, indolyl, indazolyl, benzothiadiazolyl, quinolyl, isoquinolyl, cinnolinyl, quinazolyl, quinoxalyl, carbazolyl, phenoxazinyl, phenanthridinyl, benzodioxolyl, etc.

[0032] Herein, “substituted” in the expression “substituted or unsubstituted” means that hydrogen atom in a certain functional group is replaced with another atom or another functional group, i.e. a substituent. In R_1 to R_{12} of formula 1 of the present disclosure, the substituents of the substituted alkyl, the substituted aryl, or the substituted heteroaryl each independently, are at least one selected from the group consisting of deuterium; a halogen; a cyano; a carboxyl; a nitro; a hydroxyl; a (C1-C30)alkyl; a halo(C1-C30)alkyl; a (C2-C30)alkenyl; a (C2-C30)alkynyl; a (C1-C30)alkoxy; a (C1-C30)alkylthio; a (C3-C30)cycloalkyl; a (C3-C30)cycloalkenyl; a 3- to 7-membered heterocycloalkyl; a (C6-C30)aryloxy; a (C6-C30)arylthio; a 3- to 30-membered heteroaryl unsubstituted or substituted with a (C6-C30)aryl; a (C6-C30)aryl unsubstituted or substituted with a (C1-C30)alkyl, a cyano, a 3- to 30-membered heteroaryl or a tri(C6-C30)arylsilyl; a tri(C1-C30)alkylsilyl; a tri(C6-C30)arylsilyl; a di(C1-C30)alkyl(C6-C30)arylsilyl; a (C1-C30)alkyldi(C6-C30)arylsilyl; an amino; a mono- or di- (C1-C30)


alkylamino; a mono- or di-(C6-C30)arylamino; a (C1-C30)alkyl(C6-C30)arylamino; a (C1-C30)alkylcarbonyl; a (C1-C30)alkoxycarbonyl; a (C6-C30)arylcabonyl; a di(C6-C30)arylboronyl; a di(C1-C30)alkylboronyl; a (C1-C30)alkyl(C6-C30)arylboronyl; a (C6-C30)aryl(C1-C30)alkyl; and a (C1-C30)alkyl(C6-C30)aryl; preferably, are each independently, deuterium or a (C1-C6)alkyl.

[0033] In formula 1, X represents $CR_{11}R_{12}$, O or S.


[0034] In formula 1, R_1 to R_3 are each independently hydrogen, deuterium, a substituted or unsubstituted (C1-C10)alkyl, or a substituted or unsubstituted (C6-C30)aryl; preferably, hydrogen, a substituted or unsubstituted (C1-C5)alkyl, or a substituted or unsubstituted (C6-C20)aryl; more preferably, hydrogen, an unsubstituted (C1-C4)alkyl, or a (C6-C15)aryl unsubstituted or substituted with a (C1-C4)alkyl. For example, R_1 to R_3 may be each independently hydrogen, methyl, isobutyl, tert-butyl, or phenyl unsubstituted or substituted with methyl, isobutyl, or tert-butyl.

[0035] In formula 1, R_4 represents hydrogen, or a substituted or unsubstituted (C1-C10)alkyl; and preferably, hydrogen.

[0036] In formula 1, L represents




[0037] In formula 1, if L is



R_5 to R_7 are each independently hydrogen, deuterium, a substituted or unsubstituted (C1-C10)alkyl, or a substituted or unsubstituted (C6-C30)aryl; preferably, hydrogen, a substituted or unsubstituted (C1-C5)alkyl, or a substituted or unsubstituted (C6-C15)aryl; more preferably, hydrogen, an unsubstituted (C1-C15)alkyl, or an unsubstituted (C6-C15)aryl. For example, L may be hydrogen, methyl, isobutyl, tert-butyl, pentyl, or phenyl.

[0038] In formula 1, if L is




R_8 to R_{10} may be each independently hydrogen, deuterium, a substituted or unsubstituted (C1-C10)alkyl, or a substi-

tuted or unsubstituted (C6-C30)aryl or at least two of R_8 to R_{10} may be linked to each other as an adjacent substituent to form a substituted or unsubstituted 9- to 20-membered heteroaryl including the pyridine ring linked to R_8 to R_{10} , and the heteroaryl may comprise one or more hetero atoms selected from a nitrogen, an oxygen, and a sulfur in addition to the nitrogen atom of the pyridine ring; preferably, hydrogen, a substituted or unsubstituted (C1-C5)alkyl, or a substituted or unsubstituted (C6-C20)aryl or at least two of R_8 to R_{10} may be linked to an adjacent substituent to form a 9- to 16-membered heteroaryl which includes the pyridine ring linked to R_8 to R_{10} and is unsubstituted or substituted with a (C1-C15)alkyl, and the heteroaryl may comprise one or more hetero atoms selected from a nitrogen, an oxygen, and a sulfur in addition to the nitrogen atom of the pyridine ring; and for example, hydrogen, methyl, or phenyl substituted with methyl or at least two of R_8 to R_{10} may be linked to each other as an adjacent substituent to form a quinoline which includes the pyridine ring linked to R_8 to R_{10} and is unsubstituted or substituted with a (C1-C6)alkyl.

[0039] In formula 1, R_{11} and R_{12} are each independently, a substituted or unsubstituted (C1-C10)alkyl, or a substituted or unsubstituted (C6-C30)aryl. R_{11} and R_{12} each independently may be preferably a substituted or unsubstituted (C1-C5)alkyl, or a substituted or unsubstituted (C6-C20)aryl; more preferably, a (C1-C4)alkyl unsubstituted or substituted with deuterium, or an unsubstituted (C6-C15)aryl; and for example, methyl unsubstituted or substituted with deuterium, ethyl unsubstituted or substituted with deuterium, or phenyl.


[0040] In formula 1, m and n, each independently, represent an integer of 0 to 4; o represents an integer of 0 to 2; and where m, n or o is an integer of 2 or more, each of R_1 , each of R_2 , or each of R_3 may be the same or different.

[0041] According to one embodiment of the present disclosure, in formula 1, X may represent $CR_{11}R_{12}$, O or S; R_1 to R_3 may be each independently hydrogen, a substituted or unsubstituted (C1-C5)alkyl, or a substituted or unsubstituted (C6-C20)aryl; R_4 may represent hydrogen; L may represent




R_5 to R_7 may be each independently hydrogen, a substituted or unsubstituted (C1-C5)alkyl, or a substituted or unsubstituted (C6-C15)aryl; R_{11} and R_{12} may be each independently, a substituted or unsubstituted (C1-C5)alkyl, or a substituted or unsubstituted (C6-C20)aryl; m and n, each independently, represent an integer of 0 to 4; o represents an integer of 0 to 2; and where m, n or o is an integer of 2 or more, each of R_1 , each of R_2 , or each of R_3 may be the same or different.

[0042] According to another embodiment of the present disclosure, in formula 1, X may represent $CR_{11}R_{12}$, O or S; R_1 to R_3 may be each independently hydrogen, a substituted or unsubstituted (C1-C5)alkyl, or a substituted or unsubstituted (C6-C20)aryl; R_4 may represent hydrogen; L may represent




R_5 to R_{10} may be each independently hydrogen, a substituted or unsubstituted (C1-C5)alkyl, or a substituted or unsubstituted (C6-C20)aryl, or at least two of R_5 to R_{10} may be linked to each other as an adjacent substituent to form a 9- to 16-membered heteroaryl which includes the pyridine ring linked to R_5 to R_{10} and is unsubstituted or substituted with a (C1-C15)alkyl, and the heteroaryl may comprise one or more hetero atoms selected from a nitrogen, an oxygen, and a sulfur in addition to a nitrogen atom of the pyridine ring; R_{11} and R_{12} may be each independently, a substituted or unsubstituted (C1-C5)alkyl, or a substituted or unsubstituted (C6-C20)aryl; m and n , each independently, may represent an integer of 0 to 4; o may represent an integer of 0 to 2; and where m , n or o is an integer of 2 or more, each of R_1 , each of R_2 , or each of R_3 may be the same or different.

[0043] According to another embodiment of the present disclosure, in formula 1, X may represent $CR_{11}R_{12}$, O or S; R_1 to R_3 may be each independently hydrogen, an unsubstituted (C1-C4)alkyl, or a (C6-C15)aryl unsubstituted or substituted with a (C1-C4)alkyl; R_4 may represent hydrogen; L may represent




R_5 to R_7 may be each independently hydrogen, an unsubstituted (C1-C15)alkyl, or an unsubstituted (C6-C15)aryl; R_{11} and R_{12} may be each independently a (C1-C4)alkyl unsubstituted or substituted with deuterium, or an unsubstituted (C6-C15)aryl; m and n , each independently, may represent an integer of 0 to 4; o may represent an integer of 0 to 2; and where m , n or o is an integer of 2 or more, each of R_1 , each of R_2 , or each of R_3 may be the same or different.

[0044] According to another embodiment of the present disclosure, in formula 1, X may represent $CR_{11}R_{12}$, O or S; R_1 to R_3 may be each independently hydrogen, an unsubstituted (C1-C4)alkyl, or a (C6-C15)aryl unsubstituted or substituted with a (C1-C4)alkyl; R_4 may represent hydrogen; L may represent




R_8 to R_{10} may be each independently hydrogen, methyl, or phenyl substituted with methyl, or at least two of R_8 to R_{10} may be linked to each other as an adjacent substituent to form a quinoline which includes the pyridine ring linked to R_8 to R_{10} and is unsubstituted or substituted with a (C1-C6)alkyl; R_{11} and R_{12} may be each independently, a (C1-C4)alkyl unsubstituted or substituted with deuterium, or an unsubstituted (C6-C15)aryl; m and n , each independently, may represent an integer of 0 to 4; o may represent an integer of 0 to 2; and where m , n or o is an integer of 2 or more, each of R_1 , each of R_2 , or each of R_3 may be the same or different.

[0045] According to another embodiment of the present disclosure, in formula 1, X may represent $CR_{11}R_{12}$, O or S; R_1 to R_3 may be each independently hydrogen, methyl, isobutyl, tert-butyl, or phenyl unsubstituted or substituted with methyl, isobutyl, or tert-butyl; R_4 may represent hydrogen; L may represent









R_5 to R_7 may be each independently hydrogen, methyl, isobutyl, tert-butyl, pentyl, or phenyl; R_{11} and R_{12} may be each independently methyl unsubstituted or substituted with deuterium, ethyl unsubstituted or substituted with deuterium, or phenyl; m and n , each independently, may represent an integer of 0 to 4; o may represent an integer of 0 to 2; and where m , n or o is an integer of 2 or more, each of R_1 , each of R_2 , or each of R_3 may be the same or different.

[0046] According to another embodiment of the present disclosure, in formula 1, X may represent $CR_{11}R_{12}$, O or S; R_1 to R_3 may be each independently hydrogen, methyl, isobutyl, tert-butyl, or phenyl unsubstituted or substituted with methyl, isobutyl, or tert-butyl; R_4 may represent hydrogen; L may represent




R_8 to R_{10} may be each independently hydrogen, methyl, or phenyl substituted with methyl; or at least two of R_8 to R_{10} may be linked to each other as an adjacent substituent to form a quinoline which includes the pyridine ring linked to R_8 to R_{10} and is unsubstituted or substituted with a (C1-C6)alkyl; R_{11} and R_{12} may be each independently methyl unsubstituted or substituted with deuterium, ethyl unsubstituted or substituted with deuterium, or phenyl; m and n , each independently, may represent an integer of 0 to 4; o may represent an integer of 0 to 2; and where m , n or o is an integer of 2 or more, each of R_1 , each of R_2 , or each of R_3 may be the same or different.






[0047] The compound represented by formula 1 includes the following compounds, but is not limited thereto:



-continued




-continued




-continued

D-13




-continued


D-16




D-14




D-17



D-15




D-18




-continued

D-19




-continued


D-22




D-20




D-23



D-21




D-24




-continued

D-25




-continued


D-28




D-26




D-29



D-27




D-30




-continued

D-31




-continued


D-34




D-32




D-35



D-33




D-36




-continued

D-37




-continued


D-40




D-38




D-41




D-39




D-42




-continued




-continued




D-44




D-47



D-45




D-48




-continued

D-49




-continued


D-52




D-50




D-53



D-51




D-54



-continued

D-55




-continued


D-58




D-56




D-59



D-57




D-60




-continued

D-61




-continued


D-64




D-62




D-65



D-63




D-66




-continued

D-67




-continued


D-70




D-68




D-71




D-69




D-72




-continued




-continued




D-74




D-77



D-75




D-78




-continued

D-79




-continued


D-82




D-80




D-83




D-81



D-84




-continued




D-85


-continued




D-88




D-86



D-89




D-87



D-90


-continued

D-91




[0048] The compound according to the present disclosure may be produced by a synthetic method known to a person skilled in the art. For example, it may be produced by the following reaction scheme 1:

[Reaction Scheme 1]



-continued



[0049] wherein, R_1 to R_7 , X , m , n , and o are as defined in formula 1.

[0050] The present disclosure also discloses an organic electroluminescent material comprising the compound of formula 1, and an organic electroluminescent device comprising the material.

[0051] The organic electroluminescent material may consist of the organic electroluminescent compound of the present disclosure as a sole compound, or may further comprise conventional materials generally used in organic electroluminescent materials.

[0052] The organic electroluminescent device of the present disclosure may comprise a first electrode, a second electrode, and at least one organic layer between the first and second electrodes. The organic layer may comprise at least one organic electroluminescent compound of formula 1.


[0053] One of the first and second electrodes may be an anode, and the other may be a cathode. The organic layer may comprise a light-emitting layer, and may further comprise at least one layer selected from a hole injection layer, a hole transport layer, a hole auxiliary layer, a light-emitting auxiliary layer, an electron transport layer, an electron injection layer, an interlayer, a hole blocking layer, an electron buffer layer, and an electron blocking layer.

[0054] Herein, the light-emitting auxiliary layer may be placed between the anode and the light-emitting layer, or the cathode and the light-emitting layer, which may be used for facilitating the injection and/or transport of the hole or for blocking the overflow of the electron when placed between the anode and the light-emitting layer, or which may be used for facilitating the injection and/or transport of the electron or for blocking the overflow of the hole when placed between the cathode and the light-emitting layer. In addition, the hole auxiliary layer is placed between the hole transport layer (or the hole injection layer) and the light-emitting layer, which may exhibit facilitating a transport rate (or injection rate) of a hole or blocking a hole, thereby controlling a charge balance. In addition, the electron blocking layer is placed between the hole transport layer (or the hole injection layer) and the light-emitting layer, which prevents light leakage by blocking the overflow of the electron from the light-emitting layer and confining excitons in the light-emitting layer. If two or more hole transport layers are included, the additional hole transport layer(s), which is

(are) included in addition to the hole transport layer, may be used as the hole auxiliary layer or electron blocking layer. The hole auxiliary layer or the electron blocking layer provides excellent efficiencies and improved lifespan of an organic electroluminescent device.

[0055] The compound represented by formula 1 of the present disclosure is a dopant material, which may be included in the light-emitting layer. In addition, the light-emitting layer may further include one or more host materials.

[0056] The host compounds which are capable of being used with the compound of the present disclosure may be the following compounds represented by formula 2.



(2)

[0057] wherein

[0058] Ma represents a substituted or unsubstituted, nitrogen-containing 5- to 11-membered heteroaryl;

[0059] La represents a single bond, or a substituted or unsubstituted (C6-C30)arylene;

[0060] Xa to Xh , each independently, represent hydrogen, deuterium, a halogen, a cyano, a substituted or unsubstituted (C1-C30)alkyl, a substituted or unsubstituted (C2-C30)alkenyl, a substituted or unsubstituted (C2-C30)alkynyl, a substituted or unsubstituted (C3-C30)cycloalkyl, a substituted or unsubstituted (C6-C60)aryl, a substituted or unsubstituted 3- to 30-membered heteroaryl, a substituted or unsubstituted tri(C1-C30)alkylsilyl, a substituted or unsubstituted tri(C6-C30)arylsilyl, a substituted or unsubstituted di(C1-C30)alkyl(C6-C30)arylsilyl, a substituted or unsubstituted (C1-C30)alkyldi(C6-C30)arylsilyl, a substituted or unsubstituted (C1-C30)alkyl(C6-C30)arylamino, or a substituted or unsubstituted mono- or di-(C6-C30)arylamino; or may be linked to an adjacent substituent(s) to form a substituted or unsubstituted (C3-C30) mono- or polycyclic,

alicyclic or aromatic ring, whose carbon atom(s) may be replaced with at least one hetero atom selected from the group consisting of nitrogen, oxygen, and sulfur; and

[0061] the heteroaryl contains at least one hetero atom selected from B, N, O, S, Si, and P.

[0062] In formula 2, the substituents of a substituted alkyl, a substituted alkenyl, a substituted alkynyl, a substituted cycloalkyl, a substituted aryl, a substituted heteroaryl, a substituted trialkylsilyl, a substituted triarylsilyl, a substituted dialkylarylsilyl, a substituted alkyldiarylsilyl, a substituted alkylarylamino, a substituted monoarylamino, a substituted diarylamino, or a substituted mono- or polycyclic, alicyclic or aromatic ring may be each independently, at least one selected from the group consisting of deuterium; a halogen; a cyano; a carboxyl; a nitro; a hydroxyl; a (C1-C30)alkyl; a halo(C1-C30)alkyl; a (C2-C30)alkenyl; a (C2-C30)alkynyl; a (C1-C30)alkoxy; a (C1-C30)alkylthio; a (C3-C30)cycloalkyl; a (C3-C30)cycloalkenyl; a 3- to 7-membered heterocycloalkyl; a (C6-C30)aryloxy; a (C6-C30)arylthio; a 3- to 30-membered heteroaryl unsubstituted or substituted with a tri(C6-C30)arylsilyl, a (C6-C30)aryl, a (C1-C30)alkyl(C6-C30)aryl, or a tri(C6-C30)arylsilyl(C6-C30)aryl; a (C6-C30)aryl unsubstituted or substituted with a (C1-C30)alkyl, a halogen, a (C6-C30)aryl or a 3- to 30-membered heteroaryl; a tri(C1-C30)alkylsilyl; a tri(C6-C30)arylsilyl; a di(C1-C30)alkyl(C6-C30)arylsilyl; a (C1-C30)alkyl(C6-C30)arylsilyl; an amino; a mono- or di-(C1-C30)alkylamino; a mono- or di-(C6-C30)arylamino; a (C1-C30)alkyl(C6-C30)arylamino; a (C1-C30)alkylcarbonyl; a (C1-C30)alkoxycarbonyl; a (C6-C30)arylcarbonyl; a di(C6-C30)arylboronyl; a di(C1-C30)alkylboronyl; a (C1-C30)alkyl(C6-C30)arylboronyl; a (C6-C30)aryl(C1-C30)alkyl; and a (C1-C30)alkyl(C6-C30)aryl.

[0063] In formula 2, La may represent preferably, a single bond, or a substituted or unsubstituted (C6-C12)arylene; and more preferably, a single bond, or a (C6-C12)arylene unsubstituted or substituted with a tri(C6-C10)arylsilyl. Specifically, La may represent a single bond, a substituted or unsubstituted phenylene, a substituted or unsubstituted naphthylene, or a substituted or unsubstituted biphenylene.

[0064] In formula 2, Ma may represent preferably, a substituted or unsubstituted, nitrogen-containing 5- to 11-membered heteroaryl; and more preferably, a nitrogen-containing 6- to 11-membered heteroaryl unsubstituted or substituted with a cyano, a (C1-C6)alkyl, a tri(C6-C12)arylsilyl, a (C6-C18)aryl, or a 5- to 15-membered heteroaryl.


[0065] Specifically, Ma may represent a substituted or unsubstituted pyrrolyl, a substituted or unsubstituted imidazolyl, a substituted or unsubstituted pyrazolyl, a substituted or unsubstituted triazinyl, a substituted or unsubstituted tetrazinyl, a substituted or unsubstituted triazolyl, a substituted or unsubstituted tetrazolyl, a substituted or unsubstituted pyridyl, a substituted or unsubstituted pyrazinyl, a substituted or unsubstituted pyrimidinyl, a substituted or unsubstituted pyridazinyl, a substituted or unsubstituted benzimidazolyl, a substituted or unsubstituted isoindolyl, a substituted or unsubstituted indolyl, a substituted or unsubstituted indazolyl, a substituted or unsubstituted benzothiadiazolyl, a substituted or unsubstituted quinolyl, a substituted or unsubstituted isoquinolyl, a substituted or unsubstituted cinnolinyl, a substituted or unsubstituted quinazolinyl, a substituted or unsubstituted naphthyridinyl, or a substituted or unsubstituted quinoxalinyl. More specifically, Ma may represent a substituted or unsubstituted triazinyl, a

substituted or unsubstituted pyrimidinyl, a substituted or unsubstituted pyridyl, a substituted or unsubstituted quinolyl, a substituted or unsubstituted isoquinolyl, a substituted or unsubstituted quinazolinyl, a substituted or unsubstituted naphthyridinyl, or a substituted or unsubstituted quinoxalinyl.


[0066] Preferably, Xa to Xh, each independently, may represent hydrogen, a cyano, a substituted or unsubstituted (C6-C15)aryl, a substituted or unsubstituted 6- to 20-membered heteroaryl, or a substituted or unsubstituted tri(C6-C15)arylsilyl; or may be linked to an adjacent substituent(s) to form a substituted or unsubstituted 6- to 20-membered, mono- or polycyclic aromatic ring, whose carbon atom(s) may be replaced with at least one hetero atom selected from the group consisting of nitrogen, oxygen, and sulfur. More preferably, Xa to Xh, each independently, may represent hydrogen, a cyano, a (C6-C15)aryl unsubstituted or substituted with a tri(C6-C12)arylsilyl, or a 10- to 20-membered heteroaryl unsubstituted or substituted with a (C6-C12)aryl; or may be linked to an adjacent substituent(s) to form a substituted or unsubstituted benzene, a substituted or unsubstituted indole, a substituted or unsubstituted benzoindole, a substituted or unsubstituted indene, a substituted or unsubstituted benzofuran, or a substituted or unsubstituted benzothiophene. Specifically, at least one of Xa to Xh, for example, Xb, Xc, Xf, or Xg, each independently, may represent a substituted or unsubstituted dibenzothiophene, a substituted or unsubstituted dibenzofuran, a substituted or unsubstituted carbazole, or a substituted or unsubstituted benzocarbazole; or may be linked to an adjacent substituent (s) to form a substituted or unsubstituted benzene, a substituted or unsubstituted indole, a substituted or unsubstituted benzindole, a substituted or unsubstituted indene, a substituted or unsubstituted benzofuran, or a substituted or unsubstituted benzothiophene.

[0067] More specifically, the compound of formula 2 includes the following, but is not limited thereto.


H2-1



H2-2




-continued




H2-3


-continued




H2-6




H2-4




H2-7



H2-5




H2-8




H2-9

-continued




H2-10

-continued




H2-13


H2-11




H2-14



H2-12




H2-15




-continued

H2-16




-continued


H2-18



H2-17




H2-19




-continued

H2-20




-continued


H2-22



H2-21




H2-23




-continued

H2-24




-continued


H2-26



H2-25




H2-27




-continued

H2-28




-continued


H2-30



H2-29




H2-31




-continued


H2-32



H2-33




H2-34




-continued


H2-35




H2-36



H2-37




-continued




H2-38


-continued




H2-41




H2-39



H2-42




H2-40



H2-43


-continued

H2-44




-continued


H2-47




H2-45



H2-48




H2-46




-continued

H2-49




-continued


H2-51



H2-50




H2-52




-continued

H2-53




-continued


H2-55




H2-56



H2-54




H2-57




-continued

H2-58




-continued


H2-61




H2-59




H2-62



H2-60




H2-63




-continued

H2-64




-continued


H2-67




H2-65




H2-68



H2-66




H2-69




-continued

H2-70




-continued


H2-73




H2-71




H2-74




H2-72




H2-75



H2-76




-continued




H2-77


-continued




H2-80




H2-78



H2-81




H2-79




H2-82

-continued




H2-83

-continued




H2-86


H2-84



H2-87




H2-85




-continued

H2-88




-continued


H2-90




H2-91




H2-89



H2-92




-continued




H2-93

-continued




H2-95


H2-94



H2-96




-continued




H2-97

-continued





H2-99

H2-100




H2-98

H2-101




-continued

H2-102




-continued


H2-105




H2-103




H2-106



H2-104




H2-107




-continued

H2-108




-continued


H2-111




H2-109




H2-112




H2-110



H2-113




-continued




H2-114


-continued




H2-117




H2-115




H2-118



H2-119




H2-116




H2-120

-continued




H2-121


-continued




H2-125




H2-122




H2-126



H2-123




H2-127



H2-124


-continued

H2-128




-continued


H2-131




H2-129



H2-132




H2-130




-continued

H2-133




-continued


H2-135




H2-136



H2-134




H2-137




-continued

H2-138




-continued


H2-140



H2-139




H2-141




-continued

H2-142




-continued


H2-144




H2-143



H2-145




-continued




H2-146


-continued




H2-148



H2-147




H2-149




H2-150

-continued




H2-151


-continued




H2-154




H2-152



H2-155




H2-153




H2-156

-continued




H2-157

-continued




H2-161


H2-158




H2-162




H2-159




H2-163



H2-160




-continued




H2-164

-continued




H2-167


H2-165




H2-168




H2-166



H2-169




-continued




H2-170


-continued




H2-173




H2-171



H2-174




H2-172




H2-175

-continued




H2-176

-continued




H2-179


H2-177



H2-180




H2-178




-continued

H2-181




-continued


H2-184




H2-182




H2-185




H2-183



H2-186




-continued




H2-187

-continued




H2-188


H2-190




H2-189




H2-191



H2-192




-continued




H2-193

-continued




H2-196


H2-194




H2-197



H2-195




H2-198




-continued

H2-199




-continued


H2-202



H2-200





H2-203




H2-204

H2-201




-continued


H2-205



H2-206




H2-207




-continued

H2-208




H2-209




-continued


H2-210



H2-211




H2-212




-continued

H2-213




H2-214




-continued

H2-215




-continued


H2-218




H2-216



H2-219




H2-217




-continued

H2-220




-continued


H2-223




H2-221




H2-222



H2-224




-continued




H2-225

-continued




H2-227

H2-226




H2-228




-continued

H2-229




-continued


H2-231



H2-230




H2-232




-continued

H2-233




-continued


H2-235



H2-234




H2-236




-continued

H2-237




-continued


H2-239



H2-238




H2-240




-continued

H2-241




-continued


H2-243




H2-242



H2-244




-continued




H2-245

-continued





H2-248




H2-249


H2-246



H2-250




H2-247




H2-251


-continued



H2-252




H2-253




H2-254


-continued




H2-255



H2-256




H2-257




H2-258


-continued




H2-259



H2-260




H2-261




H2-262


-continued




H2-263



H2-264




H2-265




H2-266

-continued




H2-267

-continued




H2-271


H2-268



H2-272





H2-269




H2-273

H2-270




-continued




H2-274


-continued




H2-278




H2-275




H2-279



H2-276




H2-277




H2-280

-continued




H2-281


-continued




H2-284




H2-282




H2-285



H2-283




H2-286




H2-287

-continued





H2-288

-continued





H2-291

H2-289




H2-292

H2-290




H2-293

H2-294




-continued




H2-295


-continued




H2-298




H2-296




H2-299



H2-297




H2-300




H2-301

-continued




H2-302


-continued




H2-305




H2-303



H2-306




H2-304



H2-307


-continued

H2-308




-continued


H2-311




H2-309




H2-312



H2-310




H2-313




-continued

H2-314





-continued

H2-317





H2-318

H2-315




H2-319

H2-316




-continued

H2-320




-continued

H2-322





H2-323

H2-321




H2-324




-continued

H2-325




-continued


H2-328




H2-326




H2-329




H2-327



H2-330




-continued




H2-331

-continued




H2-334


H2-332




H2-335



H2-333




H2-336




-continued

H2-337





-continued

H2-340





H2-338

H2-341




H2-339

H2-342




-continued




H2-343


-continued




H2-346




H2-344



H2-347




H2-345




H2-348

-continued




H2-349

-continued




H2-352


H2-350




H2-353



H2-351




H2-354




-continued

H2-355




-continued


H2-358




H2-359




H2-356




H2-360



H2-357




H2-361




-continued


H2-362




H2-363



H2-364




H2-365




-continued


H2-366



H2-367




H2-368




-continued


H2-369



H2-370




H2-371




-continued


H2-372




H2-373



H2-374




-continued




H2-375

-continued




H2-378


H2-376




H2-379



H2-377




H2-380




-continued

H2-381




-continued


H2-384



H2-382





H2-385




H2-386

H2-383




-continued

H2-387




-continued


H2-390




H2-391




H2-388




H2-392




H2-389



H2-393




-continued




H2-394

-continued




H2-395


H2-398




H2-396




H2-399



H2-400




H2-397




-continued

H2-401





-continued

H2-404





H2-405

H2-402




H2-406

H2-403




H2-407




-continued

H2-408





-continued

H2-412





H2-413

H2-409





H2-414

H2-410




H2-415

H2-411




-continued

H2-416





-continued

H2-419




H2-420


H2-417



H2-418




H2-421




-continued

H2-422




-continued


H2-425




H2-423




H2-426



H2-424




H2-427




-continued

H2-428




-continued


H2-431




H2-429




H2-432



H2-430




H2-433




-continued

H2-434




-continued


H2-437




H2-435




H2-438



H2-436




H2-439




-continued

H2-440





-continued

H2-443





H2-444

H2-441




H2-442

H2-445




-continued

H2-446





-continued

H2-449





H2-450

H2-447




H2-451

H2-448




-continued

H2-452




-continued


H2-454




H2-453



H2-455




-continued




H2-456

-continued




H2-459


H2-460




H2-457



H2-461




H2-458




H2-461

-continued




H2-462


-continued




H2-465




H2-463



H2-466




H2-464




H2-467

-continued


H2-468




H2-469



H2-470




H2-471




-continued


H2-472



H2-473




H2-474




-continued

H2-475




-continued


H2-478




H2-476




H2-479



H2-477




H2-480




-continued


H2-481



H2-482




H2-483




-continued


H2-484




H2-485



H2-486




-continued




H2-487


-continued




H2-490




H2-488



H2-491



H2-489



H2-492

[0068] According to another embodiment of the present disclosure, a combination of the compound represented by formula 1 and the compound represented by formula 2, and an organic electroluminescent device comprising the combination are provided.

[0069] According to another embodiment of the present disclosure, a mixture or a composition for preparing an organic electroluminescent device is provided. The mixture or composition comprises the compound represented by formula 1. The mixture or composition may be for preparing a light-emitting layer of an organic electroluminescent device. The mixture or composition may comprise a host compound represented by formula 2, besides the compound of the present disclosure. In addition, the mixture or composition may comprise the compound represented by formula 1, which is combined with a host compound represented by formula 2. In addition, the mixture or composition may further comprise a conventional material which is included for preparing an organic electroluminescent device.

[0070] The organic electroluminescent device of the present disclosure comprises the compound represented by formula 1, at the same time, the organic electroluminescent device comprises at least one compound selected from the group consisting of arylamine-based compounds and styrylarylamine-based compounds.

[0071] In the organic electroluminescent device of the present disclosure, the organic layer may further comprise at least one metal selected from the group consisting of metals of Group 1, metals of Group 2, transition metals of the 4th period, transition metals of the 5th period, lanthanides and organic metals of the d-transition elements of the Periodic Table, or at least one complex compound, besides the compound represented by formula 1.

[0072] In addition, the organic electroluminescent device of the present disclosure may emit white light by further comprising at least one light-emitting layer, which comprises a blue electroluminescent compound, a red electroluminescent compound or a green electroluminescent compound known in the art, besides the light-emitting layer of the present disclosure. If necessary, it may further comprise a yellow light-emitting layer or an orange light-emitting layer.

[0073] In the organic electroluminescent device of the present disclosure, preferably, at least one layer (hereinafter, "a surface layer") may be placed on an inner surface(s) of one or both electrode(s), selected from a chalcogenide layer, a metal halide layer, and a metal oxide layer. Specifically, a chalcogenide (includes oxides) layer of silicon or aluminum is preferably placed on an anode surface of an electroluminescent medium layer, and a metal halide layer or a metal oxide layer is preferably placed on a cathode surface of an electroluminescent medium layer. Such a surface layer provides operation stability for the organic electroluminescent

device. Preferably, the chalcogenide includes SiO_x ($1 \leq x \leq 2$), AlO_x ($1 \leq x \leq 1.5$), SiON , SiAlON , etc.; the metal halide includes LiF , MgF_2 , CaF_2 , a rare earth metal fluoride, etc.; and the metal oxide includes Cs_2O , Li_2O , MgO , SrO , BaO , CaO , etc.

[0074] In the organic electroluminescent device of the present disclosure, a mixed region of an electron transport compound and a reductive dopant, or a mixed region of a hole transport compound and an oxidative dopant may be placed on at least one surface of a pair of electrodes. In this case, the electron transport compound is reduced to an anion, and thus it becomes easier to inject and transport electrons from the mixed region to an electroluminescent medium. Furthermore, the hole transport compound is oxidized to a cation, and thus it becomes easier to inject and transport holes from the mixed region to the electroluminescent medium. Preferably, the oxidative dopant includes various Lewis acids and acceptor compounds, and the reductive dopant includes alkali metals, alkali metal compounds, alkaline earth metals, rare-earth metals, and mixtures thereof. A reductive dopant layer may be employed as a charge generating layer to prepare an electroluminescent device having two or more light-emitting layers and emitting white light.

[0075] In order to form each layer of the organic electroluminescent device of the present disclosure, dry film-forming methods such as vacuum evaporation, sputtering, plasma and ion plating methods, or wet film-forming methods such as ink jet printing, nozzle printing, slot coating, spin coating, dip coating, and flow coating methods can be used.


[0076] When using a wet film-forming method, a thin film can be formed by dissolving or diffusing materials forming each layer into any suitable solvent such as ethanol, chloroform, tetrahydrofuran, dioxane, etc. The solvent can be any solvent where the materials forming each layer can be dissolved or diffused, and where there are no problems in film-formation capability.


[0077] Hereinafter, the compound according to the present disclosure, the preparation method thereof, and the luminescent properties of the device will be explained in detail with reference to the following representative compounds.

EXAMPLE 1

Preparation of Compound D-1

[0078]



**[0079]** 1) Preparation of Compound 1-1

[0080] After introducing malonic acid (38 g, 358 mmol) and POCl_3 (356 mL, 3822 mmol) into a reaction vessel, the mixture was stirred for 10 minutes at room temperature. After slowly adding 9,9-dimethyl-9H-fluorene-2-amine (50 g, 239 mmol) dropwise thereto, the mixture was stirred at 150° C. After slowly adding H_2O dropwise to the mixture, an extraction with methylene chloride (MC) was conducted. After removing the solvent, the resultant was purified by column chromatography to obtain compound 1-1 (33.5 g, 45%).

[0081] 2) Preparation of Compound 1-2

[0082] After introducing compound 1-1 (16.5 g, 53 mmol), 3,5-dimethylphenylboronic acid (9.45 g, 63 mmol), $\text{Pd}(\text{PPh}_3)_4$ (1.82 g, 1.58 mmol), Na_2CO_3 (16.70 g, 157.53 mmol), toluene (214 mL), and H_2O (79 mL) into a reaction vessel, the mixture was under reflux at 120° C. The resultant was cooled to room temperature, extracted with ethyl acetate and H_2O , and then purified by column chromatography to obtain compound 1-2 (15.3 g, 76%).

[0083] 3) Preparation of Compound 1-3

[0084] After introducing compound 1-2 (15.3 g, 39.85 mmol), isobutyl boronic acid (8.198 g, 79.71 mmol), 2-dicyclohexylphosphino-2',6'-dimethoxybiphenyl(S-Phos) (1.30 g, 2.81 mmol), K_3PO_4 (41.43 g, 172.28 mmol), tris(dibenzylideneacetone)dipalladium(0) ($Pd_2(dba)_3$) (1.46 g, 1.41 mmol), and toluene (266 mL) into the reaction vessel, the mixture was stirred for 12 hours. The resultant was cooled to room temperature, extracted with ethyl acetate and H_2O , and then purified by column chromatography to obtain compound 1-3 (15.1 g, 93%).

[0085] 4) Preparation of Compound 1-4


[0086] After introducing compound 1-3 (15.1 g, 37.23 mmol), $IrCl_3 \cdot xH_2O$ (5.05 g, 16.92 mmol), 2-ethoxy ethanol

solid was purified by column chromatography to obtain compound D-1 (0.7 g, 18%).

	Molecular Weight (MW)	MP ($^{\circ}C.$)	UV (nm)	PL (nm)
D-1	1184.62	330	288	615

EXAMPLE 2

Preparation of Compound D-12

[0089]

(130 mL), and H_2O (43.4 mL) into the reaction vessel, the mixture was under reflux for 24 hours at $130^{\circ}C.$, and then the resultant was cooled to room temperature. After introducing H_2O , the mixture was stirred for 30 minutes, and then filtered to obtain compound 1-4 (7.9 g, 45%) as solid.

[0087] 5) Preparation of Compound D-1

[0088] After introducing compound 1-4 (3.5 g, 1.69 mmol), 2,8-dimethylnonane-4,6-dione (3.11 g, 16.88 mmol), K_2CO_3 (2.34 g, 16.88 mmol), and 2-ethoxyethanol (21 mL) into the reaction vessel, the mixture was reacted overnight at room temperature and filtered. The obtained


[0090] After introducing compound 1-4 (7.9 g, 3.81 mmol), acetylacetone (3.8 g, 38.10 mmol), Na_2CO_3 (4.04 g, 38.10 mmol), and 2-ethoxyethanol (48 mL), the mixture was reacted overnight and then filtered. The obtained solid was purified by column chromatography to obtain compound D-12 (3 g, 36%).

	MW	MP ($^{\circ}C.$)	UV (nm)	PL (nm)
D-12	1100.46	372	276	617

EXAMPLE 3

Preparation of Compound D-61

[0091]



[0092] 1) Preparation of Compound 3-1

[0093] After introducing compound 1-2 (67.2 g, 181.68 mmol), m-tolyl boronic acid (49.40 g, 363.35 mmol), tris (dibenzylideneacetone)dipalladium(0) ($Pd_2(dba)_3$) (6.65 g, 7.27 mmol), K_3PO_4 (188.97 g, 890.23 mmol), 2-dicyclohexylphosphino-2',6'-dimethoxybiphenyl(s-phos) (6.00 g,

14.53 mmol), and toluene (1200 mL) into a 2 L round-bottom flask, the mixture was stirred under reflux for 24 hours. After completion of the reaction, the reaction product was cooled to room temperature, then extracted with ethyl acetate and treated with $MgSO_4$. The reaction mixture was purified by column chromatography to obtain compound 3-1 (46 g, 58%).

[0094] 2) Preparation of Compound 3-2

[0095] After introducing compound 3-1(46 g, 104.64 mmol), $\text{IrCl}_3 \cdot x\text{H}_2\text{O}$ (14.22 g, 47.56 mmol), 2-ethoxyethanol (365 mL, 0.13 M), and H_2O (122 mL) into a 1 L round-bottom flask under nitrogen atmosphere, the mixture was stirred under reflux for 24 hours. The reaction mixture was cooled to room temperature. The solvent was removed therefrom as much as possible, and then after adding water (500 mL), the mixture was stirred for 30 minutes. The reaction mixture was rinsed with methanol and hexane and dried to obtain compound 3-2 (50.7 g, 97%).

[0096] 3) Preparation of Compound D-61




[0097] After introducing compound 3-2 (10 g, 4.53 mmol), picolinic acid (1.11 g, 9.05 mmol), NaOH (0.36 g, 9.05 mmol), 2-ethoxyethanol (105 mL, 0.043 M) and H_2O (10 mL) into a 250 mL round-bottom flask under nitrogen atmosphere, the mixture was stirred at room temperature for 24 hours. After completion of the reaction, water (330 mL) was added. Thereafter, the mixture was stirred for 30 minutes and then filtered. The obtained resultant was purified by column chromatography to obtain compound D-61(0.8 g, 30%).

DEVICE EXAMPLES 1-1 and 1-2


Preparation of OLED Comprising a Dopant of the Present Disclosure

[0098] OLED comprising the organic electroluminescent compound of the present disclosure was produced. A transparent electrode indium tin oxide (ITO) thin film (10 Ω/sq) on a glass substrate for an organic light-emitting diode (OLED) (Geomatec) was subjected to an ultrasonic washing with acetone, ethanol, and distilled water, sequentially, and then was stored in isopropanol. The ITO substrate was then mounted on a substrate holder of a vacuum vapor depositing apparatus. HI-1 was introduced into a cell of the vacuum vapor depositing apparatus, and then the pressure in the chamber of said apparatus was controlled to 10^{-6} torr. Thereafter, an electric current was applied to the cell to evaporate the above introduced material, thereby forming a first hole injection layer having a thickness of 80 nm on the ITO substrate. HI-2 was introduced into another cell of the vacuum vapor depositing apparatus, and was evaporated by applying an electric current to the cell, thereby forming a second hole injection layer having a thickness of 5 nm on the first hole injection layer. HT-1 was introduced into a cell of the vacuum vapor depositing apparatus, and was evaporated by applying an electric current to the cell, thereby forming a first hole transport layer having a thickness of 10 nm on the second hole injection layer. HT-2 was introduced into another cell of the vacuum vapor depositing apparatus, and was evaporated by applying an electric current to the cell, thereby forming a second hole transport layer having a thickness of 60 nm on the first hole transport layer. Then, the light-emitting layer on the hole injection layers and the hole transport layers was formed as follows. Compound H2-16 was introduced into one cell of the vacuum vapor depositing apparatus as a host, and a dopant material shown in Table 1 below was introduced into another cell. Thereafter, the host material was evaporated, and simultaneously, the dopant

material was evaporated at different rates from the host material, so that the dopant was deposited in a doping amount of 3 wt % based on the total amount of the host and dopant to form a light-emitting layer having a thickness of 40 nm on the second hole transport layer. ET-1 and EI-1 were introduced into two cells of the vacuum vapor depositing apparatus, respectively, and evaporated at a 1:1 rate to form an electron transport layer having a thickness of 30 nm on the light-emitting layer. After depositing EI-1 as an electron injection layer having a thickness of 2 nm, an Al cathode having a thickness of 80 nm was then deposited by another vacuum vapor deposition apparatus on the electron injection layer to produce OLED.



-continued



HT-2

[0100] The evaluation result of the OLED prepared in Device Examples 1-1 and 1-2, and Comparative Example 1-1 above is shown in Table 1 below.

TABLE 1


	Host	Dopant	Voltage (V)	Efficiency (cd/A)	Color Coordinate (x, y)	
Device Example 1-1	H2-16	D-12	4.2	32.7	668	331
Device Example 1-2	H2-16	D-1	4.1	34.0	669	330
Comparative Example 1-1	H2-16	RD-1	4.2	22.4	660	338

[0101] By using an organic electroluminescent compound of the present disclosure, it is possible to provide an organic electroluminescent device with excellent efficiency and color purity compared to the conventional electroluminescent compound.

[0102] This can be understood that an azabenzob[fluorene] ligand of the Device Example attributes the organic electroluminescent device to have better efficiency compared to the quinoline ligand of the Comparative Example. Besides, the substituent (alkyl substituent in the Device Example above) is introduced on the outside of azabenzob[fluorene] ligand according to the present disclosure, and it can be understood that the substituent applies a steric hindrance to the octahedral structure of the iridium complex, thereby reducing Triplet-Triplet Annihilation to maximize the characteristic which improves efficiency.

[0103] Upon comparing the azabenzob[fluorene] ligand of the present disclosure with an azabenzob[a]fluorene ligand, according to the quantum mechanics simulation results, the bond distance between the azabenzob[fluorene] ligand and the iridium metal is shorter than the one between the azabenzob[a]fluorene ligand and the iridium metal. It can be predicted that the shorter the bond distance, the stronger the spin orbital coupling by an iridium atom is applied to have better efficiency.

1. An organic electroluminescent compound represented by the following formula 1:




ET-1

EI-1


COMPARATIVE EXAMPLE 1-1

Preparation of OLED Comprising a Conventional Dopant

[0099] OLED was produced in the same manner as in Device Example 1-1, except that compound RD-1 below was used as a dopant for a light-emitting layer.



RD-1



(1)

wherein

X represents CR₁₁R₁₂, O or S;

R₁ to R₃, each independently, represent hydrogen, deuterium, a substituted or unsubstituted (C1-C10)alkyl, or a substituted or unsubstituted (C6-C30)aryl;

R₄ represents hydrogen, or a substituted or unsubstituted (C1-C10)alkyl;


R₁₁ and R₁₂, each independently, represent a substituted or unsubstituted (C1-C10)alkyl, or a substituted or unsubstituted (C6-C30)aryl;

m and n, each independently, represent an integer of 0 to 4;


o represents an integer of 0 to 2;

where m, n or o is an integer of 2 or more, each of R₁, each of R₂, or each of R₃ may be the same or different;


L represents



where L is



R₅ to R₇, each independently, represent hydrogen, deuterium, a substituted or unsubstituted (C1-C10)alkyl, or a substituted or unsubstituted (C6-C30)aryl; where L is



R₈ to R₁₀, each independently, represent hydrogen, deuterium, a substituted or unsubstituted (C1-C10)alkyl, or a substituted or unsubstituted (C6-C30)aryl; or may be linked to an adjacent substituent to form a substituted or unsubstituted 9- to 20-membered heteroaryl including the pyridine ring linked to R₈ to R₁₀; and the heteroaryl may comprise one or more hetero atoms selected from a nitrogen, an oxygen, and a sulfur in addition to the nitrogen atom of the pyridine ring.

2. The organic electroluminescent compound according to claim 1, wherein

R₁₁ and R₁₂ are each independently, a substituted or unsubstituted (C1-C5)alkyl, or a substituted or unsubstituted (C6-C20)aryl.

3. The organic electroluminescent compound according to claim 1, wherein

R₁ to R₃ are each independently hydrogen, a substituted or unsubstituted (C1-C5)alkyl, or a substituted or unsubstituted (C6-C20)aryl.

4. The organic electroluminescent compound according to claim 1, wherein

R₁₁ and R₁₂ are each independently, a (C1-C4)alkyl unsubstituted or substituted deuterium, or an unsubstituted (C6-C15)aryl;

R₁ to R₃ are each independently hydrogen, an unsubstituted (C1-C4)alkyl, or a (C6-C15)aryl unsubstituted or substituted with a (C1-C4)alkyl; and

R₄ is hydrogen.

5. The organic electroluminescent compound according to claim 1, wherein


R₅ to R₇ are each independently hydrogen, a substituted or unsubstituted (C1-C5)alkyl, or a substituted or unsubstituted (C6-C15)aryl.

6. The organic electroluminescent compound according to claim 1, wherein

R₈ to R₁₀ are each independently hydrogen, a substituted or unsubstituted (C1-C5)alkyl, or a substituted or unsubstituted (C6-C20)aryl; or


at least two of R₈ to R₁₀ may be linked to each other as an adjacent substituent to form a 9- to 16-membered heteroaryl which includes the pyridine ring linked to R₈ to R₁₀ and is unsubstituted or substituted with a (C1-C15)alkyl, and the heteroaryl may comprise one or more hetero atoms selected from a nitrogen, an oxygen, and a sulfur in addition to a nitrogen atom of the pyridine ring.

7. The organic electroluminescent compound according to claim 1, wherein the compound represented by formula 1 is selected from the group consisting of:




D-1

-continued




D-2


-continued




D-5




D-3



D-6




D-4




D-7

-continued




D-8


-continued




D-11




D-9









D-12



D-10




D-13




-continued

D-20




-continued


D-23




D-21




D-24



D-22




D-25




-continued

D-26




-continued


D-29




D-27




D-30









D-28




D-31







-continued




-continued




D-39




D-42



D-40




D-43




-continued

D-44



-continued


D-47




D-45




D-48



D-46




D-49




-continued

D-50





-continued

D-53





D-54

D-51




D-55

D-52



-continued



-continued

D-57


D-60

D-58

D-61


-continued

D-62





-continued

D-65





D-66







D-63









D-67

D-64









-continued

D-80




-continued


D-83




D-81




D-84




D-82




D-85





-continued





-continued



D-87



D-88



8. The organic electroluminescent device comprising the organic electroluminescent compound according to claim 1.

* * * * *

专利名称(译)	有机电致发光化合物和包含其的有机电致发光器件		
公开(公告)号	US20180351114A1	公开(公告)日	2018-12-06
申请号	US15/779607	申请日	2016-12-09
[标]申请(专利权)人(译)	罗门哈斯电子材料有限公司		
申请(专利权)人(译)	罗门哈斯电子材料KOREA LTD.		
当前申请(专利权)人(译)	罗门哈斯电子材料KOREA LTD.		
[标]发明人	KIM HYUN LEE GA WON JANG SUNG WOO		
发明人	KIM, HYUN LEE, GA-WON JANG, SUNG-WOO		
IPC分类号	H01L51/00 C07F15/00 C09K11/06		
CPC分类号	H01L51/0085 C07F15/0033 C09K11/06 C09K2211/185 C09K2211/1029 H01L51/5016 H01L51/001 H01L51/56 H01L51/5088 H01L51/5056 H01L51/5072 H01L51/5092		
优先权	1020150176262 2015-12-10 KR 1020160165699 2016-12-07 KR		
其他公开文献	US10276808		
外部链接	Espacenet USPTO		

摘要(译)

本公开涉及有机电致发光化合物和包含其的有机电致发光器件。根据本发明的有机电致发光化合物能够制备具有合理改善的色纯度和效率的有机电致发光器件。

