



US009882150B2

(12) United States Patent
Li et al.**(10) Patent No.: US 9,882,150 B2**
(45) Date of Patent: Jan. 30, 2018**(54) METAL COMPOUNDS, METHODS, AND USES THEREOF****(71) Applicant: ARIZONA BOARD OF REGENTS FOR AND ON BEHALF OF ARIZONA STATE UNIVERSITY, Scottsdale, AZ (US)****(72) Inventors: Jian Li, Phoenix, AZ (US); Guijie Li, Mesa, AZ (US)****(73) Assignee: Arizona Board of Regents for and on behalf of Arizona State University, Scottsdale, AZ (US)****(*) Notice:** Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 374 days.**(21) Appl. No.: 14/430,454****(22) PCT Filed: Sep. 24, 2013****(86) PCT No.: PCT/US2013/061353**

§ 371 (c)(1),

(2) Date: Mar. 23, 2015**(87) PCT Pub. No.: WO2014/047616****PCT Pub. Date: Mar. 27, 2014****(65) Prior Publication Data**

US 2015/0228914 A1 Aug. 13, 2015

Related U.S. Application Data**(60)** Provisional application No. 61/704,880, filed on Sep. 24, 2012.**(51) Int. Cl.****H01L 51/00** (2006.01)**C09K 11/06** (2006.01)**C07F 15/00** (2006.01)**H01L 51/42** (2006.01)**H01L 51/50** (2006.01)**(52) U.S. Cl.**CPC **H01L 51/0087** (2013.01); **C07F 15/0086** (2013.01); **C09K 11/06** (2013.01); **C09K 2211/1007** (2013.01); **C09K 2211/1029** (2013.01); **C09K 2211/1033** (2013.01); **C09K 2211/1037** (2013.01); **C09K 2211/1044** (2013.01); **C09K 2211/1059** (2013.01); **C09K 2211/185** (2013.01); **H01L 51/42** (2013.01); **H01L 51/5012** (2013.01); **H01L 51/5016** (2013.01); **H01L 51/5036** (2013.01); **Y02E 10/549** (2013.01)**(58) Field of Classification Search**

CPC .. C07D 213/06; C07D 213/30; C07D 213/53; C07D 213/64; C07D 213/74; C07D 277/28; C07D 401/14; C07D 409/14; C07F 15/0086; C09K 11/06; C09K 2211/1037; C09K 2211/1033; C09K 2211/1029; C09K 2211/1007; C09K 2211/1059; C09K 2211/185; C09K

2211/1044; H01L 51/0087; H01L 51/5036; H01L 51/5012; H01L 51/5016; H01L 51/42; H05B 33/14; Y02E 10/549
See application file for complete search history.**(56) References Cited****U.S. PATENT DOCUMENTS**

4,769,292 A	9/1988	Tang et al.
5,707,745 A	1/1998	Forrest et al.
5,844,363 A	12/1998	Gu et al.
6,200,695 B1 *	3/2001	Arai H01L 51/5088 313/504
6,303,238 B1	10/2001	Thompson et al.
6,780,528 B2	8/2004	Tsuboyama et al.
7,002,013 B1	2/2006	Chi et al.
7,037,599 B2	5/2006	Culligan et al.
7,279,704 B2	10/2007	Walters et al.
7,332,232 B2	2/2008	Ma et al.
7,442,797 B2	10/2008	Itoh et al.
7,501,190 B2	3/2009	Ise
7,655,322 B2	2/2010	Forrest et al.
7,947,383 B2	5/2011	Ise et al.
8,389,725 B2	3/2013	Li et al.
8,617,723 B2	12/2013	Stoessel
8,816,080 B2	8/2014	Li et al.
8,871,361 B2	10/2014	Xia et al.
8,927,713 B2	1/2015	Li et al.
8,946,417 B2	2/2015	Li et al.
9,059,412 B2	6/2015	Zeng et al.
9,224,963 B2	12/2015	Li et al.
9,238,668 B2	1/2016	Li et al.
9,312,505 B2	4/2016	Brooks
9,324,957 B2	4/2016	Li et al.
9,382,273 B2	7/2016	Li et al.
9,385,329 B2	7/2016	Li et al.

(Continued)

FOREIGN PATENT DOCUMENTS

CN	1777663	5/2006
CN	1894269	1/2007

(Continued)

OTHER PUBLICATIONS

Murakami; JP 2007258550, English machine translation from EPO, Oct. 4, 2007. 80 pages.

Murakami; JP 2007324309, English machine translation from EPO, Dec. 13, 2007, 89 pages.

Dorwald; "Side Reactions in Organic Synthesis: A Guide to Successful Synthesis Design," Chapter 1, 2005 Wiley-VCH Verlag GmbH & Co. KGaA, Weinheim, 32 pages.

Marc Lepeltier et al., "Efficient blue green organic light-emitting devices based on a monofluorinated heteroleptic iridium(III) complex," Synthetic Metals, vol. 199, 2015, pp. 139-146.

Stefan Bernhard, "The First Six Years: A Report," Department of Chemistry, Princeton University, May 2008, 11 pages.

Wong; Challenges in organometallic research—Great opportunity for solar cells and OLEDs, Journal of Organometallic Chemistry, 2009, 694, 2644-2647.

(Continued)

Primary Examiner — Alexander Kollias*(74) Attorney, Agent, or Firm* — Fish & Richardson P.C.**(57) ABSTRACT**

Disclosed herein are metal compounds useful in devices, such as, for example, OLEDs.

16 Claims, 1 Drawing Sheet

(56)

References Cited

U.S. PATENT DOCUMENTS

9,425,415 B2	8/2016	Li et al.	
9,461,254 B2	10/2016	Tsai	
9,550,801 B2	1/2017	Li	
9,617,291 B2	4/2017	Li	
9,673,409 B2	6/2017	Li	
9,755,163 B2	9/2017	Li	
2002/0068190 A1	6/2002	Tsuboyama et al.	
2003/0062519 A1	4/2003	Yamazaki et al.	
2003/0186077 A1 *	10/2003	Chen	C07D 209/80 428/690
2005/0170207 A1	8/2005	Ma et al.	
2005/0260446 A1	11/2005	Mackenzie et al.	
2006/0073359 A1	4/2006	Ise et al.	
2006/0094875 A1	5/2006	Itoh et al.	
2006/0202197 A1	9/2006	Nakayama et al.	
2006/0210831 A1	9/2006	Sano et al.	
2006/0263635 A1	11/2006	Ise	
2006/0286406 A1	12/2006	Igarashi et al.	
2007/0057630 A1	3/2007	Nishita et al.	
2007/0059551 A1	3/2007	Yamazaki	
2007/0082284 A1	4/2007	Stoessel et al.	
2007/0103060 A1 *	5/2007	Itoh	C07D 213/06 313/504
2008/0001530 A1	1/2008	Ise et al.	
2008/0036373 A1	2/2008	Itoh et al.	
2008/0054799 A1	3/2008	Satou	
2008/0079358 A1	4/2008	Satou	
2008/0241518 A1	10/2008	Satou et al.	
2008/0241589 A1	10/2008	Fukunaga et al.	
2009/0026936 A1	1/2009	Satou et al.	
2009/0026939 A1	1/2009	Kinoshita et al.	
2009/0032989 A1	2/2009	Karim et al.	
2009/0039768 A1	2/2009	Igarashi et al.	
2009/0079340 A1	3/2009	Kinoshita et al.	
2009/0128008 A1	5/2009	Ise et al.	
2009/0218561 A1	9/2009	Kitamura et al.	
2009/0261721 A1	10/2009	Murakami et al.	
2009/0267500 A1	10/2009	Kinoshita et al.	
2010/0000606 A1	1/2010	Thompson et al.	
2010/0013386 A1	1/2010	Thompson et al.	
2010/0171111 A1	7/2010	Takada et al.	
2012/0095232 A1	4/2012	Li et al.	
2012/0181528 A1	7/2012	Takada et al.	
2012/0215001 A1	8/2012	Li et al.	
2012/0223634 A1	9/2012	Xia et al.	
2012/0302753 A1	11/2012	Li	
2013/0048963 A1	2/2013	Beers et al.	
2013/0168656 A1	7/2013	Tsai et al.	
2013/0203996 A1	8/2013	Li et al.	
2013/0237706 A1	9/2013	Li	
2013/0341600 A1	12/2013	Lin et al.	
2014/0014922 A1	1/2014	Lin et al.	
2014/0027733 A1	1/2014	Zeng et al.	
2014/0084261 A1	3/2014	Brooks et al.	
2014/0114072 A1	4/2014	Li et al.	
2014/0203248 A1	7/2014	Zhou et al.	
2014/0330019 A1	11/2014	Li et al.	
2014/0364605 A1	12/2014	Li et al.	
2015/0008419 A1	1/2015	Li	
2015/0028323 A1	1/2015	Xia et al.	
2015/0069334 A1	3/2015	Xia et al.	
2015/0105556 A1	4/2015	Li et al.	
2015/0162552 A1	6/2015	Li et al.	
2015/0194616 A1	7/2015	Li et al.	
2015/0287938 A1	10/2015	Li et al.	
2015/0318500 A1	11/2015	Li et al.	
2015/0349279 A1	12/2015	Li et al.	
2016/0028028 A1	1/2016	Li et al.	
2016/0043331 A1	2/2016	Li et al.	
2016/0133862 A1	5/2016	Li et al.	
2016/0197291 A1	7/2016	Li et al.	
2016/0285015 A1	9/2016	Li et al.	
2016/0359120 A1	12/2016	Li	
2016/0359125 A1	12/2016	Li	
2017/0005278 A1	1/2017	Li	

2017/0012224 A1	1/2017	Li
2017/0047533 A1	2/2017	Li
2017/0066792 A1	3/2017	Li
2017/0069855 A1	3/2017	Li

FOREIGN PATENT DOCUMENTS

CN	101142223 A	3/2008
CN	101667626 A	3/2010
CN	102449108 A	5/2012
CN	102892860 A	1/2013
CN	102971396 A	3/2013
CN	104232076 A	12/2014
CN	104693243 A	6/2015
CN	105367605 A1	3/2016
CN	105418591 A1	3/2016
EP	1808052	7/2007
EP	1874893	1/2008
EP	1874894	1/2008
EP	1919928	5/2008
EP	2036907	3/2009
EP	2096690 A2	9/2009
EP	2417217	2/2012
EP	2112213	7/2012
EP	2711999	3/2014
JP	2005267557 A	9/2005
JP	2005310733 A	11/2005
JP	2006047240 A	2/2006
JP	2006232784 A	9/2006
JP	2006242080 A	9/2006
JP	2006242081 A	9/2006
JP	2006256999 A	9/2006
JP	2006257238 A	9/2006
JP	2006261623 A	9/2006
JP	2006290988	10/2006
JP	2006313796 A	11/2006
JP	2006332622 A	12/2006
JP	2006351638 A	12/2006
JP	2007019462 A	1/2007
JP	2007042875 A	2/2007
JP	2007053132	3/2007
JP	2007066581 A	3/2007
JP	2007073620 A	3/2007
JP	2007073845 A	3/2007
JP	2007073900 A	3/2007
JP	2007080593 A	3/2007
JP	2007080677 A	3/2007
JP	2007088105 A	4/2007
JP	2007088164	4/2007
JP	2007096259 A	4/2007
JP	2007110067 A	4/2007
JP	2007110102 A	4/2007
JP	2007258550 A	10/2007
JP	2007324309 A	12/2007
JP	2008010353 A	1/2008
JP	2008091860 A	4/2008
JP	2008103535 A	5/2008
JP	2008108617 A	5/2008
JP	2008109085 A	5/2008
JP	2008109103 A	5/2008
JP	2008160087 A	7/2008
JP	2008198801 A	8/2008
JP	2008270729 A	11/2008
JP	2008270736 A	11/2008
JP	2009016184 A	1/2009
JP	2009016579 A	1/2009
JP	2009032977 A	2/2009
JP	2009032988 A	2/2009
JP	2009266943 A	11/2009
JP	2009267171	11/2009
JP	2009267244	11/2009
JP	2009272339 A	11/2009
JP	2009283891	12/2009
JP	2010135689	6/2010
JP	2012222255 A	11/2012
JP	2013525436	6/2013
JP	5604505	10/2014
JP	2014221807	11/2014
JP	2015081257	4/2015

(56) References Cited

FOREIGN PATENT DOCUMENTS

KR	1020060115371	11/2006
KR	2007061830	6/2007
KR	2007112465	11/2007
KR	1020130043460	4/2013
TW	200701835	1/2007
TW	201307365	2/2013
TW	201710277 A1	3/2017
WO	WO 2000070655	11/2000
WO	WO2004003108 A1	1/2004
WO	WO2004108857	12/2004
WO	WO2005042444	5/2005
WO	WO2005042550	5/2005
WO	WO2006033440	3/2006
WO	WO2006098505	9/2006
WO	WO2006115299	11/2006
WO	WO2006115301	11/2006
WO	WO2007034985 A1	3/2007
WO	WO2007069498	6/2007
WO	WO2008066192	6/2008
WO	WO2008066195	6/2008
WO	WO2008066196	6/2008
WO	WO2008117889	10/2008
WO	WO2008123540 A2	10/2008
WO	WO2009017211	2/2009
WO	WO2010118026	10/2010
WO	WO2011137429	11/2011
WO	WO2011137431	11/2011
WO	WO2012112853	8/2012
WO	WO2012142387	10/2012
WO	WO2012162488	11/2012
WO	WO2012163471	12/2012
WO	WO2013130483	9/2013
WO	WO2014016611 A1	1/2014
WO	WO2014031977	2/2014
WO	WO2014047616	3/2014
WO	WO2014109814	7/2014
WO	WO2015027060	2/2015
WO	WO2015131158 A1	9/2015
WO	WO2016025921 A1	2/2016
WO	WO2016029186 A1	2/2016

OTHER PUBLICATIONS

JP2009267244, English Translation from EPO, Nov. 2009, 80 pages.

JP2010135689, English translation from EPO, Jun. 2010, 95 pages.
Chi et al.; Transition-metal phosphors with cyclometalating ligands: fundamentals and applications, Chemical Society Reviews, vol. 39, No. 2, Feb. 2010, pp. 638-655.

Satake et al., "Interconvertible Cationic and Neutral Pyridinylimidazole η^3 -Allylpalladium Complexes. Structural Assignment by ¹H, ¹³C, and ¹⁵N NMR and X-ray Diffraction", Organometallics, vol. 18, No. 24, 1999, pp. 5108-5111.

International Search Report mailed by the International Searching Authority dated Jan. 28, 2014 for PCT/US2013/061353 filed Sep. 24, 2013 and published as WO/2014/047616 on Mar. 27, 2014 (Applicant—Arizona Board of Regents for and on behalf of Arizona State University / Inventors—Jian Li, et al.) (pp. 1-4).

Baldo et al., "Highly Efficient Phosphorescent Emission from Organic Electroluminescent Devices," Nature, vol. 395, Sep. 10, 1998, pp. 151-154.

Baldo et al., "Very high-efficiency green organic light-emitting devices based on electrophosphorescence," Applied Physics Letters, vol. 75, No. 1, Jul. 5, 1999, pp. 4-6.

Xiao-Chu Hang et al., "Highly Efficient Blue-Emitting Cyclometalated Platinum(II) Complexes by Judicious Molecular Design," Angewandte Chemie, International Edition, vol. 52, Issue 26, Jun. 24, 2013, pp. 6753-6756.

Ying Yang et al., "Induction of Circularly Polarized Electroluminescence from an Achiral Light-Emitting Polymer via a Chiral Small-Molecule Dopant," Advanced Materials, vol. 25, Issue 18, May 14, 2013, pp. 2624-2628.

Barry O'Brien et al.: White organic light emitting diodes using Pt-based red, green and blue phosphorescent dopants. Proc. SPIE, vol. 8829, pp. 1-6 Aug. 25, 2013.

Ayan Maity et al., "Room-temperature synthesis of cyclometalated iridium(III) complexes; kinetic isomers and reactive functionalities" Chem. Sci., vol. 4, pp. 1175-1181 (2013).

Shiro Koseki et al., "Spin-orbit coupling analyses of the geometrical effects on phosphorescence in Ir(ppy)₃ and its derivatives", J. Phys. Chem. C, vol. 117, pp. 5314-5327 (2013).

Ji Hyun Seo et al., "Efficient blue-green organic light-emitting diodes based on heteroleptic tris-cyclometalated iridium (III) complexes". Thin Solid Films, vol. 517, pp. 1807-1810 (2009).

International Preliminary Report on Patentability issued by the International Searching Authority dated Apr. 2, 2015 for PCT/US2013/061353 filed Sep. 24, 2013, 10 pages.

Vanessa Wood et al., "Colloidal quantum dot light-emitting devices," Nano Reviews, vol. 1, 2010, 8 pages.

Glauco Ponterini et al., "Comparison of Radiationless Decay Processes in Osmium and Platinum Porphyrins," J. Am. Chem. Soc., vol. 105, No. 14, 1983, pp. 4639-4645.

Shizuo Tokito et al., "Confinement of triplet energy on phosphorescent molecules for highly-efficient organic blue-light-emitting devices," Applied Physics Letters, vol. 83, No. 3, Jul. 21, 2003, pp. 569-571.

Brian W. D'Andrade et al., "Controlling Exciton Diffusion in Multilayer White Phosphorescent Organic Light Emitting Devices," Adv. Mater., vol. 14, No. 2, Jan. 16, 2002, pp. 147-151.

Dileep A. K. Vezzu et al., "Highly Luminescent Tetradentate Bis-Cyclometalated Platinum Complexes: Design, Synthesis, Structure, Photophysics, and Electroluminescence Application," Inorg. Chem., vol. 49, 2010, pp. 5107-5119.

Evan L. Williams et al., "Excimer-Based White Phosphorescent Organic Light Emitting Diodes with Nearly 100% Internal Quantum Efficiency," Adv. Mater., vol. 19, 2007, pp. 197-202.

Shih-Chun Lo et al., "High-Triplet-Energy Dendrons: Enhancing the Luminescence of Deep Blue Phosphorescent Iridium(III) Complexes," J. Am. Chem. Soc., vol. 131, 2009, pp. 16681-16688.

Jan Kalinowski et al., "Light-emitting devices based on organometallic platinum complexes as emitters," Coordination Chemistry Reviews, vol. 255, 2011, pp. 2401-2425.

Ke Feng et al., "Norbornene-Based Copolymers Containing Platinum Complexes and Bis(carbazolyl)benzene Groups in Their Side-Chains," Macromolecules, vol. 42, 2009, pp. 6855-6864.

Chi-Ming Che et al., "Photophysical Properties and OLED Applications of Phosphorescent Platinum(II) Schiff Base Complexes," Chem. Eur. J., vol. 16, 2010, pp. 233-247.

Stephen R. Forrest, "The path to ubiquitous and low-cost organic electronic appliances on plastic," Nature, vol. 428, Apr. 29, 2004, pp. 911-918.

Nicholas R. Evans et al., "Triplet Energy Back Transfer in Conjugated Polymers with Pendant Phosphorescent Iridium Complexes," J. Am. Chem. Soc., vol. 128, 2006, pp. 6647-6656.

Xiaofan Ren et al., "Ultrahigh Energy Gap Hosts in Deep Blue Organic Electrophosphorescent Devices," Chem. Mater., vol. 16, 2004, pp. 4743-4747.

Jeonghun Kwak et al., "Bright and Efficient Full-Color Colloidal Quantum Dot Light-Emitting Diodes Using an Inverted Device Structure," Nano Lett., 2012, Vol. 12, pp. 2362-2366.

Hirohiko Fukagawa et al., "Highly Efficient and Stable Red Phosphorescent Organic Light-Emitting Diodes Using Platinum Complexes," Adv. Mater., 2012, vol. 24, pp. 5099-5103.

Eric Turner et al., "Cyclometalated Platinum Complexes with Luminescent Quantum Yields Approaching 100%," Inorg. Chem., 2013, vol. 52, pp. 7344-7351.

Steven C. F. Kui et al., "Robust Phosphorescent Platinum(II) Complexes Containing Tetradentate O[^]N[^]C[^]N[^] Ligands: Excimeric Excited State and Application in Organic White-Light-Emitting Diodes," Chem. Eur. J., 2013, vol. 19, pp. 69-73.

Steven C. F. Kui et al., "Robust phosphorescent platinum(II) complexes with tetradentate O[^]N[^]C[^]N[^] ligands: high efficiency OLEDs with excellent efficiency stability," Chem. Commun., 2013, vol. 49, pp. 1497-1499.

(56)

References Cited

OTHER PUBLICATIONS

Kai Li et al., "Light-emitting platinum(II) complexes supported by tetradentate dianionic bis(N-heterocyclic carbene) ligands: towards robust blue electrophosphors," Chem. Sci., 2013, vol. 4, pp. 2630-2644.

* cited by examiner




FIG. 1




FIG. 2

1

METAL COMPOUNDS, METHODS, AND
USES THEREOFCROSS-REFERENCE TO RELATED
APPLICATIONS

This application is a U.S. National Phase Application of International Patent Application No. PCT/US2013/061353 filed Sep. 24, 2013, which claims U.S. Provisional Application Ser. No. 61/704,880 entitled "TETRADENTATE CYCLOMETALATED METAL COMPLEXES" and filed on Sep. 24, 2012, the contents of both of which are incorporated herein by reference in their entirety.

BACKGROUND

Technical Field

The present disclosure relates to metal compounds that are useful in devices, such as, for example, organic light emitting diodes (OLEDs).

Technical Background


Compounds capable of absorbing and/or emitting light can be ideally suited for use in a wide variety of optical and electro-optical devices, including, for example, photo-absorbing devices such as solar- and photo-sensitive devices, photo-emitting devices, OLEDs, or devices capable of both photo-absorption and emission. Much research has been devoted to the discovery and optimization of organic and organometallic materials for using in optical and electro-optical devices. Generally, research in this area aims to accomplish a number of goals, including improvements in absorption and emission efficiency, as well as improvements in processing ability.

Despite significant advances in research devoted to optical and electro-optical materials, many currently available materials exhibit a number of disadvantages, including poor processing ability, inefficient emission or absorption, and less than ideal stability, among others. Thus, a need exists for new materials which exhibit improved performance in optical and electro-optical devices. This need and other needs are satisfied by the present invention.

SUMMARY


Disclosed herein are metal compounds that are useful in devices, such as, for example, organic light emitting diodes (OLEDs).

Disclosed herein is a compound having the formula





2

wherein each of L^1 , L^2 , L^3 , and L^4 independently is a substituted or unsubstituted aryl, cycloalkyl, cycloalkenyl, heterocyclyl, heteroaryl, carbene, or N-heterocyclic carbene, wherein each of Z^1 , Z^2 , and Z^3 independently is present or absent, and if present each of Z^1 , Z^2 , and Z^3 independently is A, A^1 , or A^2 , wherein each of A, A^1 , or A^2 independently is O, S, S=O, SO_2 , Se, NR^3 , PR^3 , $RP=O$, CR^1R^2 , C=O, SiR^1R^2 , GeR^1R^2 , BH, P(O)H, PH, NH, CR^1H , CH_2 , SiH_2 , $SiHR^1$, BH, or BR^3 , wherein M is Pt, Pd, Au, Ir, Rh, Ru, Fe, Co, Ni, Cu, Zn, Ag, Hg, Cd, or Zr, wherein at least one of L^1 , L^2 , L^3 , and L^4 comprises



wherein m and n independently is an integer from 0 to 4, wherein each of V, X, and Y independently is V^1 , V^2 , V^3 , V^4 , O, S, S=O, SO_2 , Se, NR^3 , PR^3 , $R^1P=O$, CR^1R^2 , C=O, SiR^1R^2 , GeR^1R^2 , BH, P(O)H, PH, NH, CR^1H , CH_2 , SiH_2 , $SiHR^1$, BH, or BR^3 , or any one of





wherein at least one of V, X, and Y is V¹, V², V³, or V⁴, wherein m and n independently is an integer from 0 to 4, wherein each of V¹, V², V³ and V⁴ independently is coordinated to M, and wherein each of V¹, V², V³ and V⁴ independently is N, C, CH, P, B, SiH, or Si, wherein each of R, R¹, R², R³, and R⁴, independently is hydrogen, aryl, cycloalkyl, cycloalkenyl, heterocyclyl, heteroaryl, alkyl, alkenyl, alkynyl, deuterium, halogen, hydroxyl, thiol, nitro, cyano, amino, a mono- or di-alkylamino, a mono- or diaryl amino, alkoxy, aryloxy, haloalkyl, aralkyl, ester, nitrile, isonitrile, alkoxycarbonyl, acylamino, alkoxycarbonylamino, aryloxy carbonylamino, sulfonylamino, sulfamoyl, carbamoyl, alkylthio, sulfinyl, ureido, phosphoramidate, mercapto, sulfo, carboxyl, hydrazino, substituted silyl, or polymerizable, or any conjugate or combination thereof, wherein each of V¹, V², V³ and V⁴ independently optionally is substituted for any one of V¹, V², V³ and V⁴.

Also disclosed herein are devices, such as, for example, OLEDs, comprising one or more of the disclosed compounds.

BRIEF DESCRIPTION OF THE FIGURES

The accompanying figures, which are incorporated in and constitute a part of this specification, illustrate several aspects and together with the description serve to explain the principles of the invention.

FIG. 1 shows a drawing of a cross-section of an exemplary organic light-emitting diode (OLED).

FIG. 2 is a emission spectra of PtN^{III}3PPy in CH₂Cl₂ at room temperature and in 2-MeTHF at 77K.

5 Additional aspects of the invention will be set forth in part
in the description which follows, and in part will be obvious
from the description, or can be learned by practice of the
invention. The advantages of the invention will be realized
and attained by means of the elements and combinations
10 particularly pointed out in the appended claims. It is to be
understood that both the foregoing general description and
the following detailed description are exemplary and
explanatory only and are not restrictive of the invention, as
claimed.

DESCRIPTION

The present invention can be understood more readily by reference to the following detailed description of the invention and the Examples included therein.

Before the present compounds, devices, and/or methods are disclosed and described, it is to be understood that they are not limited to specific synthetic methods unless otherwise specified, or to particular reagents unless otherwise 25 specified, as such can, of course, vary. It is also to be understood that the terminology used herein is for the purpose of describing particular aspects only and is not intended to be limiting. Although any methods and materials similar or equivalent to those described herein can be used 30 in the practice or testing of the present invention, example methods and materials are now described.

1. Definitions

35 As used in the specification and the appended claims, the singular forms “a,” “an” and “the” include plural referents unless the context clearly dictates otherwise. Thus, for example, reference to “a component” includes mixtures of two or more components.

40 Ranges can be expressed herein as from “about” one particular value, and/or to “about” another particular value. When such a range is expressed, another aspect includes from the one particular value and/or to the other particular value. Similarly, when values are expressed as approximations, by use of the antecedent “about,” it will be understood 45 that the particular value forms another aspect. It will be further understood that the endpoints of each of the ranges are significant both in relation to the other endpoint, and independently of the other endpoint. It is also understood 50 that there are a number of values disclosed herein, and that each value is also herein disclosed as “about” that particular value in addition to the value itself. For example, if the value “10” is disclosed, then “about 10” is also disclosed. It is also understood that each unit between two particular units are 55 also disclosed. For example, if 10 and 15 are disclosed, then 11, 12, 13, and 14 are also disclosed.

As used herein, the terms “optional” or “optionally” means that the subsequently described event or circumstance can or cannot occur, and that the description includes 60 instances where said event or circumstance occurs and instances where it does not.

Disclosed are the components to be used to prepare the compositions of the invention as well as the compositions themselves to be used within the methods disclosed herein. These and other materials are disclosed herein, and it is understood that when combinations, subsets, interactions, groups, etc. of these materials are disclosed that while

specific reference of each various individual and collective combinations and permutation of these compounds cannot be explicitly disclosed, each is specifically contemplated and described herein. For example, if a particular compound is disclosed and discussed and a number of modifications that can be made to a number of molecules including the compounds are discussed, specifically contemplated is each and every combination and permutation of the compound and the modifications that are possible unless specifically indicated to the contrary. Thus, if a class of molecules A, B, and C are disclosed as well as a class of molecules D, E, and F and an example of a combination molecule, A-D is disclosed, then even if each is not individually recited each is individually and collectively contemplated meaning combinations, A-E, A-F, B-D, B-E, B-F, C-D, C-E, and C-F are considered disclosed. Likewise, any subset or combination of these is also disclosed. Thus, for example, the sub-group of A-E, B-F, and C-E would be considered disclosed. This concept applies to all aspects of this application including, but not limited to, steps in methods of making and using the compositions of the invention. Thus, if there are a variety of additional steps that can be performed it is understood that each of these additional steps can be performed with any specific embodiment or combination of embodiments of the methods of the invention.

As referred to herein, a linking atom connect two groups such as, for example, a N and C group. The linking atom can, if valency permits, have other chemical moieties attached. For example, an oxygen would not have any other chemical groups attached as the valency is satisfied once it is bonded to the two groups (N and/or C groups). In another example, when carbon is the linking atom, two additional chemical moieties would be attached to the carbon as valency would require such. Suitable chemical moieties includes, but are not limited to, hydrogen, hydroxyl, alkyl, alkoxy, =O, halogen, nitro, amine, amide, thiol, aryl, heteroaryl, cycloalkyl, and heterocyclyl.

The term "alkyl" as used herein is a branched or unbranched saturated hydrocarbon group of 1 to 24 carbon atoms, such as methyl, ethyl, n-propyl, isopropyl, n-butyl, isobutyl, s-butyl, t-butyl, n-pentyl, isopentyl, s-pentyl, neopentyl, hexyl, heptyl, octyl, nonyl, decyl, dodecyl, tetradecyl, hexadecyl, eicosyl, tetracosyl, and the like. The alkyl group can be cyclic or acyclic. The alkyl group can be branched or unbranched. The alkyl group can also be substituted or unsubstituted. For example, the alkyl group can be substituted with one or more groups including, but not limited to, optionally substituted alkyl, cycloalkyl, alkoxy, amino, ether, halide, hydroxy, nitro, silyl, sulfo-oxo, or thiol, as described herein. A "lower alkyl" group is an alkyl group containing from one to six (e.g., from one to four) carbon atoms.

The terms "amine" or "amino" as used herein are represented by the formula $NA^1A^2A^3$, where A^1 , A^2 , and A^3 can be, independently, hydrogen or optionally substituted alkyl, cycloalkyl, alkenyl, cycloalkenyl, alkynyl, cycloalkynyl, aryl, or heteroaryl group as described herein.

The term "halide" as used herein refers to the halogens fluorine, chlorine, bromine, and iodine.

The term "hydroxyl" as used herein is represented by the formula —OH.

The term "nitro" as used herein is represented by the formula —NO₂.

The term "nitrile" as used herein is represented by the formula —CN.

The term "thiol" as used herein is represented by the formula —SH.

The term "heterocyclyl" or the like terms refer to cyclic structures including a heteroatom. Thus, "heterocyclyl" includes both aromatic and non-aromatic ring structures with one or more heteroatoms. Non-limiting examples of heterocyclic includes, pyridine, isoquinoline, methylpyrrole and thiophene etc. "Heteroaryl" specifically denotes an aromatic cyclic structure including a heteroatom.

As briefly described above, the present invention is directed to multidentate, for example, tetradentate cyclometalated metal complexes. In one aspect, such complexes can be incorporated with heptacyclic or higher order materials. In another aspect, such complexes can be useful, for example, in displays and lighting applications.

In various aspects, the compounds of the present disclosure can comprise one or more of platinum (Pt) complexes, palladium (Pd) complexes, gold (Au) complexes, iridium (Ir) complexes, rhodium (Rh) complexes, ruthenium (Ru) complexes, iron (Fe) complexes, cobalt (Co) complexes, nickel (Ni) complexes, copper (Cu) complexes, zinc (Zn) complexes, silver (Ag) complexes, mercury (Hg) complexes, cadmium (Cd) complexes, zirconium (Zr) complexes, or other metal complexes not specifically recited herein which are capable of emitting light and are thus useful as an emissive materials in devices.

The term "each of V¹, V², V³ and V⁴ independently optionally is substituted for any one of V¹, V², V³ and V⁴," as used herein means that any one of V¹, V², V³, and V⁴ can be substituted for another of V¹, V², V³, and V⁴. For example, V¹ can be substituted for V², V³, or V⁴. In another example, V³ can be substituted for V¹, V², or V⁴. In one example, V² can be substituted for V¹. In another example, V³ can be substituted for V¹. In another example, V⁴ can be substituted for V². In another example, V³ can be substituted for V². In one aspect, V, as described herein, can be V¹, V², V³, or V⁴ as described herein. For example, V can be V¹. In another example, V can be V². In another example, V can be V³. In another example, V can be V⁴.

As used herein, the terms "compound" and "complex" are used interchangeably.


2. Compounds

In one aspect, disclosed herein are compounds comprising a metal, such as platinum (Pt), palladium (Pd), gold (Au), iridium (Ir), rhodium (Rh), ruthenium (Ru), iron (Fe), cobalt (Co), nickel (Ni), copper (Cu), zinc (Zn), silver (Ag), mercury (Hg), cadmium (Cd), or zirconium (Zr). The disclosed compounds can emit electromagnetic radiation. In another aspect, the emission of the disclosed compounds can be tuned, for example, from the ultraviolet to near-infrared, by, for example, modifying the ligand structure. In another aspect, the disclosed compounds can provide emission over a majority of the visible spectrum. In a specific example, the disclosed compounds can emit light over a range of from about 400 nm to about 700 nm. In another aspect, the disclosed compounds have improved stability and efficiency over traditional emission complexes. In yet another aspect, the disclosed compounds can be useful as luminescent labels in, for example, bio-applications, anti-cancer agents, emitters in organic light emitting diodes (OLED), or a combination thereof. In another aspect, the disclosed compounds can be useful in light emitting devices, such as, for example, compact fluorescent lamps (CFL), light emitting diodes (LED), incandescent lamps, and combinations thereof.

The disclosed compounds can be, for example, multidentate compounds.

7

Disclosed herein are compounds having the formula




wherein each of L¹, L², L³, and L⁴ independently is a substituted or unsubstituted aryl, cycloalkyl, cycloalkenyl, heterocyclyl, heteroaryl, carbene, or N-heterocyclic carbene, wherein each of Z¹, Z², and Z³ independently is present or absent, and if present each of Z¹, Z², and Z³ independently is A, A¹, or A².

wherein each of A, A¹, or A² independently is O, S, S=O, SO₂, Se, NR³, PR³, RP=O, CR¹R², C=O, SiR¹R², GeR¹R², BH, P(O)H, PH, NH, CR¹H, CH₂, SiH₂, SiHR¹, BH, or BR³,


wherein M is Pt, Pd, Au, Ir, Rh, Ru, Fe, Co, Ni, Cu, Zn, Ag, Hg, Cd, or Zr.

wherein at least one of L^1 , L^2 , L^3 , and L^4 comprises




wherein m and n independently is an integer from 0 to 4,

wherein each of V, X, and Y independently is V¹, V², V³, V⁴, O, S, S=O, SO₂, Se, NR³, PR³, R¹P=O, CR¹R², C=O, SiR¹R², GeR¹R², BH, P(O)H, PH, NH, CR¹H, CH₂, SiH₂, SiHR¹, BH, or BR³, or any one of



8

-continued



wherein at least one of V, X, and Y is V¹, V², V³, or V⁴.

wherein m and n independently is an integer from 0 to 4,

65 wherein each of V^1 , V^2 , V^3 and V^4 independently is coordinated to M, and wherein each of V^1 , V^2 , V^3 and V^4 independently is N, C, CH, P, B, SiH, or Si.



9

wherein each of R , R^1 , R^2 , R^3 , and R^4 , independently is hydrogen, aryl, cycloalkyl, cycloalkenyl, heterocyclyl, heteroaryl, alkyl, alkenyl, alkynyl, deuterium, halogen, hydroxyl, thiol, nitro, cyano, amino, a mono- or di-alkylamino, a mono- or diaryl amino, alkoxy, aryloxy, haloalkyl, aralkyl, ester, nitrile, isonitrile, alkoxycarbonyl, acylamino, alkoxycarbonylamino, aryloxycarbonylamino, sulfonylamino, sulfamoyl, carbamoyl, alkylthio, sulfinyl, ureido, phosphoramidate, mercapto, sulfo, carboxyl, hydrazino, substituted silyl, or polymerizable, or any conjugate or combination thereof,

wherein each of V^1 , V^2 , V^3 and V^4 independently optionally is substituted for any one of V^1 , V^2 , V^3 and V^4 .




In one aspect each of Z^1 , Z^2 , and Z^3 independently is present. In another aspect, Z^1 and Z^2 are present and Z^3 is absent. In yet another aspect, Z^2 and Z^3 are present and Z^1 is absent. In yet another aspect, Z^1 and Z^3 are present and Z^2 is absent. In yet another aspect, each of Z^1 , Z^2 , and Z^3 independently is absent. In another aspect, Z^1 and Z^2 are absent and Z^3 is present. In yet another aspect, Z^2 and Z^3 are absent and Z^1 is present. In yet another aspect, Z^1 and Z^3 are absent and Z^2 is present.

In one aspect, the compound can have the structure






10

-continued








11

-continued


**12**

In another aspect, the compound can have the structure:




13

-continued


**14**

-continued






15

-continued








wherein each of o and p independently is an integer of 0 to 4.

In another aspect, the compound can have the structure:


**16**

-continued




17

-continued





**18**

-continued




19

-continued

**20**

-continued

5



10

15

20

25


30

35

40

45


50



55





60

65







21

-continued








22

-continued







23

-continued





**24**

-continued







25

-continued





**26**

-continued




28

-continued




29

-continued




wherein each of o, p, and q independently is an integer of 0 to 4,

wherein each of Z and U independently is V^1 , V^2 , V^3 , V^4 , O, S, S=O, SO_2 , Se, NR^3 , PR^3 , $R^1P=O$, CR^1R^2 , C=O, SiR^1R^2 , GeR^1R^2 , BH, $P(O)H$, PH, NH, CR^1H , CH_2 , SiH_2 , $SiHR^1$, BH, or BR^3 , or any one of



30


-continued



wherein at least one of U, V, X, Y, and Z is V¹, V², V³, or V⁴.





wherein each R⁵ independently is hydrogen, aryl, cycloalkyl, cycloalkenyl, heterocyclyl, heteroaryl, alkyl, alkenyl, alkynyl, deuterium, halogen, hydroxyl, thiol, nitro, cyano, amino, a mono- or di-alkylamino, a mono- or diaryl amino, alkoxy, aryloxy, haloalkyl, aralkyl, ester, nitrile, isonitrile, alkoxycarbonyl, acylamino, alkoxycarbonylamino, aryloxy carbonylamino, sulfonylamino, sulfamoyl, carbamoyl, alkylthio, sulfinyl, ureido, phosphoramidate, mercapto, sulfo, carboxyl, hydrazino, substituted silyl, or polymerizable, or any conjugate or combination thereof

In one aspect, the compound can have the structure:







31

-continued





**32**

-continued







33

-continued





**34**

-continued







35

-continued





**36**

-continued







37

-continued





**38**

-continued







39

-continued






**40**

-continued








41

-continued

**42**


-continued



43


wherein each of o, p, q, and r independently is an integer of 0 to 4,

wherein each of U, Y¹, X¹, Z, and Z¹, independently is V¹, V², V³, V⁴, O, S, S=O, SO₂, Se, NR³, PR³, R¹P=O, CR¹R², C=O, SiR¹R², GeR¹R², BH, P(O)H, PH, NH, CR¹H, CH₂, SiH₂, SiHR¹, BH, or BR³, or any one of



44


-continued




wherein at least one of U, V, X, Y, and Z is V¹, V², V³, or V⁴,

wherein each R⁵ independently is hydrogen, aryl, cycloalkyl, cycloalkenyl, heterocyclyl, heteroaryl, alkyl, alkenyl, alkynyl, deuterium, halogen, hydroxyl, thiol, nitro, cyano, amino, a mono- or di-alkylamino, a mono- or diaryl amino, alkoxy, aryloxy, haloalkyl, aralkyl, ester, nitrile, isonitrile, alkoxycarbonyl, acylamino, alkoxycarbonylamino, aryloxycarbonylamino, sulfonylamino, sulfamoyl, carbamoyl, alkylthio, sulfinyl, ureido, phosphoramidate, amercapto, sulfo, carboxyl, hydrazino, substituted silyl, or polymerizable, or any conjugate or combination thereof.

In one aspect, in the disclosed compounds,



In one aspect, in the disclosed compounds,




In one aspect, at least two of L¹, L², L³, and L⁴ is substituted or un substituted aryl or heteroaryl.


45

In one aspect, at least one of V^1 , V^2 , V^3 , and V^4 is N. In another aspect, at least one of V^1 , V^2 , V^3 , and V^4 is C. In yet another aspect, at least one of V^1 , V^2 , V^3 , and V^4 is N and at least one of V^1 , V^2 , V^3 , and V^4 is C. In yet another aspect, at least two of V^1 , V^2 , V^3 , and V^4 is N and at least one of V^1 , V^2 , V^3 , and V^4 is C. In yet another aspect, at least one of V^1 , V^2 , V^3 , and V^4 is N and at least two of V^1 , V^2 , V^3 , and V^4 is C.


In one aspect, at least one of L^1 , L^2 , L^3 , and L^4 together with V^1 , V^2 , V^3 , and V^4 respectively can comprise one or more of the following structures:



In another aspect, at least one of L^1 , L^2 , L^3 , and L^4 together with V^1 , V^2 , V^3 , and V^4 respectively can comprise one or more of the following structures:




can comprise one or more of the following structures:




46

-continued




47

-continued




48

-continued




49

-continued




50


-continued



In one aspect,













can have the structure











51

-continued

**52**


-continued










, or

53

-continued




Such as for example,


**54**

-continued


5




10




15




20




25




30




35




40




45



50



55









60

65

55

-continued




In one aspect, each of m, n, o, p, q, or r can independently be 0. In another aspect, each of m, n, o, p, q, or r can independently be 0 or 1. In another aspect, each of m, n, o, p, q, or r can independently be 1.


The compound of any one claims 1-10, wherein the compound comprises at least one phenyl and at least one pyridine.

In one aspect, for any of the formulas illustrated in this disclosure,


56



are intended to mean that L and L' are either linked directly or that L and L' are linked by a linkage group, wherein each of the linkage groups can independently be an oxygen (O), sulfur (S), nitrogen (N), phosphor (P), carbon (C), silicon (Si) or boron (B). In another aspect,




can each independently represent one or more of the following structures:



In another aspect, for any of the formulas illustrated in this disclosure,




can represent one or more of the following structures:




57


-continued




In yet another aspect, for any of the formulas illustrated in this disclosure,




can each independently represent one or more of the following structures:



In still another aspect,



as shown in the disclosed compounds can be one of the following structures:

















In still another aspect, for any of the formulas illustrated in this disclosure,




58

can represent one or more of the following structures:




59

-continued







In one aspect, each of R^1 , R^2 , R^3 , R^4 , and R^5 can independently be hydrogen, aryl, cycloalkyl, cycloalkenyl, heterocyclyl, heteroaryl, alkyl, alkenyl, alkynyl, deuterium, halogen, hydroxyl, thiol, nitro, cyano, amino, a mono- or di-alkylamino, a mono- or diaryl amino, alkoxy, aryloxy, haloalkyl, aralkyl, ester, nitrile, isonitrile, alkoxycarbonyl, acylamino, alkoxycarbonylamino, aryloxycarbonylamino, sulfonylamino, sulfamoyl, carbamoyl, alkylthio, sulfinyl, ureido, phosphoramidate, mercapto, sulfo, carboxyl, hydrazino, substituted silyl, or polymerizable, or any conjugate or combination thereof. In another aspect, each of R^1 , R^2 , R^3 , R^4 , and R^5 can independently be aryl, cycloalkyl, cycloalkenyl, heterocyclyl, heteroaryl, alkyl, alkenyl, alkynyl, halogen, hydroxyl, thiol, nitro, amino, haloalkyl, or any conjugate or a combination thereof. In yet another aspect, each of R^1 , R^2 , R^3 , R^4 , and R^5 can independently be aryl, cycloalkyl, cycloalkenyl, heterocyclyl, heteroaryl, alkyl, alkenyl, halogen, or hydroxyl, or a combination thereof.

In one aspect, for any of the metal complexes illustrated in this disclosure, can comprise one or more of the following structures. In another aspect, they can also comprise other structures or portions thereof not specifically recited herein, and the present invention is not intended to be limited to those structures or portions thereof specifically recited.







60

-continued



61

-continued




62

-continued

5

10


15



20

25

30




35

40

45


50



55





60

65







63

-continued



64

-continued



5

10

15

20

25

30

35

40

45

50





55

60

65





65

-continued







66

-continued



67

-continued



68

-continued

5

10

15

20

25

30

35

40





45

50

55


60

65




69

-continued



70

-continued



5

10

15

20

25

30

35

40







45

50

55


60

65




71

-continued

**72**

-continued



5

10

15

20

25

30

35

40





45

50

55


60

65



73

-continued




74

-continued

5

10

15




20

25

30


35



40

45



50



55





60

65







75

-continued




76

-continued







77

-continued




78

-continued



79

-continued


**80**

-continued

5

10


15



20

25

30




35

40

45



50



55





60

65



81

-continued

**82**

-continued

5

10

15

20

25

30

35

40





45

50

55





60

65







83

-continued


**84**

-continued




85

-continued


**86**

-continued










87

-continued





**88**

-continued



89

-continued



90

-continued

5

10

15

20

25

30

35

40





45

50

55





60

65







91

-continued




92

-continued




93

-continued




94

-continued



95


-continued



5

10


15



20

25


30



35

40

45



50





55

60

65


96

-continued




97

-continued



98


-continued



5

10


15




20

25

30




35



40

45



50



55





60

65







99

-continued







100

-continued







101

-continued



102

-continued



5

10

15

20

25

30

35

40

45

50





55

60

65





103

-continued







104

-continued



105

-continued



106

-continued

5

10

15

20

25

30

35

40





45

50

55





60

65







107

-continued





**108**

-continued







109

-continued





**110**

-continued



111

-continued



112

-continued

5

10

15

20

25

30

35

40





45

50

55


60

65




113

-continued





**114**

-continued







115

-continued






**116**

-continued



117


-continued



118

-continued

5




10

15

20

25





30

35

40

45


50



55


60

65




119

-continued







120

-continued







121

-continued





**122**

-continued







123

-continued





**124**

-continued







125

-continued


**126**

-continued




127

-continued





**128**

-continued






129

-continued





**130**

-continued




131

-continued

**132**

-continued

5



10

15

20

25

30

35

40




45

50

55





60

65



133

-continued

**134**

-continued

5

10

15

20

25

30

35

40





45

50

55





60

65



135

-continued

**136**

-continued

5

10

15

20

25

30

35

40





45

50

55


60

65




137

-continued







138

-continued







139

-continued







140

-continued



141

-continued

**142**

-continued

5

10

15

20

25

30

35

40





45

50

55





60

65



143

-continued

**144**

-continued

5

10

15

20

25

30

35

40





45

50

55





60

65






145


-continued

**146**

-continued




In one aspect, the compound has the structure:



PtN''3PPy

147

such as, for example




It should be noted that each of multiple recitations or illustrations of a particular structure, reference letter or numeral, etc., appearing in one or more structures of this disclosure can represent the same or different species, and that both aspects wherein they represent the same and wherein they represent different species are intended to be disclosed.

3. Methods

The disclosed compound can be made by one or more of the methods of synthesizing disclosed herein.


In one aspect, the disclosed compounds can be made by a synthesis comprising one or more of the following reactions or steps:



X = I, Br, Cl, OTf
 $L^a = L^1$ or L^4
 $L^b = L^2$ or L^3

148

-continued




$L^a = L^1$ or L^4
 $L^b = L^2$ or L^3


X = I, Br,
 $L^a = L^1$ or L^4
 $L^b = L^2$ or L^3

149

-continued




E



F

150

-continued



G


$L^a = L^1 \text{ or } L^4$
 $L^b = L^2 \text{ or } L^3$


30

In another aspect, the disclosed compounds can be made by a synthesis comprising one or more of the following reactions or steps:

151



152







155

In another aspect, the disclosed compounds can be made by a synthesis comprising one or more of the following reactions or steps:




156

-continued




In yet another aspect, some of the disclosed compounds can be made by a synthesis comprising one or more of the following reactions or steps:



157


-continued

158




30

For example, a platinum compound can be made by a reaction comprising one or more of the following reactions or steps:




1





2

3

159





PtN''3PPy




5

-continued



1

160



4

4. Devices

As briefly described above, the present invention is directed to metal compounds. In one aspect, the compounds disclosed herein can be used as host materials for OLED applications, such as full color displays.

The disclosed compounds can be useful in a wide variety of applications, such as, for example, lighting devices. In a particular aspect, one or more of the compounds can be host materials for an organic light emitting display device.

The compounds are useful in a variety of applications. As light emitting materials, the compounds can be useful in organic light emitting diodes (OLED)s, luminescent devices and displays, and other light emitting devices. The device can be a phosphorescent OLED device. The device can also be a fluorescent OLED device.

In one aspect, the device is a photovoltaic device. In another aspect, the device is a luminescent display device. In yet another aspect, the device is a light emitting device.

The energy profile of the compounds can be tuned by varying the structure of the ligand surrounding the metal center. For example, compounds having a ligand with electron withdrawing substituents will generally exhibit different properties, than compounds having a ligand with electron donating substituents. Generally, a chemical structural change affects the electronic structure of the compound, which thereby affects the electrical transport and transfer functions of the material. Thus, the compounds of the present invention can be tailored or tuned to a specific application that desires an energy or transport characteristic.

In another aspect, the disclosed compounds can provide improved efficiency and/or operational lifetimes in lighting devices, such as, for example, organic light emitting devices, as compared to conventional materials.

In other various aspects, the disclosed compounds can be useful as, for example, host materials for organic light emitting diodes, lighting applications, and combinations thereof.

In one embodiment, the compounds can be used in an OLED. FIG. 1 shows a cross-sectional view of an OLED **100**, which includes substrate **102** with an anode **104**, which is typically a transparent material, such as indium tin oxide, a layer of hole-transporting material(s) (HTL) **106**, a layer of light processing material **108**, such as an emissive material (EML) including an emitter and a host, a layer of electron-transporting material(s) (ETL) **110**, and a metal cathode layer **112**.

In one aspect, a light emitting device, such as, for example, an OLED, can comprise one or more layers. In various aspects, any of the one or more layers can comprise indium tin oxide (ITO), poly(3,4-ethylenedioxythiophene) (PEDOT), polystyrene sulfonate (PSS), N,N'-di-1-naphthyl-

N,N'-diphenyl-1,1'-biphenyl-4,4'-diamine (NPD), 1,1-bis((di-4-tolylamino)phenyl)cyclohexane (TAPC), 2,6-Bis(N-carbazolyl)pyridine (mCpy), 2,8-bis(diphenylphosphoryl) dibenzothiophene (PO15), LiF, Al, or a combination thereof.

In this embodiment, the layer of light processing material **108** can comprise one or more of the disclosed compounds optionally together with a host material. The host material can be any suitable host material known in the art. The emission color of an OLED is determined by the emission energy (optical energy gap) of the light processing material **108**, which as discussed above can be tuned by tuning the electronic structure of the emitting compounds and/or the host material. Both the hole-transporting material in the HTL layer **106** and the electron-transporting material(s) in the ETL layer **110** can comprise any suitable hole-transporter known in the art. A selection of which is well within the purview of those skilled in the art.

It will be apparent that the compounds of the present invention can exhibit phosphorescence. Phosphorescent OLEDs (i.e., OLEDs with phosphorescent emitters) typically have higher device efficiencies than other OLEDs, such as fluorescent OLEDs. Light emitting devices based on electrophosphorescent emitters are described in more detail in WO2000/070655 to Baldo et al., which is incorporated herein by this reference for its teaching of OLEDs, and in particular phosphorescent OLEDs.

The compounds of the invention can be made using a variety of methods, including, but not limited to those recited in the examples provided herein. In other aspects, one of skill in the art, in possession of this disclosure, could readily determine an appropriate method for the preparation of an iridium complex as recited herein.

EXAMPLES

The following examples are put forth so as to provide those of ordinary skill in the art with a complete disclosure and description of how the compounds, compositions, articles, devices and/or methods claimed herein are made and evaluated, and are intended to be purely exemplary of the invention and are not intended to limit the scope of what the inventors regard as their invention. Efforts have been made to ensure accuracy with respect to numbers (e.g., amounts, temperature, etc.), but some errors and deviations should be accounted for. Unless indicated otherwise, parts are parts by weight, temperature is in $^\circ\text{C}$. or is at ambient temperature, and pressure is at or near atmospheric.


Hereinafter, the preparation method of the compounds for the displays and lighting applications will be illustrated. However, the following embodiments are only exemplary and do not limit the scope of the present invention. Temperatures, catalysts, concentrations, reactant compositions,

161


and other process conditions can vary, and one of skill in the art, in possession of this disclosure, could readily select appropriate reactants and conditions for a desired complex.

1. Prophetic Synthetic Routes

A general proposed synthetic route for the compounds disclosed herein includes:






$X = I, Br, Cl, OTf$
 $L^a = L^1 \text{ or } L^4$
 $L^b = L^2 \text{ or } L^3$




162

-continued




163


-continued



$L^a = L^1 \text{ or } L^4$
 $L^b = L^2 \text{ or } L^3$

**164**


-continued




$L^a = L^1 \text{ or } L^4$
 $L^b = L^2 \text{ or } L^3$


A proposed synthesis for the disclosed compounds herein also includes:

165




166






169

A proposed synthesis for some of the metal compounds, such as platinum or palladium compounds, disclosed herein is:




170

-continued




A proposed synthesis for a metal compound is:



171

-continued


172




30

2. Synthesis of PtN3"PPy



Platinum complex PtN3"PPy was prepared according to the following scheme:



173





PtN''3PPy




5

-continued



1

174



4

Synthesis of 2-(3-bromophenyl)pyridine 1: To a three-necked flask equipped with a magnetic stir bar and a condenser, added 3-bromophenylboronic acid (8033 mg, 40 mmol) and K₂CO₃ (12.16 g, 88 mmol). The flask was sealed and then evacuated and backfilled with nitrogen. Repeated the evacuation and backfill procedure four additional times. After that solvents DME (100 mL), EtOH (32 mL) and H₂O (44 mL) were added independently by syringe. The mixture was bubbled with nitrogen through a needle for 30 minutes. Then 2-bromopyridine (3.89 mL, 40 mmol) and Pd(PPh₃)₄ (924 mg, 0.8 mmol) were added under the atmosphere of nitrogen. The mixture was heated to reflux (about 95-105° C.) in an oil bath. The reaction was monitored by TLC and about 24 hours later the reaction was completed. Then cooled down to ambient temperature and water was added until the salt dissolved completely. Then the organic layer was separated and the aqueous layer was extracted with ethyl acetate for twice. The combined organic layer was dried over sodium sulfate. Then filtered and washed with ethyl acetate. The filtrate was concentrated under reduced pressure using a rotary evaporator and the residue was purified through column chromatography on silica gel using hexane and ethyl acetate (20:1) as eluent to afford the desired product 2-(3-bromophenyl)pyridine 1 as a colorless liquid 8.33 g in 89% yield. ¹H NMR (CDCl₃, Me₄Si, 400 MHz): δ 7.25-7.28 (m, 1H), 7.34 (td, J=8.0, 1.2 Hz, 1H), 7.53-7.56 (m, 1H), 7.71 (dd, J=8.0, 0.8 Hz, 1H), 7.75-7.80 (m, 1H), 7.90-7.93 (m, 1H), 8.18-8.19 (m, 1H), 8.70-8.81 (m, 1H). ¹H NMR (DMSO-d₆, 400 MHz): δ 7.39-7.42 (m, 1H), 7.47 (t, J=8.0 Hz, 1H), 7.65 (dt, J=8.4, 0.8 Hz, 1H), 7.91 (tt, J=7.2, 0.8 Hz, 1H), 8.02-8.04 (m, 1H), 8.09-8.12 (m, 1H), 8.29-8.30 (m, 1H), 8.68-8.70 (m, 1H).

Synthesis of 2-(4-chloro-3-nitrophenyl)pyridine 2: To a three-necked flask equipped with a magnetic stir bar and a condenser, added 4-chloro-3-nitrophenylboronic acid (3968 mg, 19.7 mmol) and NaHCO₃ (3310 mg, 39.4 mmol). The flask was sealed and then evacuated and backfilled with nitrogen. Repeated the evacuation and backfill procedure four additional times. After that solvents DMF (40 mL) and H₂O (20 mL) were added independently by syringe. The mixture was bubbled with nitrogen through a needle for 30 minutes. Then 2-bromopyridine (3.11 mL, 21.7 mmol) and Pd(PPh₃)₄ (1138 mg, 0.99 mmol) were added under the atmosphere of nitrogen. The mixture was heated to reflux (about 95-105° C.) in an oil bath. The reaction was monitored by TLC and after about 4.5 hours the reaction was completed. Then cooled down to ambient temperature and water was added. Then the mixture was filtered and washed with ethyl acetate. The organic layer of the filtrate was separated and the aqueous layer was extracted with ethyl acetate for twice. The combined organic layer was dried over sodium sulfate. Then filtered and washed with ethyl acetate.

15 The filtrate was concentrated under reduced pressure using a rotary evaporator and the residue was purified through column chromatography on silica gel using hexane and ethyl acetate (20:1-15:1-10:1-5:1) as eluent to afford the desired product 2-(4-chloro-3-nitrophenyl)pyridine 2 as a grey solid 2.65 g in 57% yield. ¹H NMR (DMSO-d₆, 400 MHz): δ 7.47-7.50 (m, 1H), 7.92 (d, J=8.4 Hz, 1H), 7.99 (td, J=7.6, 0.8 Hz, 1H), 8.16 (d, J=8.0 Hz, 1H), 8.44 (dd, J=8.0, 0.8 Hz, 1H), 8.74-8.75 (m, 1H), 8.77 (d, J=2.0 Hz, 1H).

20 Synthesis of 2-chloro-5-(pyridin-2-yl)benzenamine 3: To a single-necked flask equipped with a magnetic stir bar, added 2-(4-chloro-3-nitrophenyl)pyridine 2 (2.65 g, 11.29 mmol) and SnCl₂ (21.41 g, 112.90 mmol). Then a condenser was equipped and the system was evacuated and backfilled with nitrogen. Repeated the evacuation and backfill procedure twice additional times. After that solvent EtOH (150 mL) was added under the atmosphere of nitrogen. The mixture was heated to 60-70° C. in an oil bath. The reaction was monitored by TLC and after about 3 hours the reaction was completed. Then cooled down to ambient temperature and quenched with water. Then the pH of the mixture was adjusted to 9-10 using 1 N NaOH aqueous solution. Filtered and washed with ethyl acetate. The organic layer of the filtrate was separated and the aqueous layer was extracted with ethyl acetate for three times. The combined organic layer was dried over sodium sulfate. Then filtered and washed with ethyl acetate. The filtrate was concentrated under reduced pressure using a rotary evaporator and the residue was purified through column chromatography on silica gel using hexane and ethyl acetate (5:1-3:1-2:1) as eluent to afford the desired product 2-chloro-5-(pyridin-2-yl)benzenamine 3 as a colorless liquid 2.03 g in 88% yield. ¹H NMR (DMSO-d₆, 400 MHz): δ 5.48 (bs, 2H), 7.23 (dd, J=8.0, 2.0 Hz, 1H), 7.29 (d, J=8.0 Hz, 1H), 7.33-7.36 (m, 1H), 7.60 (d, J=2.0 Hz, 1H), 7.82-7.89 (m, 2H), 8.63-8.64 (m, 1H).

35 Synthesis of 3-(pyridin-2-yl)-5H-dibenzo[b,f]azepine 4: To an oven dried pressure vessel equipped with a magnetic stir bar, added Pd₂(dba)₃ (268 mg, 0.29 mmol), DavePhos (346 mg, 0.88 mmol) and ^tBuONa (2817 mg, 29.31 mmol). The vessel was evacuated and backfilled with nitrogen. Repeated the evacuation and backfill procedure four additional times. Then a degassed solution of 2-chloro-5-(pyridin-2-yl)benzenamine 3 (2000 mg, 9.77 mmol) and 2-bromostyrene (1.52 mL, 11.72 mmol) in dioxane (20 mL) was added under the atmosphere of nitrogen. The sealed vessel was then placed in a preheated oil bath at a temperature of 110° C. The reaction was stirred and monitored by TLC and after about 24 hours the reaction was completed. Cooled down to ambient temperature and quenched with water. Then diluted with ethyl acetate and stirred for 10 minutes, filtered and washed with ethyl acetate. The organic layer of

175

the filtrate was separated and the aqueous layer was extracted with ethyl acetate for three times. The combined organic layer was dried over sodium sulfate. Then filtered and washed with ethyl acetate. The filtrate was concentrated under reduced pressure using a rotary evaporator and the residue was purified through column chromatography on silica gel using hexane and ethyl acetate (5:1-3:1) as eluent to afford the desired product 3-(pyridin-2-yl)-5H-dibenzo[b,f]azepine 4 as a brown-yellow solid 1.33 g in 50% yield. ¹H NMR (DMSO-d₆, 400 MHz): δ 6.10 (s, 2H), 6.65 (d, J=8.0 Hz, 1H), 6.69 (td, J=7.6, 1.2 Hz, 1H), 6.76 (dd, J=7.6, 1.6 Hz, 1H), 6.85 (d, J=8.0 Hz, 1H), 6.98 (td, J=8.0, 1.6 Hz, 1H), 7.13 (s, 1H), 7.33-7.39 (m, 2H), 7.47 (d, J=1.6 Hz, 1H), 7.82-7.89 (m, 2H), 8.64 (dd, J=4.8, 0.8 Hz, 1H).

Synthesis of 3-(pyridin-2-yl)-5-(3-(pyridin-2-yl)phenyl)-5H-dibenzo[b,f]azepine 5: To an oven dried pressure vessel equipped with a magnetic stir bar, added 3-(pyridin-2-yl)-5H-dibenzo[b,f]azepine 4 (1.33 g, 4.92 mmol), Pd₂(dba)₃ (180 mg, 0.20 mmol), JohnPhos (118 mg, 0.39 mmol) and ^tBuONa (756 mg, 7.87 mmol). The vessel was evacuated and backfilled with nitrogen. Repeated the evacuation and backfill procedure four additional times. Then a degassed solution of 2-(3-bromophenyl)pyridine 1 (1728 mg, 7.38 mmol) in toluene (20 mL) was added under the atmosphere of nitrogen. The sealed vessel was then placed in a preheated oil bath at a temperature of 95-105° C. The reaction was stirred and monitored by TLC and after about 4 days the reaction was completed. Cooled down to ambient temperature. The solvent was removed under reduced pressure using a rotary evaporator and the residue was purified through column chromatography on silica gel using hexane and ethyl acetate (5:1-3:1) as eluent to afford the desired ligand 3-(pyridin-2-yl)-5-(3-(pyridin-2-yl)phenyl)-5H-dibenzo[b,f]azepine 5 as a brown solid 1.42 g in 68% yield. ¹H NMR (DMSO-d₆, 400 MHz): δ 6.25 (dd, J=8.0, 2.4 Hz, 1H), 6.97-6.98 (m, 1H), 7.01 (s, 2H), 7.11 (t, J=8.0 Hz, 1H), 7.23-7.27 (m, 1H), 7.29 (d, J=7.6 Hz, 1H), 7.38-7.42 (m, 1H), 7.47-7.51 (m, 1H), 7.61 (s, 1H), 7.63 (s, 1H), 7.65 (dd, J=7.2, 1.6 Hz, 1H), 7.68 (dd, J=7.6, 1.6 Hz, 1H), 7.71 (d, J=8.4 Hz, 1H), 7.78 (td, J=7.6, 2.0 Hz, 1H), 7.92 (td, J=8.0, 1.6 Hz, 1H), 8.11 (d, J=8.0, 1H), 8.20 (dd, J=8.0, 2.0 Hz, 1H), 8.33 (d, J=2.0 Hz, 1H), 8.51 (dd, J=4.8, 0.8 Hz, 1H), 8.71 (dd, J=4.8, 0.8 Hz, 1H).


Synthesis of platinum complex PtN³3PPy: To an oven dried pressure vessel equipped with a magnetic stir bar, ligand 3-(pyridin-2-yl)-5-(3-(pyridin-2-yl)phenyl)-5H-dibenzo[b,f]azepine 5 (84.7 mg, 0.20 mmol), K₂PtCl₄ (87.2 mg, 0.21 mmol) and ⁿBu₄NCl (5.5 mg, 0.02 mmol). The vessel was taken into a glove box. Then solvent acetic acid (12 mL) was added. The mixture was bubbled with nitrogen for 30 minutes. Then the vessel was sealed and taken out of the glove box and stirred at ambient temperature for 18 hours. After that the mixture was heated in an oil bath at a temperature of 110° C. for another 18 hours. Cooled down to ambient temperature and water (about 24 mL) was added. The precipitate was collected through filter and washed with water for three times. The precipitate was dried in air and purified through column chromatography on silica gel using dichloromethane as eluent to obtain a crude product which was further purified by recrystallization in dichloromethane and ether at refrigerator to get the desired platinum complex PtN³3PPy as a brown-yellow solid 5.9 mg in 4.8% yield. ¹H NMR (DMSO-d₆, 400 MHz): δ 6.43 (d, J=8.0 Hz, 1H), 6.75 (d, J=8.4 Hz, 1H), 6.92 (d, J=7.2 Hz, 1H), 6.98-7.07 (m, 5H), 7.19 (dd, J=7.4, 1.6 Hz, 1H), 7.58-7.63 (m, 3H), 7.67 (d, J=8.0 Hz, 1H), 8.11 (d, J=7.2 Hz, 1H), 8.15 (d, J=7.6 Hz, 1H), 8.21 (d, J=8.0 Hz, 1H), 8.11 (d, J=8.0, 1H), 8.25 (d,

176

J=7.6 Hz, 1H), 9.15 (d, J=5.2 Hz, 1H), 8.17 (d, J=5.2 Hz, 1H); HRMS (MALDI/DHB) for C₃₀H₂₀N₃Pt [M+H]⁺: calcd 617.13, found 617.33.

3. Synthesis of PtN³3N

Platinum complex PtN³3N can be prepared according to the following scheme:



Synthesis of 3-(pyridin-2-yl)-5-(9-(pyridin-2-yl)-9H-carbazol-2-yl)-5H-dibenzo[b,f]azepine Ligand N³3N: To a dry Schlenk tube equipped with a magnetic stir bar, added of 3-(pyridin-2-yl)-5H-dibenzo[b,f]azepine 4 (92 mg, 0.34


177

mmol, 1.0 eq), 2-bromo-9-(pyridin-2-yl)-9H-carbazole (132 mg, 0.41 mmol, 1.2 eq), $\text{Pd}_2(\text{dba})_3$ (9 mg, 0.010 mmol, 0.03 eq), JohnPhos (6 mg, 0.020 mmol, 0.06 eq) and $^t\text{BuONa}$ (52 mg, 0.54 mmol, 1.6 eq). The tube was evacuated and back-filled with nitrogen and this evacuation/back-fill procedure was repeated for another twice. Then dry solvents toluene (4 mL) and dioxane (3 mL) were added under the atmosphere of nitrogen, the tube was then sealed quickly. And then the mixture was stirred in an oil bath at a temperature of 95-105° C. The reaction was monitored by TLC. 19 hours later, much of the starting material **4** was not consumed. So more $\text{Pd}_2(\text{dba})_3$ (6 mg, 0.0067 mmol, 0.02 eq), and SPhos (5.6 mg, 0.0134 mmol, 0.04 eq), $^t\text{BuONa}$ (16 mg, 0.21 mmol, 0.5 eq) were added. The mixture was stirred in an oil bath at a temperature of 95-105° C. for another 7 hours, cooled down to ambient temperature. The mixture was concentrated and the residue was purified through column chromatography on silica gel using hexane/ethyl acetate (20:1-10:1-5:1-3:1) as eluent to obtain the desired product Ligand N³N as a brown solid 135 mg in 78% yield. ¹H NMR (DMSO-*d*₆, 400 MHz): δ 6.26 (dd, J=8.4, 2.4 Hz, 1H), 6.73 (d, J=1.6 Hz, 1H), 6.98 (s, 2H), 7.21 (t, J=7.6 Hz, 1H), 7.26-7.31 (m, 2H), 7.41-7.52 (m, 3H), 7.60-7.70 (m, 5H), 7.79-7.83 (m, 2H), 7.93-7.97 (m, 2H), 8.11 (d, J=7.2 Hz, 1H), 8.18 (dd, J=7.6, 2.4 Hz, 1H), 8.36 (d, J=1.6 Hz, 1H), 8.40 (dd, J=4.8, 2.0 Hz, 1H), 8.72-8.73 (m, 1H).

Synthesis of 3-(pyridin-2-yl)-5-(9-(pyridin-2-yl)-9H-carbazol-2-yl)-5H-dibenzo[b,f]azepine platinum complex PtN³N: To a dry pressure tube equipped with a magnetic stir bar, added 3-(pyridin-2-yl)-5-(9-(pyridin-2-yl)-9H-carbazol-2-yl)-5H-dibenzo[b,f]azepine Ligand N³N (51 mg, 0.1 mmol, 1.0 eq), K_2PtCl_4 (42 mg, 0.1 mmol, 1.0 eq) and $^t\text{Bu}_4\text{NCl}$ (2.8 mg, 0.01 mmol, 0.1 eq). Then the tube was taken into a glove box. Solvent acetic acid (6 mL) was added. The mixture was bubbled with nitrogen for 30 minutes and then the tube was sealed. The tube was taken out of the glove box and the mixture was stirred in an oil bath at a temperature of 108-115° C. for 18.5 hours. Then the mixture was cooled down to ambient temperature and water (12 mL) was added slowly. The precipitate was filtered off and washed with water for three times. Then the solid was dried in air under reduced pressure. The collected solid was purified through column chromatography on silica gel using dichloromethane/hexane (1:1) as eluent to obtain the desired product PtN³N 4.5 mg in 6% yield.






What is claimed is:

1. A compound having a formula selected from:




178

-continued




179

-continued




180

-continued







182

-continued







183

-continued





**184**

-continued







185

-continued





**186**

-continued






187

-continued

**188**

-continued



50





55

60

65






189

-continued




190

-continued







192

-continued







193

-continued







194

-continued







195

-continued





**196**

-continued







197

-continued





**198**

-continued







199

-continued





**200**

-continued







201

-continued





**202**

-continued




203

-continued

**204**

-continued

5



10

15

20

25

30

35

40





45

50

55





60

65




206

-continued



207

-continued




wherein each of A or A^1 independently is O, S, S=O, SO_2 , Se, NR^3 , PR^3 , $RP=O$, CR^1R^2 , $C=O$, SiR^1R^2 , GeR^1R^2 , BH, P(O)H, PH, NH, CR^1H , CH_2 , SiH_2 , $SiHR^1$, BH, or BR^3 ,

wherein M is Pt, Pd, Au, Ir, Rh, Ru, Fe, Co, Ni, Cu, Zn, Ag, Hg, Cd, or Zr,

wherein each of m and n independently is an integer from 0 to 4,


wherein each X, independently is V^1 , V^2 , V^3 , V^4 , O, S=O, SO_2 , Se, NR^3 , PR^3 , $R^1P=O$, CR^1R^2 , $C=O$, SiR^1R^2 , GeR^1R^2 , BH, P(O)H, PH, NH, CR^1H , CH_2 , SiH_2 , $SiHR^1$, BH, or BR^3 , or any one of

208




209

-continued




wherein each of U, V, X¹, Y, Y¹, Z, and Z¹ independently is V¹, V², V³, V⁴, O, S, S=O, SO₂, Se, NR³, PR³, R¹P=O, CR¹R², C=O, SiR¹R², GeR¹R², BH, P(O)H, PH, NH, CR¹H, CH₂, SiH₂, SiHR¹, BH, or BR³, or any one of



210

-continued



wherein at least one of U, V, X, X¹, Y¹, Y¹, Z, or Z¹ is V¹, V², V³, or V⁴, wherein each of m and n independently is an integer from 0 to 4,

wherein each of V¹, V², V³, and V⁴ independently is coordinated to M, and wherein each of V¹, V², V³, and V⁴ independently is N, C, CH, P, B, SiH, or Si,

wherein each of R, R¹, R², R³, R⁴, R⁵, and R⁶ independently is hydrogen, aryl, cycloalkyl, cycloalkenyl, heterocyclyl, heteroaryl, alkyl, alkenyl, alkynyl, deuterium, halogen, hydroxyl, thiol, nitro, cyano, amino, a mono- or di-alkylamino, a mono- or diaryl amino, alkoxy, aryloxy, haloalkyl, aralkyl, ester, nitrile, isonitrile, alkoxy carbonyl, acylamino, alkoxy carbonylamino, aryloxy carbonylamino, sulfonylamino, sulfamoyl, carbamoyl, alkylthio, sulfinyl, ureido, phosphoramidate, mercapto, sulfo, carboxyl, hydrazino, substituted silyl, or polymerizable, or any conjugate or combination thereof,

wherein each of V¹, V², V³ and V⁴ independently optionally is substituted for any one of V¹, V², V³ and V⁴, wherein each of o, p, q, and r independently is an integer of 0 to 4.

2. The compound of claim 1, wherein at least one of V¹, V², V³, and V⁴ is N.

3. The compound of claim 1, wherein the compound comprises at least one phenyl and at least one pyridine.

4. The compound of claim 1, wherein M is Pt or Pd.

5. The compound of claim 1, wherein M is Pt.


6. A photovoltaic device comprising one or more compounds of claim 1.

7. A luminescent display device comprising one or more compounds of claim 1.

211

8. A light emitting device comprising one or more compounds of claim 1.

9. The compound of claim 1, wherein each of U, V, X, X¹, Y, Z, and Z¹ independently is N, NH, C, CH, or



10. A device comprising one or more compounds of claim 1.


11. The device of claim 10, wherein the device is a full color display.

12. The device of claim 10, wherein the device is an organic light emitting diode.

13. The device of claim 12, wherein the organic light emitting diode is a phosphorescent OLED device.





14. The device of claim 12, wherein the organic light emitting diode is a fluorescent OLED device.

15. A compound, wherein the compound has one of the following structures:




212

-continued



213

-continued




214

-continued

5

10



15



20

25


30



35

40

45





50

55


60

65




215

-continued



216


-continued



5

10


15



20

25


30




35

40

45




50




55

60







65







217

-continued







218

-continued



219

-continued




220

-continued

5

10


15



20

25


30



35

40

45




50

55





60

65







221

-continued



222

-continued



5

10

15

20

25

30

35

40

45

50


55

60

65








223

-continued




224

-continued



225

-continued


**226**

-continued

5

10


15



20

25


30



35

40

45





50

55





60

65







227

-continued





**228**

-continued







229

-continued





**230**

-continued







231

-continued





**232**

-continued







233

-continued


**234**

-continued










235

-continued






**236**

-continued







237

-continued






**238**

-continued







239

-continued





**240**

-continued







241

-continued


**242**

-continued




243

-continued


**244**

-continued










245

-continued





**246**

-continued







247

-continued

**248**

-continued



5

10

15

20

25

30

35

40

45

50





55

60

65





249

-continued



250

-continued



5

10

15

20

25

30

35

40

45

50





55

60

65

251

-continued



252

-continued

5

10

15

20

25

30

35

40





45

50

55





60

65







253

-continued





**254**

-continued







255

-continued





**256**

-continued



257

-continued

**258**

-continued

5

10

15

20

25

30

35

40






45

50

55





60

65







259

-continued








**260**

-continued



261

-continued

**262**

-continued

5

10

15

20

25

30

35

40






45

50

55






60

65








263

-continued


**264**

-continued




265

-continued





**266**

-continued







267

-continued





**268**

-continued







269

-continued

**270**

-continued







55

60





65

271

-continued





**272**

-continued



273

-continued

**274**

-continued

5

10

15

20

25

30

35

40





45

50

55





60

65




275

-continued

**276**

-continued



5

10

15

20

25

30

35

40

45

50





55

60





65

277

-continued





**278**

-continued







279

-continued


**280**

-continued




281

-continued





**282**

-continued




283

-continued

**284**

-continued

5




10

15

20

25


30



35

40

45




50

55





60

65







285

-continued





**286**

-continued



287

-continued

**288**

-continued

5

10

15

20

25

30

35

40





45

50

55





60

65







289

-continued




**290**

-continued



291


-continued

**292**


wherein each of R^1 , R^2 , R^3 , R^4 , R^5 , and R^6 independently is hydrogen, aryl, cycloalkyl, cycloalkenyl, heterocycl, heteroaryl, alkyl, alkenyl, alkynyl, deuterium, halogen, hydroxyl, thiol, nitro, cyano, amino, a mono- or di-alkylamino, a mono- or diaryl amino, alkoxy, aryloxy, haloalkyl, aralkyl, ester, nitrile, isonitrile, alkoxycarbonyl, acylamino, alkoxycarbonylamino, aryloxycarbonylamino, sulfonylamino, sulfamoyl, carbamoyl, alkylthio, sulfinyl, ureido, phosphoramidate, mercapto, sulfo, carboxyl, hydrazino, substituted silyl, or polymerizable, or any conjugate or combination thereof, and

each of o, p, q, and r independently is an integer of 0 to 4.

16. A compound, wherein the compound has the structure:



or



* * * * *

专利名称(译)	金属化合物，其方法和用途		
公开(公告)号	US9882150	公开(公告)日	2018-01-30
申请号	US14/430454	申请日	2013-09-24
申请(专利权)人(译)	亚利桑那州BOARD FOR并代表美国亚利桑那州立大学校董		
当前申请(专利权)人(译)	亚利桑那州BOARD FOR并代表美国亚利桑那州立大学校董		
[标]发明人	LI JIAN LI GUIJIE		
发明人	LI, JIAN LI, GUIJIE		
IPC分类号	H01L51/00 C09K11/06 C07F15/00 H01L51/42 H01L51/50		
CPC分类号	H01L51/0087 C09K11/06 C07F15/0086 Y02E10/549 C09K2211/1007 C09K2211/1029 C09K2211/1033 C09K2211/1037 C09K2211/1044 C09K2211/1059 C09K2211/185 H01L51/42 H01L51/5012 H01L51/5016 H01L51/5036		
代理机构(译)	FISH & RICHARDSON P.C.		
优先权	61/704880 2012-09-24 US		
其他公开文献	US20150228914A1		
外部链接	Espacenet USPTO		

摘要(译)

本文公开了可用于器件的金属化合物，例如OLED。

