



US009214494B2

(12) **United States Patent**
Sakariya et al.

(10) **Patent No.:** **US 9,214,494 B2**
(45) **Date of Patent:** **Dec. 15, 2015**

(54) **ACTIVE MATRIX DISPLAY PANEL WITH
GROUND TIE LINES**

(71) Applicant: **LuxVue Technology Corporation**,
Santa Clara, CA (US)

(72) Inventors: **Kapil V. Sakariya**, Los Altos, CA (US);
Andreas Bibl, Los Altos, CA (US);
Hsin-Hua Hu, Los Altos, CA (US)

(73) Assignee: **LuxVue Technology Corporation**,
Santa Clara, CA (US)

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 0 days.

(21) Appl. No.: **14/640,979**

(22) Filed: **Mar. 6, 2015**

(65) **Prior Publication Data**

US 2015/0179703 A1 Jun. 25, 2015

Related U.S. Application Data

(63) Continuation of application No. 13/842,793, filed on
Mar. 15, 2013, now Pat. No. 9,029,880, which is a
continuation-in-part of application No. 13/710,443,
filed on Dec. 10, 2012.

(51) **Int. Cl.**
H01L 27/15 (2006.01)
H01L 27/12 (2006.01)
H01L 25/075 (2006.01)
H01L 33/20 (2010.01)

(Continued)

(52) **U.S. Cl.**
CPC **H01L 27/156** (2013.01); **H01L 25/0753**
(2013.01); **H01L 27/124** (2013.01); **H01L**
33/20 (2013.01); **H01L 33/42** (2013.01); **G09G**
3/32 (2013.01)

(58) **Field of Classification Search**

CPC H01L 33/14
USPC 257/88
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

5,592,358 A 1/1997 Shamouilian et al.
5,839,187 A 11/1998 Sato et al.

(Continued)

FOREIGN PATENT DOCUMENTS

JP 08-045972 A 2/1996
JP 3406207 5/1999

(Continued)

OTHER PUBLICATIONS

Asano, Kazutoshi, et al., "Fundamental Study of an Electrostatic
Chuck for Silicon Wafer Handling" IEEE Transactions on Industry
Applications, vol. 38, No. 3, May/Jun. 2002, pp. 840-845.

(Continued)

Primary Examiner — Yu-Hsi D Sun


Assistant Examiner — Ankush Singal

(74) *Attorney, Agent, or Firm* — Blakely, Sokoloff, Taylor &
Zafman LLP

(57) **ABSTRACT**

A display panel and a method of forming a display panel are
described. The display panel may include a thin film transis-
tor substrate including a pixel area and a non-pixel area. The
pixel area includes an array of bank openings and an array of
bottom electrodes within the array of bank openings. A
ground line is located in the non-pixel area and an array of
ground tie lines run between the bank openings in the pixel
area and are electrically connected to the ground line in the
non-pixel area.

17 Claims, 25 Drawing Sheets



- (51) **Int. Cl.**
H01L 33/42 (2010.01)
G09G 3/32 (2006.01)

(56) **References Cited**

U.S. PATENT DOCUMENTS

- 5,851,664 A 12/1998 Bennett et al.
 5,888,847 A 3/1999 Rostoker et al.
 5,903,428 A 5/1999 Grimard et al.
 5,996,218 A 12/1999 Shamouilian et al.
 6,071,795 A 6/2000 Cheung et al.
 6,335,263 B1 1/2002 Cheung et al.
 6,403,985 B1 6/2002 Fan et al.
 6,420,242 B1 7/2002 Cheung et al.
 6,521,511 B1 2/2003 Inoue et al.
 6,531,996 B1* 3/2003 Murade 345/98
 6,558,109 B2 5/2003 Gibbel
 6,613,610 B2 9/2003 Iwafuchi et al.
 6,629,553 B2 10/2003 Odashima et al.
 6,670,038 B2 12/2003 Sun et al.
 6,786,390 B2 9/2004 Yang et al.
 6,878,607 B2 4/2005 Inoue et al.
 6,911,666 B2 6/2005 Voutsas
 7,033,842 B2 4/2006 Haji et al.
 7,148,127 B2 12/2006 Oohata et al.
 7,160,633 B2 1/2007 Tai et al.
 7,161,184 B2* 1/2007 Miyagi et al. 257/88
 7,208,337 B2 4/2007 Eisert et al.
 7,224,118 B2* 5/2007 Yamazaki et al. 313/506
 7,353,596 B2 4/2008 Shida et al.
 7,358,158 B2 4/2008 Aihara et al.
 7,482,696 B2 1/2009 Shei et al.
 7,495,389 B2* 2/2009 Noguchi et al. 313/506
 7,510,889 B2 3/2009 Pan et al.
 7,585,703 B2 9/2009 Matsumura et al.
 7,723,764 B2 5/2010 Oohata et al.
 7,791,267 B2* 9/2010 Baek et al. 313/504
 7,795,629 B2 9/2010 Watanabe et al.
 7,795,804 B2 9/2010 Kim
 7,797,820 B2 9/2010 Shida et al.
 7,838,410 B2 11/2010 Hirao et al.
 7,872,418 B2* 1/2011 Hata et al. 313/512
 7,880,184 B2 2/2011 Iwafuchi et al.
 7,884,543 B2 2/2011 Doi
 7,888,690 B2 2/2011 Iwafuchi et al.
 7,906,787 B2 3/2011 Kang
 7,910,945 B2 3/2011 Donofrio et al.
 7,927,976 B2 4/2011 Menard
 7,928,465 B2 4/2011 Lee et al.
 7,972,875 B2 7/2011 Rogers et al.
 7,994,711 B2* 8/2011 Nakamura et al. 313/506
 7,999,454 B2 8/2011 Winters et al.
 8,023,248 B2 9/2011 Yonekura et al.
 8,049,410 B2* 11/2011 Suh et al. 313/504
 8,497,143 B2 7/2013 Han
 8,497,512 B2 7/2013 Nakamura et al.
 8,833,982 B2* 9/2014 Funakubo 362/311.02
 8,912,020 B2* 12/2014 Bedell et al. 438/29
 8,921,869 B2* 12/2014 Welch et al. 257/81
 2001/0029088 A1 10/2001 Odajima et al.
 2002/0076848 A1 6/2002 Spooner et al.
 2002/0158835 A1* 10/2002 Kobayashi et al. 345/100
 2003/0017360 A1 1/2003 Tai et al.
 2003/0094615 A1 5/2003 Yamazaki et al.
 2003/0177633 A1 9/2003 Haji et al.
 2004/0208210 A1 10/2004 Inoguchi
 2004/0217704 A1* 11/2004 Iwase et al. 313/518
 2004/0256620 A1* 12/2004 Yamazaki et al. 257/66
 2005/0051776 A1* 3/2005 Miyagi et al. 257/72
 2005/0104530 A1* 5/2005 Chung et al. 315/169.3
 2005/0116620 A1 6/2005 Kobayashi
 2005/0167682 A1* 8/2005 Fukasawa 257/79
 2005/0218468 A1* 10/2005 Owen et al. 257/433
 2005/0274959 A1 12/2005 Kim et al.
 2005/0285830 A1* 12/2005 Iwabuchi 345/77
 2006/0071225 A1 4/2006 Beeson et al.

- 2006/0169993 A1 8/2006 Fan et al.
 2006/0202210 A1 9/2006 Mok et al.
 2006/0208271 A1 9/2006 Kim et al.
 2006/0238463 A1 10/2006 Kim et al.
 2007/0166851 A1 7/2007 Tran et al.
 2008/0093606 A1 4/2008 Pan et al.
 2008/0163481 A1 7/2008 Shida et al.
 2008/0265752 A1* 10/2008 Meijer et al. 313/504
 2009/0014749 A1 1/2009 Matsuda
 2009/0015149 A1* 1/2009 Lee et al. 313/504
 2009/0050907 A1* 2/2009 Yuan et al. 257/88
 2009/0068774 A1 3/2009 Slater et al.
 2009/0114934 A1 5/2009 Horng et al.
 2009/0217517 A1* 9/2009 Pique et al. 29/832
 2009/0284501 A1 11/2009 Nathan et al.
 2009/0314991 A1 12/2009 Cho et al.
 2010/0022039 A1* 1/2010 Chang 438/28
 2010/0051910 A1 3/2010 Choi
 2010/0188794 A1 7/2010 Park et al.
 2010/0193822 A1* 8/2010 Inobe et al. 257/98
 2010/0213467 A1 8/2010 Lee et al.
 2010/0248484 A1 9/2010 Bower et al.
 2010/0270567 A1* 10/2010 Emerson et al. 257/89
 2010/0295078 A1* 11/2010 Chen et al. 257/98
 2011/0003410 A1 1/2011 Tsay et al.
 2011/0057866 A1 3/2011 Konicek
 2011/0068674 A1* 3/2011 Takenaka et al. 313/318.07
 2011/0073838 A1* 3/2011 Khan et al. 257/13
 2011/0084291 A1* 4/2011 Jeong et al. 257/89
 2011/0114969 A1 5/2011 Lee et al.
 2011/0169429 A1* 7/2011 Ing et al. 315/312
 2011/0198598 A1 8/2011 Kim et al.
 2011/0266561 A1 11/2011 Rogers et al.
 2011/0284867 A1 11/2011 Tran et al.
 2011/0291151 A1* 12/2011 Matsuda et al. 257/99
 2012/0018746 A1 1/2012 Hsieh
 2012/0064642 A1 3/2012 Huang et al.
 2012/0134065 A1 5/2012 Furuya et al.
 2012/0146030 A1 6/2012 You et al.
 2012/0168714 A1* 7/2012 Chu et al. 257/13
 2012/0168776 A1 7/2012 Nakamura et al.
 2012/0205689 A1* 8/2012 Welch et al. 257/91
 2012/0223875 A1* 9/2012 Lau et al. 345/83
 2012/0326188 A1 12/2012 Han
 2013/0126081 A1 5/2013 Hu et al.
 2013/0126891 A1 5/2013 Bibl et al.
 2013/0187179 A1 7/2013 Tan et al.
 2013/0210194 A1 8/2013 Bibl et al.
 2013/0234115 A1* 9/2013 Song et al. 257/40
 2013/0285086 A1 10/2013 Hu et al.
 2014/0027709 A1* 1/2014 Higginson et al. 257/13
 2014/0084240 A1 3/2014 Hu et al.
 2014/0084482 A1 3/2014 Hu et al.
 2014/0159064 A1 6/2014 Sakariya et al.

FOREIGN PATENT DOCUMENTS

- JP 2004-303706 A 10/2004
 JP 2007-173408 A 7/2007
 KR 2010-0089115 A 8/2010
 KR 10-1051488 B1 7/2011
 WO WO 98-48319 A1 10/1998
 WO WO 03012884 A1* 2/2003 H01L 27/15
 WO WO 2011/102030 A1 8/2011
 WO WO 2011/123285 10/2011

OTHER PUBLICATIONS

- Bower, C.A., et al., "Active-Matrix OLED Display Backplanes Using Transfer-Printed Microscale Integrated Circuits", IEEE, 2010 Electronic Components and Technology Conference, pp. 1339-1343.
 "Characteristics of electrostatic Chuck(ESC)" Advanced Materials Research Group, New Technology Research Laboratory, 2000, pp. 51-53 accessed at http://www.socnb.com/report/ptech_e/2000p51_e.pdf.
 Geffroy, et al., "Organic light-emitting diode (OLED) technology: materials, devices and display technologies," 2006 Society of Chemical Industry, pp. 572-582.

(56)

References Cited**OTHER PUBLICATIONS**

Gohda, et al., "58.3: A 3.6-in. 202-ppi Full-Color AMPLD Display Fabricated by Ink-Jet Method," 2006 SID Digest, pp. 1767-1770.

Guerre, Roland, et al., "Selective Transfer Technology for Microdevice Distribution" *Journal of Microelectromechanical Systems*, vol. 17, No. 1, Feb. 2008, pp. 157-165.

Han, Min-Koo, "AM backplane for AMOLED" *Proc. of ASID '06*, Oct. 8-12, New Delhi, pp. 53-58.

Harris, Jonathan H., "Sintered Aluminum Nitride Ceramics for High-Power Electronic Applications" *Journal of the Minerals, Metals and Materials Society*, vol. 50, No. 6, Jun. 1998, p. 56.

Hekmatshoar, et al., "A novel TFT-OLED integration for OLED-independent pixel programming in amorphous-Si AMOLED pixels," 2008, Society for Information Display, *Journal of the SID* 16/1, pp. 183-188.

Horwitz, Chris M., "Electrostatic Chucks: Frequently Asked Questions" *ElectroGrip*, 2006, 10 pgs, accessed at www.electrogrip.com.

Hossick-Schott, Joachim, "Prospects for the ultimate energy density of oxide-based capacitor anodes" *Medtronic Energy and Components Center*, 10 pgs.

Lee, San Youl, et al., "Wafer-level fabrication of GaN-based vertical light-emitting diodes using a multi-functional bonding material system" *Semicond. Sci. Technol.* 24, 2009, 4 pgs.

"Major Research Thrust: Epitaxial Layer Transfer by Laser Lift-off" *Purdue University, Heterogeneous Integration Research Group*, accessed at https://engineering.purdue.edu/HetInt/project_epitaxial_layer_transfer_llo.htm, last updated Aug. 2003.

Mei, Zequn, et al., "Low-Temperature Solders" *Hewlett-Packard Journal*, Article 10, Aug. 1996, pp. 1-10.

Mercado, Lei, L., et al., "A Mechanical Approach to Overcome RF MEMS Switch Stiction Problem" 2003 *Electronic Components and Technology Conference*, pp. 377-384.

Miskys, Claudio R., et al., "Freestanding GaN-substrates and devices" *phys. Stat. sol.* © 0, No. 6, 2003, pp. 1627-1650.

Ohara, et al., "4.0-inch Active-Matrix Organic Light-Emitting Diode Display Integrated with Driver Circuits Using Amorphous IN—Ga—

Zn—Oxide Thin-Film Transistors with Suppressed Variation," 2010 *The Japan Society of Applied Physics*, pp. 1-6.

"Optical Coating," *Wikipedia.org*. Retrieved by Examiner from http://en.wikipedia.org/wiki/Optical_coating May 27, 2014, 6 pages.

PCT International Search Report and Written Opinion for International Application No. PCT/US2013/072913, mailed Mar. 25, 2014, 11 pages.

PCT International Search Report and Written Opinion for International Application No. PCT/US2013/072914, mailed Mar. 24, 2014, 11 pages.

PCT International Search Report and Written Opinion for International Application No. PCT/US2013/072916, mailed Mar. 27, 2014, 12 pages.

"Principles of Electrostatic Chucks: 1—Techniques for High Performance Grip and Release" *ElectroGrip, Principles1 rev3* May 2006, 2 pgs, accessed at www.electrogrip.com.

Sarma, et al., "Active Matrix OLED Using 150° C. a-Si TFT Backplane Built on Flexible Plastic Substrate," *SPIE Symp. on Aerospace/Defense Sensing*, Orlando, FL, Apr. 2003, and to be published in *SPIE Proc.*, vol. 5080, paper 24 (2003), 12 pgs.

Steigerwald, Daniel, et al., "III-V Nitride Semiconductors for High-Performance Blue and Green Light-Emitting Devices" article appears in *journal JOM* 49 (9) 1997, pp. 18-23. Article accessed Nov. 2, 2011 at <http://www.tms.org/pubs/journals/jom/9709/steigerwald-9709.html>, 12 pgs.

Widas, Robert, "Electrostatic Substrate Clamping for Next Generation Semiconductor Devices" Apr. 21, 1999, 4 pgs.

Notification Concerning Transmittal of Preliminary Report on Patentability for International Application No. PCT/US2013/072913, mailed Jun. 25, 2015, 8 pages.

Notification Concerning Transmittal of Preliminary Report on Patentability for International Application No. PCT/US2013/072914, mailed Jun. 25, 2015, 9 pages.

Notification Concerning Transmittal of Preliminary Report on Patentability for International Application No. PCT/US2013/072916, mailed Jun. 25, 2015, 9 pages.

* cited by examiner





FIG. 1
PRIOR ART






FIG. 3A




FIG. 3B




FIG. 3C







FIG. 3D






FIG. 4D




FIG. 4E




FIG. 4F




FIG. 4G




FIG. 4H




FIG. 5A




FIG. 5B




FIG. 5C




FIG. 6A




FIG. 6B




FIG. 6C




FIG. 7A




FIG. 7B




FIG. 8A




FIG. 8B




FIG. 8C




FIG. 9A




FIG. 9B






FIG. 9C



**FIG. 10**

ACTIVE MATRIX DISPLAY PANEL WITH GROUND TIE LINES

RELATED APPLICATIONS

This application is a continuation of U.S. patent application Ser. No. 13/842,793, filed on Mar. 15, 2013, which is a continuation-in-part of U.S. patent application Ser. No. 13/710,443, filed on Dec. 10, 2012, both of which are incorporated herein by reference.

BACKGROUND

1. Field

Embodiments of the present invention relate to display systems. More particularly embodiments of the present invention relate to a grounding structure for an active matrix display panel.

2. Background Information

Flat panel displays are gaining popularity in a wide range of electronic devices. Common types of flat panel displays include active matrix displays and passive matrix displays. Each pixel in an active matrix display panel is driven by active driving circuitry, while each pixel in a passive matrix display panel does not use such driving circuitry. High-resolution color display panels, such as modern computer displays, smart phones and televisions typically use an active matrix display panel structure for better image quality.

One kind of display panel that is finding commercial application is an active matrix organic light emitting diode (AMOLED) display panel. FIG. 1 is a top view illustration of a top emission AMOLED display panel. FIG. 2 is a cross-sectional side view illustration of FIG. 1 taken along line X-X in the pixel area 104 and line Y-Y crossing the ground ring 116 in the non-pixel area. The AMOLED display panel 100 illustrated in FIGS. 1-2 generally includes a thin film transistor (TFT) substrate 102 supporting a pixel area 104 and non-pixel area outside of the pixel area 102. A TFT substrate 102 is also referred to as a backplane. A TFT substrate which has been further processed to additionally include the pixel area and non-pixel area is also often referred to as a backplane. Two primary TFT substrate technologies used in AMOLEDs include polycrystalline silicon (poly-Si) and amorphous silicon (a-Si). These technologies offer the potential for fabricating the active matrix backplanes at low temperatures (below 200° C.) directly onto flexible plastic substrates for producing flexible AMOLED displays. The pixel area 104 generally includes pixels 106 and subpixels 108 arranged in a matrix, and a set of TFTs and capacitors connected to each subpixel for driving and switching the subpixels. The non-pixel area generally includes a data driver circuit 110 connected to a data line of each subpixel to enable data signals (Vdata) to be transmitted to the subpixels, a scan driver circuit 112 connected to scan lines of the subpixels to enable scan signals (Vscan) to be transmitted to the subpixels, a power supply line 114 to transmit a power signal (Vdd) to the TFTs, and a ground ring 116 to transmit a ground signal (Vss) to the array of subpixels. As shown, the data driver circuit, scan driver circuit, power supply line, and ground ring are all connected to a flexible circuit board (FCB) 113 which includes a power source for supplying power to the power supply line 114 and a power source ground line electrically connected to the ground ring 116.

In the exemplary AMOLED backplane configuration an organic thin film 120 and top electrode 118 are deposited over every subpixel 108 in the pixel area 104. The organic thin film 120 may include multiple layers such as a hole injection layer,

hole transport layer, light emitting layer, electron transport layer, and electron injection layer. The multiple layers of the organic thin film 120 are typically formed over the entire pixel area 104, however, the light emitting layer is often deposited with aid of a shadow mask only within the subpixel openings 127 and on the bottom electrode layer 124 corresponding to the emission area for the array of subpixels 108. A top electrode layer 118 is then deposited over the organic thin film within both the pixel area 104 and also within the non-pixel area so that the top electrode 118 layer overlaps the ground ring 116 in the in order to transfer the ground signal to the array of subpixels. In this manner, each of the subpixels 108 can be individually addressed with the corresponding underlying TFT circuitry while a uniform ground signal is supplied to the top of the pixel area 104.

In the particular implementation illustrated, the TFT substrate 102 includes a switching transistor T1 connected to a data line 111 from the data driver circuit 110 and a driving transistor T2 connected to a power line 115 connected to the power supply line 114. The gate of the switching transistor T1 may also be connected to a scan line (not illustrated) from the scan driver circuit 112. A planarization layer 122 is formed over the TFT substrate, and openings are formed to expose the TFT working circuitry. As illustrated, a bottom electrode layer 124 is formed on the planarization layer in electrical connection with the TFT circuitry. Following the formation of the electrode layer a pixel defining layer 125 is formed including an array of subpixel openings 127 corresponding to the emission area for the array of subpixels 108, followed by deposition of the organic layer 120 and top electrode layer 118 over the patterned pixel defining layer, and within subpixel openings 127 of the patterned pixel defining layer 125. The top electrode layer 118 additionally is formed in the non-pixel area and in electrical connection with the ground ring 116.

The planarization layer 122 may function to prevent (or protect) the organic layer 120 and the bottom electrode layer 124 from shorting due to a step difference. Exemplary planarization layer 122 materials include benzocyclobutene (BCB) and acrylic. The pixel defining layer 125 can be formed of a material such as polyimide. The bottom electrode 124 is commonly formed on indium tin oxide (ITO), ITO/Ag, ITO/Ag/ITO, ITO/Ag/indium zinc oxide (IZO), or ITO/Ag alloy/ITO. The top electrode layer 118 is formed of a transparent material such as ITO for top emission.

While AMOLED display panels generally consume less power than liquid crystal display (LCD) panels, an AMOLED display panel can still be the dominant power consumer in battery-operated devices. To extend battery life, it is necessary to reduce the power consumption of the display panel.

SUMMARY OF THE INVENTION

A display panel and a method of forming a display panel are described. In an embodiment a display panel includes a TFT substrate including a pixel area and a non-pixel area. For example, the non-pixel area may surround the pixel area. The pixel area includes an array of bank openings and an array of bottom electrodes within the array of bank openings. The array of bottom electrodes may be formed on sidewalls of the corresponding array of bank openings, and may be reflective to the visible wavelength. In an embodiment a post of solder material is formed on the bottom electrode within each bank opening in order to aid the bonding of a micro LED device to the bottom electrode. A ground line is formed in the non-pixel area, and an array of ground tie lines run between the bank openings in the pixel area and are electrically connected to the

ground line in the non pixel area. In an embodiment, the ground line is a ground ring, and the array of ground tie lines are electrically connected to the ground ring on opposite sides of the pixel area.

In an embodiment a patterned insulator layer covers the array of bottom electrodes, and an array of openings is formed in the patterned insulator exposing the array of bottom electrodes. In this manner, the patterned insulator layer may cover the edges of the array of bottom electrodes. Another array of openings may also be formed in the patterned insulator layer exposing the array of ground tie lines.

In an embodiment, an array of micro LED devices are on the array of bottom electrodes within the corresponding array of bank openings. For example, the micro LED devices may be vertical micro LED devices, and may have a maximum width of 1 μm -100 μm . A transparent passivation layer can be formed spanning sidewalls of the array of micro LED devices without completely covering a top conductive contact of each micro LED device. In an embodiment, an array of top electrode layers are formed over and in electrical contact with the array of micro LED devices and the array of ground tie lines. For example, each top electrode layer may electrically connect a plurality of micro LED devices to a single ground tie line. The top electrode layers may also be formed of a transparent or semi-transparent material such as PEDOT or ITO. In another embodiment, the top electrode layer is formed over an in electrical contact with the array of micro LED devices and the array of ground tie lines through an array of openings exposing the array of ground tie lines.

In an embodiment, a method of forming a display panel includes transferring an array of micro LED devices from a carrier substrate to a backplane that comprises a TFT substrate including a pixel area and a non-pixel area, where the pixel area includes an array of bank openings and an array of bottom electrodes within the array of bank openings. The TFT substrate also includes a ground line in the non-pixel area, and an array of ground tie lines running between the bank openings in the pixel area and electrically connected to the ground line in the non-pixel area. In an embodiment a top electrode layer is deposited over all of the micro LED devices in the array of micro LED devices. In an embodiment, the top electrode layer spans over a plurality of the micro LED devices. The top electrode layer may additionally be formed by ink jet printing or screen printing. For example a plurality of separate electrode layers can be ink jet printed, with each separate top electrode layer spanning over at least one of the micro LED devices and at least one of the ground tie lines. In jet printing may also include forming the top electrode layer within an opening over one or more ground tie lines.

In an embodiment, transfer of the array of micro LED device is performed with electrostatic principles using an array of electrostatic transfer heads. Furthermore, bonding of the array of micro LED devices may include the formation of an inter-metallic compound, and may include liquefying an array of bonding layers formed on the array of bottom electrodes. Bonding and liquefying may be accomplished in part by the transfer of thermal energy from the array of electrostatic transfer heads to the array of bonding layers formed on the array of bottom electrodes.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a top view illustration of a top emission AMOLED display panel.

FIG. 2 is a side-view illustration of the top emission AMOLED display panel of FIG. 1 taken along lines X-X and Y-Y.

FIG. 3A is a top view illustration of an active matrix display panel in accordance with an embodiment of the invention.

FIG. 3B is a side-view illustration of the active matrix display panel of FIG. 3A taken along lines X-X and Y-Y in accordance with an embodiment of the invention.

FIG. 3C is a side-view illustration of the active matrix display panel of FIG. 3A taken along lines X-X and Y-Y in accordance with an embodiment of the invention in which ground tie lines and ground ring are formed within a patterned bank layer.

FIG. 3D is a side-view illustration of the active matrix display panel of FIG. 3A taken along lines X-X and Y-Y in accordance with an embodiment of the invention in which ground tie lines and ground ring are formed below a patterned bank layer.

FIGS. 4A-4H are cross-sectional side view illustrations for a method of transferring an array of micro LED devices to a TFT substrate in accordance with an embodiment of the invention.

FIGS. 5A-5C are top view illustrations for a sequence of transferring an array of micro LED devices with different color emissions in accordance with an embodiment of the invention.

FIG. 6A is a top view illustration of an active matrix display panel after the formation of a top electrode layer in accordance with an embodiment.

FIG. 6B is a side-view illustration of the active matrix display panel of FIG. 6A taken along lines X-X and Y-Y in accordance with an embodiment of the invention.

FIG. 6C is a side-view illustration of the active matrix display panel of FIG. 6A taken along lines X-X and Y-Y illustrating a passivation layer formed on patterned bank layer in accordance with an embodiment of the invention.

FIG. 7A is a top view illustration of an active matrix display panel after the formation of a top electrode layer in accordance with an embodiment.

FIG. 7B is a side-view illustration of the active matrix display panel of FIG. 7A taken along lines X-X and Y-Y in accordance with an embodiment of the invention.

FIG. 8A is a top view illustration of an active matrix display panel after the formation of separate top electrode layers in accordance with an embodiment.

FIG. 8B is a side-view illustration of the active matrix display panel of FIG. 8A taken along lines X-X and Y-Y in accordance with an embodiment of the invention.

FIG. 8C is a top schematic view illustration of a scribed top electrode layer in accordance with an embodiment of the invention.

FIG. 9A is a top view illustration of a top emission AMOLED display panel including ground tie lines in accordance with an embodiment of the invention.

FIG. 9B is a side-view illustration of the top emission AMOLED display panel of FIG. 9A taken along lines X-X and Y-Y in accordance with an embodiment of the invention.

FIG. 9C is a top view illustration of a top emission AMOLED display panel including ground tie lines in accordance with an embodiment of the invention.

FIG. 9D is a side-view illustration of the top emission AMOLED display panel of FIG. 9C taken along lines X-X and Y-Y in accordance with an embodiment of the invention.

FIG. 10 is a schematic illustration of a display system in accordance with an embodiment of the invention.

DETAILED DESCRIPTION OF THE INVENTION

Embodiments of the present invention relate to display systems. More particularly embodiments of the present invention relate to a grounding structure for an active matrix display panel.

In one embodiment, an active matrix display panel includes an arrangement of ground tie lines running between bank openings in a pixel area of the display panel. A top electrode layer can be deposited over all of the LEDs within the bank openings and in electrical contact with the ground tie lines, or separate top electrode layers can be deposited over one or more LEDs within the bank openings and in electrical contact with one or more ground tie lines. In one aspect, the arrangement of ground tie lines may more uniformly distribute the ground signal to the array of LEDs on the display panel, thereby providing more uniform light emission across the panel. In another aspect, the arrangement of ground tie lines enables reduction of power consumption of the display panel by reducing contact resistance in the electrical path from LED to ground line, where the distance of the electrical path through the top electrode layer is reduced by connecting the top electrode layer to a ground tie line of higher electrical conductivity than the top electrode layer.

In yet another aspect, embodiments of the invention describe an active matrix display panel including wafer-based emissive micro LED devices. A micro LED device combines the performance, efficiency, and reliability of wafer-based LED devices with the high yield, low cost, mixed materials of thin film electronics used to form AMOLED backplanes. The terms “micro” device or “micro” LED structure as used herein may refer to the descriptive size of certain devices or structures in accordance with embodiments of the invention. As used herein, the terms “micro” devices or structures are meant to refer to the scale of 1 to 100 μm . However, it is to be appreciated that embodiments of the present invention are not necessarily so limited, and that certain aspects of the embodiments may be applicable to larger, and possibly smaller size scales. In an embodiment, a display panel is similar to a typical OLED display panel, with a micro LED device having replaced the organic layer of the OLED display panel in each subpixel. Exemplary micro LED devices which may be utilized with some embodiments of the invention are described in U.S. patent application Ser. No. 13/372,222, U.S. patent application Ser. No. 13/436,260, U.S. patent application Ser. No. 13/458,932, U.S. patent application Ser. No. 13/711,554, and U.S. patent application Ser. No. 13/749,647 all of which are incorporated herein by reference. The micro LED devices are highly efficient at light emission and consume very little power (e.g., 250 mW for a 10 inch diagonal display) compared to 5-10 watts for a 10 inch diagonal LCD or OLED display, enabling reduction of power consumption of the display panel.

In various embodiments, description is made with reference to figures. However, certain embodiments may be practiced without one or more of these specific details, or in combination with other known methods and configurations. In the following description, numerous specific details are set forth, such as specific configurations, dimensions and processes, etc., in order to provide a thorough understanding of the present invention. In other instances, well-known semiconductor processes and manufacturing techniques have not been described in particular detail in order to not unnecessarily obscure the present invention. Reference throughout this specification to “one embodiment” means that a particular feature, structure, configuration, or characteristic described in connection with the embodiment is included in at least one embodiment of the invention. Thus, the appearances of the phrase “in one embodiment” in various places throughout this specification are not necessarily referring to the same embodiment of the invention. Furthermore, the particular

features, structures, configurations, or characteristics may be combined in any suitable manner in one or more embodiments.

The terms “spanning”, “over”, “to”, “between” and “on” as used herein may refer to a relative position of one layer with respect to other layers. One layer “spanning”, “over” or “on” another layer or bonded “to” or in “contact” with another layer may be directly in contact with the other layer or may have one or more intervening layers. One layer “between” layers may be directly in contact with the layers or may have one or more intervening layers.

Referring now to FIGS. 3A-3B an embodiment is illustrated in which a backplane similar to an AMOLED backplane is modified to receive emissive micro LED devices rather than an organic emission layer. FIG. 3A is a top view illustration of an active matrix display panel in accordance with an embodiment, and FIG. 3B is a side-view illustration of the active matrix display panel of FIG. 3A taken along lines X-X and Y-Y in accordance with an embodiment of the invention. In such an embodiment, the underlying TFT substrate **102** can be similar to those in a typical AMOLED backplane described with regard to FIGS. 1-2 including working circuitry (e.g. T1, T2) and planarization layer **122**. Openings **131** may be formed in the planarization layer **122** to contact the working circuitry. The working circuitry can include traditional 2T1C (two transistors, one capacitor) circuits including a switching transistor, a driving transistor, and a storage capacitor. It is to be appreciated that the 2T1C circuitry is meant to be exemplary, and that other types of circuitry or modifications of the traditional 2T1C circuitry are contemplated in accordance with embodiments of the invention. For example, more complicated circuits can be used to compensate for process variation of the driver transistor and the light emitting device, or for their instabilities. Furthermore, while embodiments of the invention are described and illustrated with regard to top gate transistor structures in the TFT substrate **102**, embodiments of the invention also contemplate the use of bottom gate transistor structures. Likewise, while embodiments of the invention are described and illustrated with regard to a top emission structure, embodiments of the invention also contemplate the use of bottom, or both top and bottom emission structures. In addition, embodiments of the invention are described and illustrated below specifically with regard to a high side drive configuration including ground tie lines and ground ring. In a high side drive configuration a LED may be on the drain side of a PMOS driver transistor or a source side of an NMOS driver transistor so that the circuit is pushing current through the p-terminal of the LED. Embodiments of the invention are not so limited may also be practiced with a low side drive configuration in which case the ground tie lines and ground ring become the power line in the panel and current is pulled through the n-terminal of the LED.

A patterned bank layer **126** including bank openings **148** is then formed over the planarization layer **122**. Bank layer **126** may be formed by a variety of techniques such as ink jet printing, screen printing, lamination, spin coating, CVD, and PVD. Bank layer **126** may be opaque, transparent, or semi-transparent to the visible wavelength. Bank layer **126** may be formed of a variety of insulating materials such as, but not limited to, photo-definable acrylic, photoresist, silicon oxide (SiO_2), silicon nitride (SiN_x), poly(methyl methacrylate) (PMMA), benzocyclobutene (BCB), polyimide, acrylate, epoxy, and polyester. In an embodiment, bank layer is formed of an opaque material such as a black matrix material. Exemplary insulating black matrix materials include organic resins, glass pastes, and resins or pastes including a black

pigment, metallic particles such as nickel, aluminum, molybdenum, and alloys thereof, metal oxide particles (e.g. chromium oxide), or metal nitride particles (e.g. chromium nitride).

In accordance with embodiments of the invention, the thickness of the bank layer 126 and width of the bank openings 128 described with regard to the following figures may depend upon the height of the micro LED device to be mounted within the opening, height of the transfer heads transferring the micro LED devices, and resolution. In an embodiment, the resolution, pixel density, and subpixel density of the display panel may account for the width of the bank openings 128. For an exemplary 55 inch television with a 40 PPI (pixels per inch) and 211 μm subpixel pitch, the width of the bank openings 128 may be anywhere from a few microns to 206 μm to account for a surrounding bank structure. For an exemplary display panel with 440 PPI and a 19 μm subpixel pitch, the width of the bank openings 128 may be anywhere from a few microns to 14 μm to account for an exemplary 5 μm wide surrounding bank structure. Width of the bank structure (i.e. between bank openings 128) may be any suitable size, so long as the structure supports the required processes and is scalable to the required PPI.

In accordance with embodiments of the invention, the thickness of the bank layer 126 is not too thick in order for the bank structure to function. Thickness may be determined by the micro LED device height and a predetermined viewing angle. For example, where sidewalls of the bank openings 128 make an angle with the planarization layer 122, shallower angles may correlate to a wider viewing angle of the system. In an embodiment, exemplary thicknesses of the bank layer 126 may be between 1 μm -50 μm .

A patterned conductive layer is then formed over the patterned bank layer 126. Referring to FIG. 3B, in one embodiment the patterned conductive layer includes bottom electrodes 142 formed within the bank openings 148 and in electrical contact with the working circuitry. The patterned conductive layer may also optionally include the ground tie lines 144 and/or the ground ring 116. As used herein the term ground "ring" does not require a circular pattern, or a pattern that completely surrounds an object. Rather, the term ground "ring" means a pattern that at least partially surrounds the pixel area on three sides. In addition, while the following embodiments are described and illustrated with regard to a ground ring 116, it is to be appreciated that embodiments of the invention can also be practiced with a ground line running along one side (e.g. left, right, bottom, top), or two sides (a combination of two of the left, right, bottom, top) of the pixel area. Accordingly, it is to be appreciated that in the following description the reference to and illustration of a ground ring, could potentially be replaced with a ground line where system requirements permit.

The patterned conductive layer may be formed of a number of conductive and reflective materials, and may include more than one layer. In an embodiment, a patterned conductive layer comprises a metallic film such as aluminum, molybdenum, titanium, titanium-tungsten, silver, or gold, or alloys thereof. The patterned conductive layer may include a conductive material such as amorphous silicon, transparent conductive oxides (TCO) such as indium-tin-oxide (ITO) and indium-zinc-oxide (IZO), carbon nanotube film, or a transparent conducting polymer such as poly(3,4-ethylenedioxythiophene) (PEDOT), polyaniline, polyacetylene, polypyrrole, and polythiophene. In an embodiment, the patterned conductive layer includes a stack of a conductive material and a reflective conductive material. In an embodiment, the patterned conductive layer includes a 3-layer stack including top

and bottom layers and a reflective middle layer wherein one or both of the top and bottom layers are transparent. In an embodiment, the patterned conductive layer includes a conductive oxide-reflective metal-conductive oxide 3-layer stack. The conductive oxide layers may be transparent. For example, the patterned conductive layer may include an ITO-silver-ITO layer stack. In such a configuration, the top and bottom ITO layers may prevent diffusion and/or oxidation of the reflective metal (silver) layer. In an embodiment, the patterned conductive layer includes a Ti—Al—Ti stack, or a Mo—Al—Mo-ITO stack. In an embodiment, the patterned conductive layer includes a ITO-Ti—Al—Ti-ITO stack. In an embodiment, the patterned conductive layer is 1 μm or less in thickness. The patterned conductive layer may be deposited using a suitable technique such as, but not limited to, PVD.

Following the formation of bottom electrodes 142, ground tie lines 144, and ground ring 116, an insulator layer 146 may then optionally be formed over the TFT substrate 102 covering the sidewalls of the patterned conductive layer. The insulator layer 146 may at least partially cover the bank layer 126 and the reflective layer forming the bottom electrodes 142, ground tie lines 144, and/or ground ring 116.

In an embodiment, the insulator layer 146 is formed by blanket deposition using a suitable technique such as lamination, spin coating, CVD, and PVD, and then patterned using a suitable technique such as lithography to form openings exposing the bottom electrodes 142, openings 149 exposing the ground tie lines 144, and openings 130 exposing the ground ring 116. In an embodiment, ink jet printing or screen printing may be used to form the insulator layer 146 and openings 149 without requiring lithography. Insulator layer 146 may be formed of a variety of materials such as, but not limited to, SiO_2 , SiN_x , PMMA, BCB, polyimide, acrylate, epoxy, and polyester. For example, the insulator layer 146 may be 0.5 μm thick. The insulator layer 146 may be transparent or semi-transparent where formed over the reflective layer on sidewalls of bottom electrode 142 within the bank openings 128 as to not significantly degrade light emission extraction of the completed system. Thickness of the insulator layer 146 may also be controlled to increase light extraction efficiency, and also to not interfere with the array of transfer heads during transfer of the array of light emitting devices to the reflective bank structure. As will become more apparent in the following description, the patterned insulator layer 146 is optional, and represents one manner for electrically separating conductive layers.

In the embodiment illustrated in FIG. 3B, the bottom electrodes 142, ground tie lines 144, and ground ring 116 can be formed of the same conductive layer. In another embodiment, the ground tie lines 144 and/or ground ring 116 can be formed of a conductive material different from the bottom electrodes 142. For example, ground tie lines 144 and ground ring 116 may be formed with a material having a higher conductivity than the bottom electrodes 142. In another embodiment, ground tie lines 144 and/or ground ring 116 can also be formed within different layers from the bottom electrodes. FIGS. 3C-3D illustrate embodiments where the ground tie lines 144 and ground ring 116 can be formed within or below the patterned bank layer 126. For example, in the embodiment illustrated in FIG. 3C, openings 149, 130 may be formed through the patterned bank layer 126 when forming the ground tie lines 144 and ground ring 116. In the embodiment illustrated in FIG. 3D openings 149, 130 may be formed through the patterned bank layer 126 and planarization layer 122 to contact the ground tie lines 144 and ground ring 116 which may have been formed during formation of the working circuitry of the TFT substrate 102. In such an embodiment

the conductive layer used to form the bottom electrode **142** may also optionally include via opening layers **145** and **117** to further enable electrical contact of the top electrode layer yet to be formed with the ground tie lines **144** and ground ring **116** through openings **149** and **130**, respectively. Accordingly, it is to be appreciated that the embodiments illustrated in FIGS. 3A-3D are not limiting and that a number of possibilities exist for forming the ground tie lines **144** and ground ring **116**, as well as openings **149**, **130** to expose the ground tie lines **144** and/or ground ring **116**, respectively.

Still referring to embodiments illustrated in FIG. 3B-3D, a bonding layer **140** may be formed on the bottom electrode layer **142** to facilitate bonding of a micro LED device. In an embodiment, the bonding layer **140** is selected for its ability to be inter-diffused with a bonding layer on the micro LED device (yet to be placed) through bonding mechanisms such as eutectic alloy bonding, transient liquid phase bonding, or solid state diffusion bonding as described in U.S. patent application Ser. No. 13/749,647. In an embodiment, the bonding layer **140** has a melting temperature of 250° C. or lower. For example, the bonding layer **140** may include a solder material such as tin (232° C.) or indium (156.7° C.), or alloys thereof. Bonding layer **140** may also be in the shape of a post, having a height greater than width. In accordance with some embodiments of the invention, taller bonding layers **140** may provide an additional degree of freedom for system component leveling, such as planarity of the array of micro LED devices with the TFT substrate during the micro LED device transfer operation and for variations in height of the micro LED devices, due to the change in height of the liquefied bonding layers as they spread out over the surface during bonding, such as during eutectic alloy bonding and transient liquid phase bonding. The width of the bonding layers **140** may be less than a width of a bottom surface of the micro LEDs to prevent wicking of the bonding layers **140** around the sidewalls of the micro LEDs and shorting the quantum well structures.

In the embodiments illustrated an arrangement of ground tie lines **144** run between bank openings **128** in the pixel area **104** of the display panel **100**. In addition, a plurality of openings **149** expose the plurality of ground tie lines **144**. The number of openings **149** may or may not have a 1:1 correlation to the number of columns (top to bottom) of bank openings **128**. For example, in the embodiment illustrated in FIG. 3A, a ground tie opening **149** is formed for each column of bank openings **128**, however, this is not required and the number of ground tie openings **149** may be more or less than the number of columns of bank openings **128**. Likewise, the number of ground tie lines **144** may or may not have a 1:1 correlation to the number of rows (left to right) of bank openings. For example, in the embodiment illustrated a ground tie line **144** is formed for every two rows of bank openings **128**, however, this is not required and the number of ground tie lines **144** may have a 1:1 correlation, or any 1:n correlation to the number (n) of rows of bank openings **128**.

While the above embodiments have been described an illustrated with ground tie lines **144** running left and right horizontally across the display panel **100**, embodiments are not so limited. In other embodiments, the ground tie lines can run vertically, or both horizontally and vertically to form a grid. A number of possible variations are envisioned in accordance with embodiments of the invention. It has been observed that operation of AMOLED configurations such as those previously illustrated and described with regard to FIGS. 1-2 may result in dimmer emission from the subpixels in the center of the pixel area, where the subpixels are furthest from the ground ring **116**, compared to the emission from

subpixels at the edges of the pixel area closer to the ground ring **116**. In accordance with embodiments of the invention, ground tie lines are formed between the bank openings **128** in the pixel area and are electrically connected to the ground ring **116** or ground line in the non-display area. In this manner, the ground signal may be more uniformly applied to the matrix of subpixels, resulting in more uniform brightness across the display panel **100**. In addition, by forming the ground tie lines **144** from a material having better electrical conductivity than the top electrode layer (which is yet to be formed), this may reduce the contact resistance in the electrical ground path.

FIGS. 4A-4H are cross-sectional side view illustrations for a method of transferring an array of micro LED devices to the TFT substrate **102** in accordance with an embodiment of the invention. Referring to FIG. 4A, an array of transfer heads **302** supported by a transfer head substrate **300** are positioned over an array of micro LED devices **400** supported on a carrier substrate **200**. A heater **306** and heat distribution plate **304** may optionally be attached to the transfer head substrate **300**. A heater **204** and heat distribution plate **202** may optionally be attached to the carrier substrate **200**. The array of micro LED devices **400** are contacted with the array of transfer heads **302**, as illustrated in FIG. 4B, and picked up from the carrier substrate **200** as illustrated in FIG. 4C. In an embodiment, the array of micro LED devices **400** are picked up with an array of transfer heads **302** operating in accordance with electrostatic principles, that is, they are electrostatic transfer heads.

FIG. 4D is a cross-sectional side view illustration of a transfer head **302** holding a micro LED device **400** over a TFT substrate **102** in accordance with an embodiment of the invention. In the embodiment illustrated, the transfer head **302** is supported by a transfer head substrate **300**. As described above, a heater **306** and heat distribution plate **304** may optionally be attached to the transfer head substrate to apply heat to the transfer head **302**. A heater **152** and heat distribution plate **150** may also, or alternatively, optionally be used to transfer heat to the bonding layer **140** on the TFT substrate **102** and/or optional bonding layer **410** on a micro LED device **400** described below.

Still referring to FIG. 4D, a close-up view of an exemplary micro LED device **400** is illustrated in accordance with an embodiment. It is to be appreciated, that the specific micro LED device **400** illustrated is exemplary and that embodiments of the invention are not limited. In the particular embodiment illustrated, the micro LED device **400** includes a micro p-n diode **450** and a bottom conductive contact **420**. A bonding layer **410** may optionally be formed below the bottom conductive contact **420**, with the bottom conductive contact **420** between the micro p-n diode **450** and the bonding layer **410**. In an embodiment, the micro LED device **400** further includes a top conductive contact **452**. In an embodiment, the micro p-n diode **450** includes a top n-doped layer **414**, one or more quantum well layers **416**, and a lower p-doped layer **418**. In other embodiments, the arrangement of n-doped and p-doped layers can be reversed. The micro p-n diodes can be fabricated with straight sidewalls or tapered sidewalls. In certain embodiments, the micro p-n diodes **450** possess outwardly tapered sidewalls **453** (from top to bottom). In certain embodiments, the micro p-n diodes **450** possess inwardly tapered sidewall (from top to bottom). The top and bottom conductive contacts **420**, **452**. For example, the bottom conductive contact **420** may include an electrode layer and a barrier layer between the electrode layer and the optional bonding layer **410**. The top and bottom conductive contacts **420**, **452** may be transparent to the visible wavelength range (e.g. 380 nm-750 nm) or opaque. The top and

bottom conductive contacts **420**, **452** may optionally include a reflective layer, such as a silver layer. The micro p-n diode and conductive contacts may each have a top surface, a bottom surface and sidewalls. In an embodiment, the bottom surface **451** of the micro p-n diode **450** is wider than the top surface of the micro p-n diode, and the sidewalls **453** are tapered outwardly from top to bottom. The top surface of the micro p-n diode **450** may be wider than the bottom surface of the p-n diode, or approximately the same width. In an embodiment, the bottom surface **451** of the micro p-n diode **450** is wider than the top surface of the bottom conductive contact **420**. The bottom surface of the micro p-n diode may also be approximately the same width as the top surface of the bottom conductive contact **420**. In an embodiment, the micro p-n diode **450** is several microns thick, such as 3 μm or 5 μm , the conductive contacts **420**, **452** are 0.1 μm -2 μm thick, and the optional bonding layer **410** is 0.1 μm -1 μm thick. In an embodiment, a maximum width of each micro LED device **400** is 1-100 μm , for example, 30 μm , 10 μm , or 5 μm . In an embodiment, the maximum width of each micro LED device **400** must comply with the available space in the bank opening **128** for a particular resolution and PPI of the display panel.

FIG. 4E is a cross-sectional side view illustration of an array of transfer heads holding an array micro LED devices **400** over a TFT substrate **102** accordance with an embodiment of the invention. FIG. 4E is substantially similar to the structure illustrated in FIG. 4D with the primary difference being the illustration of the transfer of an array of micro LED devices as opposed to a single micro LED device within the array of micro LED devices.

Referring now to FIG. 4F the TFT substrate **102** is contacted with the array of micro LED devices **400**. In the embodiment illustrated, contacting the TFT substrate **102** with the array of micro LED devices **400** includes contacting bonding layer **140** with a micro LED device bonding layer **410** for each respective micro LED device. In an embodiment, each micro LED device bonding layer **410** is wider than a corresponding bonding layer **140**. In an embodiment energy is transferred from the electrostatic transfer head assembly and through the array of micro LED devices **400** to bond the array of micro LED devices **400** to the TFT substrate **102**. For example, thermal energy may be transferred to facilitate several types of bonding mechanisms such as eutectic alloy bonding, transient liquid phase bonding, and solid state diffusion bonding. The transfer of thermal energy may also be accompanied by the application of pressure from the electrostatic transfer head assembly.

Referring to FIG. 4G, in an embodiment, the transfer of energy liquefies bonding layer **140**. The liquefied bonding layer **140** may act as a cushion and partially compensate for system uneven leveling (e.g. nonplanar surfaces) between the array of micro devices **400** and the TFT substrate during bonding, and for variations in height of the micro LED devices. In the particular implementation of transient liquid phase bonding the liquefied bonding layer **140** inter-diffuses with the micro LED device bonding layer **410** to form an inter-metallic compound layer with an ambient melting temperature higher than the ambient melting temperature of the bonding layer **140**. Accordingly, transient liquid phase bonding may be accomplished at or above the lowest liquidus temperature of the bonding layers. In some embodiments of the invention, the micro LED device bonding layer **410** is formed of a material having a melting temperature above 250° C. such as bismuth (271.4° C.), or a melting temperature above 350° C. such as gold (1064° C.), copper (1084° C.), silver (962° C.), aluminum (660° C.), zinc (419.5° C.), or

nickel (1453° C.), and the TFT substrate bonding layer **140** has a melting temperature below 250° C. such as tin (232° C.) or indium (156.7° C.).

In this manner, the substrate **150** supporting the TFT substrate **102** can be heated to a temperature below the melting temperature of the bonding layer **140**, and the substrate **304** supporting the array of transfer heads is heated to a temperature below the melting temperature of bonding layer **410**, but above the melting temperature of bonding layer **140**. In such an embodiment, the transfer of heat from the electrostatic transfer head assembly through the array of micro LED devices **400** is sufficient to form the transient liquid state of bonding layer **140** with subsequent isothermal solidification as an inter-metallic compound. While in the liquid phase, the lower melting temperature material both spreads out over the surface and diffused into a solid solution of the higher melting temperature material or dissolves the higher melting temperature material and solidifies as an inter-metallic compound. In a specific embodiment, the substrate **304** supporting the array of transfer heads is held at 180° C., bonding layer **410** is formed of gold, and bonding layer **140** is formed of indium.

Following the transfer of energy to bond the array of micro LED devices **400** to the TFT substrate, the array of micro LED devices **400** are released onto the receiving substrate and the array of electrostatic transfer heads are moved away as illustrated in FIG. 4H. Releasing the array of micro LED devices **400** may be accomplished with a variety of methods including turning off the electrostatic voltage sources, lowering the voltage across the electrostatic transfer head electrodes, changing a waveform of an AC voltage, and grounding the voltage sources.

Referring now to FIGS. 5A-5C, a sequence of transferring an array of micro LED devices **400** with different color emissions is illustrated in accordance with an embodiment of the invention. In the particular configuration illustrated in FIG. 5A, a first transfer procedure has been completed for transferring an array of red-emitting micro LED devices **400R** from a first carrier substrate to the TFT substrate **102**. For example, where the micro LED devices **400R** are designed to emit a red light (e.g. 620-750 nm wavelength) the micro p-n diode **450** may include a material such as aluminum gallium arsenide (AlGaAs), gallium arsenide phosphide (GaAsP), aluminum gallium indium phosphide (AlGaInP), and gallium phosphide (GaP). Referring to FIG. 5B, a second transfer procedure has been completed for transferring an array of green-emitting micro LED devices **400G** from a second carrier substrate to the TFT substrate **102**. For example, where the micro LED devices **400G** are designed to emit a green light (e.g. 495-570 nm wavelength) the micro p-n diode **450** may include a material such as indium gallium nitride (InGaN), gallium nitride (GaN), gallium phosphide (GaP), aluminum gallium indium phosphide (AlGaInP), and aluminum gallium phosphide (AlGaP). Referring to FIG. 5C, a third transfer procedure has been completed for transferring an array of blue-emitting micro LED devices **400B** from a third carrier substrate to the TFT substrate **102**. For example, where the micro LED devices **400B** are designed to emit a blue light (e.g. 450-495 nm wavelength) the micro p-n diode **450** may include a material such as gallium nitride (GaN), indium gallium nitride (InGaN), and zinc selenide (ZnSe).

In accordance with embodiments of the invention, the transfer heads are separated by a pitch (x, y, and/or diagonal) that matches a pitch of the bank openings on the backplane corresponding to the pixel or subpixel array. Table 1 provides a list of exemplary implementations in accordance with embodiments of the invention for various red-green-blue (RGB) displays with 1920x1080 p and 2560x1600 resolu-

tions. It is to be appreciated that embodiments of the invention are not limited to RGB color schemes or the 1920×1080 p or 2560×1600 resolutions, and that the specific resolution and RGB color scheme is for illustrational purposes only.

TABLE 1

Display Substrate	Pixel Pitch (x, y)	Sub-Pixel pitch (x, y)	Pixels per inch (PPI)	Possible transfer head array pitch
55"	(634 μ m, 634 μ m)	(211 μ m, 634 μ m)	40	X: Multiples or fractions of 211 μ m Y: Multiples or fractions of 634 μ m
1920 × 1080	(85 μ m, 85 μ m)	(28 μ m, 85 μ m)	299	X: Multiples or fractions of 28 μ m Y: Multiples or fractions of 85 μ m
10"	(78 μ m, 78 μ m)	(26 μ m, 78 μ m)	326	X: Multiples or fractions of 26 μ m Y: Multiples or fractions of 78 μ m
2560 × 1600	(58 μ m, 58 μ m)	(19 μ m, 58 μ m)	440	X: Multiples or fractions of 19 μ m Y: Multiples or fractions of 58 μ m
4"				
640 × 1136				
5"				
1920 × 1080				

In the above exemplary embodiments, the 40 PPI pixel density may correspond to a 55 inch 1920×1080 p resolution television, and the 326 and 440 PPI pixel density may correspond to a handheld device with RETINA® display. In accordance with embodiments of the invention, thousands, millions, or even hundreds of millions of transfer heads can be included in a micro pick up array of a mass transfer tool depending upon the size of the micro pick up array. In accordance with embodiments of the invention, a 1 cm×1.12 cm array of transfer heads can include 837 transfer heads with a 211 μ m, 634 μ m pitch, and 102,000 transfer heads with a 19 μ m, 58 μ m pitch.

The number of micro LED devices picked up with the array of transfer heads may or may not match the pitch of transfer heads. For example, an array of transfer heads separated by a pitch of 19 μ m picks up an array of micro LED devices with a pitch of 19 μ m. In another example, an array of transfer heads separated by a pitch of 19 μ m picks up an array of micro LED devices with a pitch of approximately 6.33 μ m. In this manner the transfer heads pick up every third micro LED device for transfer to the backplane. In accordance with some embodiments, the top surface of the array of light emitting micro devices is higher than the top surface of the insulating layer so as to prevent the transfer heads from being damaged by or damaging the insulating layer (or any intervening layer) on the blackplane during placement of the micro LED devices within bank openings.

FIG. 6A is a top view illustration of an active matrix display panel in accordance with an embodiment after the formation of a top electrode layer, and FIG. 6B is a side-view illustration of the active matrix display panel of FIG. 6A taken along lines X-X and Y-Y in accordance with an embodiment of the invention. In the embodiment illustrated in FIGS. 6A-6B, a top electrode layer 118 is formed over the pixel area 104 including the array of micro LED devices 400 as well as in the non-pixel area and overlapping the ground ring 116. Additionally, the top electrode layer 118 is formed within the openings 149 and in electrical contacts with the ground tie lines 144 running between the bank openings 128 in the pixel area 104.

Referring to FIG. 6B, prior to forming the top electrode layer 118 the micro LED devices 400 are passivated within the bank openings 128 in order to prevent electrical shorting between the top and bottom electrode layers 118, 142, or shorting at the one or more quantum wells 416. As illustrated, after the transfer of the array micro LED devices 400, a passivation layer 148 may be formed around the sidewalls of the micro LED devices 400 within the array of bank openings

128. In an embodiment, where the micro LED devices 400 are vertical LED devices, the passivation layer 148 covers and spans the quantum well structure 416. The passivation layer 148 may also cover any portions of the bottom electrode layer

142 not already covered by the optional insulator layer 146 in order to prevent possible shorting. Accordingly, the passivation layer 148 may be used to passivate the quantum well structure 416, as well as the bottom electrode layer. In accordance with embodiments of the invention, the passivation layer 148 is not formed on the top surface of the micro LED devices 400, such as top conductive contact 452. In one embodiment, a plasma etching process, e.g. O₂ or CF₄ plasma etch, can be used after forming the passivation layer 148 to etch back the passivation layer 148, ensuring the top surface of the micro LED devices 400, such as top conductive contacts 452, are exposed to enable the top conductive electrode 118 layers 118 to make electrical contact with the micro LED devices 400.

In accordance with embodiments of the invention, the passivation layer 148 may be transparent or semi-transparent to the visible wavelength so as to not significantly degrade light extraction efficiency of the completed system. Passivation layer may be formed of a variety of materials such as, but not limited to epoxy, acrylic (polyacrylate) such as poly(methyl methacrylate) (PMMA), benzocyclobutene (BCB), polyimide, and polyester. In an embodiment, passivation layer 148 is formed by ink jet printing or screen printing around the micro LED devices 400.

In the particular embodiment illustrated in FIG. 6B, the passivation layer 148 is only formed within the bank openings 128. However, this is not required, and the passivation layer 148 may be formed on top of the bank structure layer 126. Furthermore, the formation of insulator layer 146 is not required, and passivation layer 148 can also be used to electrically insulate the conductive layers. As shown in the embodiment illustrated in FIG. 6C, the passivation layer 148 may also be used to passivate sidewalls of the conductive layer forming the bottom electrode 142 and/or ground tie lines 144. In an embodiment, passivation layer 148 may optionally be used to passivate ground ring 116. In accordance with some embodiments, the formation of openings 149, 130 can be formed during the process of ink jet printing or screen printing the passivation layer 148 over the ground tie lines 144 or ground ring 116. In this manner, a separate patterning operation may not be required to form the openings.

In accordance with some embodiments of the invention a canal 151, or well structure, can be formed within the bank layer 126 as illustrated in FIG. 6C in order to capture or prevent the passivation layer 148 from spreading excessively and overflowing over the ground tie lines 149, particularly when the passivation layer 148 is formed using a solvent

system such as with ink jet printing or screen printing. Accordingly, in some embodiments, a canal 151 is formed within the bank layer 126 between the bank opening 128 and an adjacent ground tie line 144.

Referring now to FIGS. 6B-6C, after formation of passivation layer 148 a top conductive electrode layer 118 is formed over each micro LED device 400 and in electrical contact with the top contact layer 452, if present. Depending upon the particular application in the following description, top electrode layer 118 may be opaque, reflective, transparent, or semi-transparent to the visible wavelength. For example, in top emission systems the top electrode layer 118 may be transparent, and for bottom emission systems the top electrode layer may be reflective. Exemplary transparent conductive materials include amorphous silicon, transparent conductive oxides (TCO) such as indium-tin-oxide (ITO) and indium-zinc-oxide (IZO), carbon nanotube film, or a transparent conductive polymer such as poly(3,4-ethylenedioxythiophene) (PEDOT), polyaniline, polyacetylene, polypyrrole, and polythiophene. In an embodiment, the top electrode layer 118 includes nanoparticles such as silver, gold, aluminum, molybdenum, titanium, tungsten, ITO, and IZO. In a particular embodiment, the top electrode layer 118 is formed by ink jet printing or screen printing. Other methods of formation may include chemical vapor deposition (CVD), physical vapor deposition (PVD), spin coating. The top electrode layer 118 may also be reflective to the visible wavelength. In an embodiment, a top conductive electrode layer 118 comprises a reflective metallic film such as aluminum, molybdenum, titanium, titanium-tungsten, silver, or gold, or alloys thereof, for example for use in a bottom emission system.

In accordance with some embodiments of the invention the ground tie lines 144 are more electrically conductive than the top electrode layer 118. In the embodiment illustrated in FIG. 3D, the ground tie lines 144 can be formed from the same metal layer used to form the source/drain connections or gate electrode layer to one of the transistors (e.g. T2) in the TFT substrate 102. For example, the ground tie lines 144 can be formed from a common interconnect material such as copper or aluminum, including their alloys. In the embodiments illustrated in FIGS. 3B-3C, the ground tie lines 144 may also be formed from the same material as the bottom electrode layers 142. For example, the ground tie lines 144 and bottom electrode layers 142 include a reflective material, which may also improve the electrical conductivity of the layers. In a specific example, the ground tie lines 144 and bottom electrodes may include a metallic film or metal particles. In accordance with some embodiments, the top electrode layer 118 is formed of a transparent or semi-transparent material such as amorphous silicon, transparent conductive oxides (TCO) such as indium-tin-oxide (ITO) and indium-zinc-oxide (IZO), carbon nanotube film, or a transparent conductive polymer such as poly(3,4-ethylenedioxythiophene) (PEDOT), polyaniline, polyacetylene, polypyrrole, and polythiophene, all of which may have a lower electrical conductivity than a conductive and reflective bottom electrode layer including a metallic film within a film stack.

Referring back to FIG. 6A again, in the particular embodiment illustrated the top electrode layer 118 is formed over the pixel area 104 including the array of micro LED devices 400 as well as in the non-pixel area and overlapping the ground ring 116. Additionally, the top electrode layer 118 is formed within the openings 149 and in electrical contacts with the ground tie lines 144 running between the bank openings 128 in the pixel area 104.

Referring now to FIGS. 7A-7B an alternative embodiment is illustrated in which the top electrode layer 118 need only be formed over the pixel area 104 in order to make electrical contact with the ground ring 116. In the particular embodiment illustrated in FIGS. 7A-7B, the top electrode layer 118 is formed over the pixel area 104 and in electrical connection with the ground tie lines 144. As illustrated, the top electrode layer 118 may be formed within openings 149 to the ground tie lines 144. In such an embodiment, since the ground tie lines 144 are in electrical connection with the ground ring 116, it is not necessary to form the top electrode layer 118 outside of the pixel area 104. As illustrated, the ground ring 116 may be buried beneath an electrically insulating layer such as such as insulator layer 146 in accordance with the embodiments illustrated in FIGS. 7A-7B.

In accordance with embodiments of the invention the line widths of the top electrode layers 118 can vary depending on application. For example, the line width may approach that of the pixel area 102. Alternatively, the line width may be minimal. For example, line widths as low as approximately 15 μm may be accomplished with commercially available in jet printers, and line widths as low as approximately 30 μm may be accomplished with commercially available screen printers. Ink jet printing may be particularly suitable in certain instances since it is a non-contact printing method. Accordingly, the line width of the top electrode layer may be more or less than the maximum width of the micro LED devices in accordance with some embodiments of the invention.

Referring to FIGS. 8A-8B an embodiment is illustrated in which separate top electrode layers 118 are formed connecting one or more micro LED devices 400 with one or more ground tie lines 144. In the particular embodiment illustrated in FIGS. 8A-8B, the top electrode layers 118 only need to provide the electrical path from a micro LED device 400 to a nearby ground tie line 144. Accordingly, the top electrode layers 118 do not cover the entire pixel area 104. Likewise, top electrode layers 118 are not required to cover the entire bank openings 128 or subpixel areas. In the particular embodiment illustrated, each top electrode layer 118 connects a micro LED device 400 on opposite sides of an intermediate ground tie line 144. However, this particular configuration is exemplary and a number of different arrangements are possible. As illustrated, the top electrode layer 118 may be formed within openings 149 to the ground tie lines 144. In such an embodiment, since the ground tie lines 144 are in electrical connection with the ground ring 116, it is not necessary to form the top electrode layer 118 outside of the pixel area 104.

As illustrated, the ground ring 116 may be buried beneath an electrically insulating layer such as such as insulator layer 146 in accordance with the embodiments illustrated in FIGS. 8A-8B. In the particular embodiments illustrated in FIG. 8A, topmost row of micro LED devices 400 are illustrated as being connected to the ground ring 116 with individual top electrode layers 118. In such an embodiment, each top electrode layer 118 may contact the ground ring 116 through one or more openings 130 as previously described. Accordingly, while the embodiments illustrated in FIGS. 8A-8B provide one manner for connecting the micro LED devices 400 to ground tie lines 144 within the pixel area 104, this does not preclude using separate top electrode layers 118 to connect to the ground ring 116 without going through a ground tie line 144.

In one aspect, the particular embodiment illustrated in FIGS. 8A-8B may be particularly suitable for localized formation of the top electrode layers 118 with ink jet printing or screen printing. Conventional AMOLED backplane process-

ing sequences such as those used for the fabrication of the display panels in FIGS. 1-2 typically blanket deposit the top electrode layer in deposition a chamber, followed by singulation of the individual backplanes **100** from a larger substrate. In accordance with some embodiments, the display panel **100** backplane is singulated from a larger substrate prior to transferring the array of micro LED devices **400**. In an embodiment, ink jet printing or screen printing provides a practical approach for patterning the individual top electrode layers **118** without requiring a separate mask layer for each separate display panel **100**.

While not illustrated separately it is to be appreciated that the embodiments illustrated in FIGS. 6A-6B, FIGS. 7A-7B and FIGS. 8A-8B are combinable with the alternative opening configurations included in FIGS. 3C-3D and passivation layer **148** configuration illustrated in FIG. 6C.

The formation of separate top electrode layer **118** as described above with regard to FIGS. 8A-8B may provide an additional benefit during electrical testing of the panel **100** after formation of the top electrode layers **118**. For example, it may not have been discovered prior to formation of the top electrode layers **118** that an underlying transistor has malfunctioned and may always be 'on'. One implication could be that the associated subpixel is always 'on' and emitting light. In the embodiment illustrated in FIG. 8C the top electrode layer **118** connected to the defective TFT transistor is cut using a suitable technique such as laser scribing to turn 'off' the subpixel. In this manner, curing the electrical defect can be performed on the top surface of the TFT substrate rather than having to drill down to access the TFT transistor.

Referring now to FIGS. 9A-9D, embodiments of the invention may also be utilized to incorporate ground tie lines **134** into AMOLED display panels. Referring to the embodiments illustrated in FIGS. 9A-9B, a bottom electrode layer **124** is formed on the planarization layer **122** in electrical connection with the underlying TFT circuitry. In the embodiments illustrated ground tie lines **134** may be formed simultaneously with the bottom electrode layer **124**. Likewise, ground ring **116** may be formed simultaneously with the bottom electrode layer **124**. Following the formation of the bottom electrode layer **124** and optionally the ground tie lines **134** and/or ground ring **116**, a pixel defining layer **125** is formed including an array of subpixel openings **127** and an array of ground tie line openings **132**. An organic layer **120** is then deposited over the subpixel openings **127**. In an embodiment the organic layer **120** is not deposited within ground tie line openings **132** or on the ground ring **116**. A top electrode layer **118** may then be formed over the patterned pixel defining layer within subpixel openings **127**, within the openings **132** to make electrical contact with the ground tie lines **134**, and optionally over the ground ring **116**. However, it is not required to make electrical contact with ground ring **116**. In the embodiment illustrated in FIGS. 9C-9D, the top electrode layer **118** is only deposited within the pixel area **104**, and the top electrode layer **118** does not overlap the ground ring **116**.

While not illustrated separately it is to be appreciated that the embodiments illustrated in FIGS. 9A-9D contemplate alternative opening configurations. For example, openings to the ground tie line **134** or ground ring **116** could be made through the planarization layer **122**.

FIG. 10 illustrates a display system **1000** in accordance with an embodiment. The display system houses a processor **1010**, data receiver **1020**, a display panel **100**, such as any of the display panels described above. The data receiver **1020** may be configured to receive data wirelessly or wired. Wireless may be implemented in any of a number of wireless standards or protocols including, but not limited to, Wi-Fi

(IEEE 802.11 family), WiMAX (IEEE 802.16 family), IEEE 802.20, long term evolution (LTE), Ev-DO, HSPA+, HSDPA+, HSUPA+, EDGE, GSM, GPRS, CDMA, TDMA, DECT, Bluetooth, derivatives thereof, as well as any other wireless protocols that are designated as 3G, 4G, 5G, and beyond.

Depending on its applications, the display system **1000** may include other components. These other components include, but are not limited to, memory, a touch-screen controller, and a battery. In various implementations, the display system **1000** may be a television, tablet, phone, laptop, computer monitor, kiosk, digital camera, handheld game console, media display, ebook display, or large area signage display.

In utilizing the various aspects of this invention, it would become apparent to one skilled in the art that combinations or variations of the above embodiments are possible for integrating ground tie lines and micro LED devices into an active matrix display panel. While the above embodiments have been described with regard to a top emission structure, embodiments of the invention are also applicable to bottom emission structures. For example, rather than locating the bank openings **128** or subpixel openings **127** above the TFT circuitry, the openings could be located adjacent the TFT circuitry on lower layers in the TFT substrate **102**. Similarly, while top gate transistor structures have been described, embodiments of the invention may also be practiced with bottom gate transistor structures. Furthermore, while embodiments of the invention have been described and illustrated with regard to a high side drive configuration, embodiments may also be practiced with a low side drive configuration in which the ground tie lines and ground ring described above become the power line in the panel. Although the present invention has been described in language specific to structural features and/or methodological acts, it is to be understood that the invention defined in the appended claims is not necessarily limited to the specific features or acts described. The specific features and acts disclosed are instead to be understood as particularly graceful implementations of the claimed invention useful for illustrating the present invention.

What is claimed is:

1. A display panel comprising:

- a ground line;
- a display substrate including a pixel area and a non-pixel area;
- an array of micro LED devices on the display substrate within the pixel area;
- an array of bottom contacts formed on a planarization layer and underneath the array of micro LED devices;
- an array of ground tie lines located below the planarization layer and running between the micro LED devices in the pixel area and electrically connected to the ground line; and
- one or more top electrode layers over and in electrical contact with the array of micro LED devices and the array of ground tie lines.

2. The display panel of claim 1, wherein the micro LED devices are vertical micro LED devices.

3. The display panel of claim 2, wherein each vertical micro LED device comprises an inorganic semiconductor-based p-n diode.

4. The display panel of claim 3, wherein the micro LED devices each have a maximum width of 1 μm -100 μm .

19

5. The display panel of claim 3, further comprising a transparent passivation layer spanning sidewalls of the array of vertical micro LED devices, wherein the transparent passivation layer does not completely cover a top conductive contact of each vertical micro LED device.

6. The display substrate of claim 1, further comprising a bank layer on the planarization layer, the bank layer comprising an array of bank openings, wherein the array of micro LED devices are within the array of bank openings.

7. The display substrate of claim 1, further comprising an array of via openings in the planarization layer exposing the array of ground tie lines.

8. The display substrate of claim 7, further comprising an array of conductive via opening layers within the array of via openings and on the array of ground tie lines.

9. The display panel of claim 8, wherein the one or more top electrode layers comprises a single top electrode layer over and in electrical contact with the array of micro LED devices and the array of conductive via opening layers.

10. The display panel of claim 8, wherein the one or more top electrode layers comprises an array of electrode layers over and in electrical contact with the array of micro LED devices and the array of conductive via opening layers.

20

11. The display panel of claim 3, wherein the one or more top electrode layers comprises a single top electrode layer over and in electrical contact with the array of micro LED devices and the array of ground tie lines.

12. The display panel of claim 11, wherein the single top electrode layer is formed of a transparent or semi-transparent material.

13. The display panel of claim 11, wherein the single top electrode layer comprises a material selected from the group consisting of PEDOT and ITO.

14. The display panel of claim 3, wherein the one or more top electrode layers comprises an array of electrode layers over and in electrical contact with the array of micro LED devices and the array of ground tie lines.

15. The display panel of claim 14, wherein each top electrode layer electrically connects a plurality of micro LED devices to a single ground tie line.

16. The display panel of claim 14, wherein the array of top electrode layers is formed of a transparent or semi-transparent material.

17. The display panel of claim 14, wherein the array of top electrode layers comprises a material selected from the group consisting of PEDOT and ITO.

* * * * *

专利名称(译)	有源矩阵显示面板，带接地线		
公开(公告)号	US9214494	公开(公告)日	2015-12-15
申请号	US14/640979	申请日	2015-03-06
[标]申请(专利权)人(译)	勒克斯维科技公司		
申请(专利权)人(译)	LUXVUE科技股份有限公司		
当前申请(专利权)人(译)	LUXVUE科技股份有限公司		
[标]发明人	SAKARIYA KAPIL V BIBL ANDREAS HU HSIN HUA		
发明人	SAKARIYA, KAPIL V. BIBL, ANDREAS HU, HSIN-HUA		
IPC分类号	H01L27/15 H01L33/20 H01L25/075 H01L33/42 H01L27/12 G09G3/32		
CPC分类号	H01L27/156 H01L25/0753 H01L27/124 H01L33/20 H01L33/42 G09G3/32 H01L24/95 H01L33/62 H01L2924/0002 H01L2924/12041 H01L2924/12042 H01L2924/12044 H01L2924/00		
其他公开文献	US20150179703A1		
外部链接	Espacenet USPTO		

摘要(译)

描述了显示面板和形成显示面板的方法。显示面板可以包括薄膜晶体管基板，该薄膜晶体管基板包括像素区域和非像素区域。像素区域包括堤开口阵列和堤开口阵列内的底电极阵列。地线位于非像素区域中，并且接地连接线阵列在像素区域中的堤开口之间延伸并且电连接到非像素区域中的地线。

