



(19) **United States**

(12) **Patent Application Publication**
Bower et al.

(10) **Pub. No.: US 2018/0204772 A1**
(43) **Pub. Date: Jul. 19, 2018**

(54) **SYSTEMS AND METHODS FOR CONTROLLING RELEASE OF TRANSFERABLE SEMICONDUCTOR STRUCTURES**

Publication Classification

(51) **Int. Cl.**
H01L 21/78 (2006.01)
(52) **U.S. Cl.**
CPC *H01L 21/7813* (2013.01)

(71) Applicant: **X-Celeprint Limited**, Cork (IE)
(72) Inventors: **Christopher Bower**, Raleigh, NC (US);
Matthew Meitl, Durham, NC (US)

(57) **ABSTRACT**


The disclosed technology relates generally to methods and systems for controlling the release of micro devices. Prior to transferring micro devices to a destination substrate, a native substrate is formed with micro devices thereon. The micro devices can be distributed over the native substrate and spatially separated from each other by an anchor structure. The anchors are physically connected/secured to the native substrate. Tethers physically secure each micro device to one or more anchors, thereby suspending the micro device above the native substrate. In certain embodiments, single tether designs are used to control the relaxation of built-in stress in releasable structures on a substrate, such as Si (1 1 1). Single tether designs offer, among other things, the added benefit of easier break upon retrieval from native substrate in micro assembly processes. In certain embodiments, narrow tether designs are used to avoid pinning of the undercut etch front.

(21) Appl. No.: **15/910,809**

(22) Filed: **Mar. 2, 2018**

Related U.S. Application Data

(63) Continuation of application No. 15/430,101, filed on Feb. 10, 2017, now Pat. No. 9,947,584, which is a continuation of application No. 14/743,988, filed on Jun. 18, 2015, now Pat. No. 9,601,356.
(60) Provisional application No. 62/029,535, filed on Jul. 27, 2014, provisional application No. 62/014,078, filed on Jun. 18, 2014.






FIG. 1




FIG. 2






FIG. 3








FIG. 6A




FIG. 6B




FIG. 7A




FIG. 7B




FIG. 8




FIG. 9







FIG. 10D




FIG. 11A




FIG. 11B




FIG. 11C




FIG. 12A




FIG. 12B




FIG. 12C




FIG. 13




FIG. 14




FIG. 15




FIG. 16




FIG. 17




FIG. 18

Prior Art




FIG. 19




FIG. 20

SYSTEMS AND METHODS FOR CONTROLLING RELEASE OF TRANSFERABLE SEMICONDUCTOR STRUCTURES

RELATED APPLICATIONS

[0001] This application is a continuation of U.S. patent application Ser. No. 14/743,988, filed Jun. 18, 2015, entitled "Systems and Methods for Controlling Release of Transferable Semiconductor Structures," which claims priority to and the benefit of U.S. Provisional Patent Application No. 62/014,078, filed Jun. 18, 2014, titled "Systems and Methods for Controlling Release of Transferable Semiconductor Structures," and U.S. Provisional Patent Application No. 62/029,535, filed Jul. 27, 2014, titled "Systems and Methods for Controlling Release of Transferable Semiconductor Structures," the content of each of which is incorporated by reference herein in their entirety.

FIELD OF THE INVENTION

[0002] The disclosed technology relates generally to systems and methods for controlling the release of micro devices using tethers from a native substrate.

BACKGROUND OF THE INVENTION

[0003] The disclosed technology relates generally to the formation of transferable micro devices. Semiconductor chip- or die-automated assembly equipment typically uses vacuum-operated placement heads, such as vacuum grippers or pick-and-place tools, to pick up and apply devices to a substrate. It is often difficult to pick up and place ultra-thin or small micro devices using this technology. Micro transfer printing permits the selection and application of these ultra-thin, fragile, or small micro devices without causing damage to the micro devices themselves.

[0004] Micro-structured stamps can be used to pick up micro devices from a native source substrate on which they are formed, transport the micro devices to a non-native destination substrate, and print the micro devices onto the destination substrate. Surface adhesion forces are used to control the selection and printing of these micro devices onto the destination substrate. This process can be performed massively in parallel, transferring hundreds to thousands of discrete structures in a single pick-up and print operation.

[0005] Electronically active components can be printed onto the non-native destination substrates. For example, these printing techniques can be used to form imaging devices such as flat-panel liquid crystal, LED, or OLED display devices or in digital radiographic plates. In each instance, the electronically active components are transferred from a native substrate to a destination substrate (e.g., a non-native substrate used to, for example, form an array of the active micro-device components). The active components are picked up from the native substrate and transferred to the destination substrate using an elastomer stamp.

[0006] Micro transfer printing enables parallel assembly of high-performance semiconductor micro devices onto virtually any substrate material, including glass, plastics, metals or other semiconductors. The substrates can be transparent or flexible, thereby permitting the production of flexible electronic devices. Flexible substrates can be integrated in a large number of configurations, including configurations not

possible with brittle silicon-based electronic devices. Additionally, some plastic substrates, for example, are mechanically rugged and can be used to provide electronic devices that are less susceptible to damage or electronic performance degradation caused by mechanical stress. These materials can be used to fabricate electronic devices by continuous, high-speed, printing techniques capable of distributing electronic devices over large substrate areas at low cost (e.g., roll-to-roll manufacturing). Moreover, these conventional micro transfer-printing techniques can be used to print semiconductor devices at temperatures compatible with assembly on plastic polymer substrates. In addition, semiconductor materials can be printed onto large areas of substrates thereby enabling continuous, high-speed printing of complex integrated electrical circuits over large substrate areas. Moreover, fully flexible electronic devices with good electronic performance in flexed or deformed device orientations can be provided to enable a wide range of flexible electronic devices. However, conventional micro transfer printing techniques lack the reproducibility and precision required to efficiently produce electronics with high-density devices at low cost.

[0007] In a conventional micro transfer printing process, prior to transferring micro devices to a destination substrate, a native source substrate is provided with a sacrificial layer having sacrificial material and a plurality of micro devices formed at least in part over the sacrificial layer. The micro devices can be distributed over the native source substrate and spatially separated from each other by an anchor structure. The anchors are physically connected or secured to the native source substrate and tethers physically secure each micro device to one or more anchors.

[0008] Anchor structures that remain rigidly attached to the substrate and tether structures that join the releasable micro object to the anchor serve to maintain the spatial configuration of the micro objects upon partial or full separation of the micro object from the bulk substrate. When a transfer stamp picks up the device, the tethers for each device that is picked up are broken. Regarding micro transfer printing, see, for example, U.S. Pat. No. 7,982,296, issued Jul. 19, 2011, the content of which is incorporated herein by reference in its entirety.

[0009] However, it has been demonstrated that the release of the active micro-device components is not reliably controlled and not predictable, leading to inefficiencies, irreproducibilities, and errors. Therefore, there is a need for an improved method and system for efficiently and predictably controlling the release of semiconductor structures.

SUMMARY OF THE INVENTION

[0010] The disclosed technology relates generally to systems and methods for controlling the release of micro devices using tethers from a native substrate. The disclosed technology provides reliably controlled and predictable release of micro-device components from a substrate, leading to efficiencies, reproducibilities, and less errors during micro-assembly. In certain embodiments, the disclosed technology accomplishes this using a single, off-center tether per micro-device. As described herein, this improves the removal of a sacrificial layer. For example, in some embodiments, this improves the etching of the sacrificial layer such that the desired area under the micro-device is removed in its entirety so that the micro-device can be micro-assembled

(e.g., the micro-device can be picked up by an elastomer stamp causing the tether to break).

[0011] The disclosed technology relates generally to systems and methods for controlling the release of micro objects (devices) from a native substrate using tethers. In some embodiments, micro objects are designed or configured so that their orientation and spatial configuration are preserved when the micro objects are released from a substrate. Anchor structures that remain rigidly attached to the native substrate and tether structures that join the releasable micro object to the anchor serve to maintain the spatial configuration of the micro objects upon partial or full release of the micro object from the substrate. This can be accomplished by selective removal of a sacrificial layer (e.g., at least partially underneath the micro object) by undercutting, etching, ablation, or other means. In some embodiments, the sacrificial layer is a portion of the native substrate on which the active components are grown. This leaves each micro device supported on and connected to the native substrate by at least one anchor and at least one tether.

[0012] In one aspect, the invention is directed to an array of micro devices, the array comprising: a source substrate having a process side; a sacrificial layer comprising sacrificial material on the process side of the source substrate; a plurality of releasable micro objects formed at least in part on the sacrificial layer; a plurality of anchor structures located on the process side of the source substrate, wherein the anchor structures remain rigidly attached to the source substrate in the absence of the sacrificial material; and a plurality of tethers, wherein each tether of the plurality of tethers connects a releasable micro object of the plurality of releasable micro objects to one of the anchor structures and each tether of the plurality of tethers is located on an off-center, anchor-facing edge of the respective releasable micro object of the plurality of releasable micro objects, so that in the absence of the sacrificial material the releasable micro objects move with respect to the anchor structures and the tethers deform and are mechanically stressed.

[0013] In certain embodiments, each of the plurality of tethers is sized and shaped to break when a corresponding micro object is contacted by an elastomer stamp for micro transfer printing from the source substrate to a target substrate, different from the source substrate.

[0014] In certain embodiments, the sacrificial material is a portion of the source substrate. In certain embodiments, the anchor structure forms a continuous structure, spanning more than one releasable micro object of the plurality of releasable micro objects in at least one dimension. In certain embodiments, the anchor structure comprises a plurality of anchors.

[0015] In certain embodiments, each of the plurality of anchors are characterized by locally concave or internal corners and each of the plurality of releasable micro objects is characterized by locally convex or external corners.

[0016] In certain embodiments, each of the plurality of tethers is a tether with a width of 10 μm to 40 μm . In certain embodiments, each of the plurality of tethers is a tether with a narrow shape and a width of 1 μm to 5 μm , 5 μm to 10 μm , 10 μm to 15 μm , 15 μm to 20 μm , or 20 μm to 40 μm .

[0017] In certain embodiments, the sacrificial layer has an anisotropic crystal structure.

[0018] In certain embodiments, the sacrificial layer comprises a material selected from the group consisting of Silicon (1 1 1), InAlP, InP, GaAs, InGaAs, AlGaAs, GaSb,

GaAlSb, AlSb, InSb, InGaAlSbAs, InAlSb, and InGaP. In certain embodiments, the sacrificial layer comprises Silicon (1 1 1).

[0019] In certain embodiments, each of the tethers comprises one or more notches that provide a point of fracture when a respective releasable micro object is moved with respect to the anchor structures.

[0020] In certain embodiments, the source substrate comprises a member selected from the group consisting of Silicon (1 1 1), silicon, indium phosphide, gallium arsenide, and sapphire.

[0021] In certain embodiments, each of the tethers has an aspect ratio of greater than 1.732.

[0022] In another aspect, the invention is directed to a method of making thin and low-cost wafer-packaged micro-scale devices suitable for micro transfer printing using a (111) Silicon system, the method comprising: providing a plurality of micro-scale devices; assembling the micro-scale devices onto a carrier wafer using micro-assembly techniques, wherein the carrier wafer comprises Silicon (111) and a first dielectric layer; embedding the assembled micro-scale devices within a second layer of dielectric; patterning the first and second dielectric layers to define a perimeter of each of the micro-scale devices with anchors and tethers that preserve the spatial configuration of the micro-scale devices with respect to the carrier wafer when the micro-scale devices are moved with respect to the carrier wafer, thereby providing a wafer-level thin wafer package having micro-scale devices suitable for micro transfer printing to other substrates.

[0023] In certain embodiment, the method further comprises: forming pad structures on at least one of the top or bottom surfaces of the micro-scale devices, thereby forming a surface-mountable device.

[0024] In certain embodiments, the micro scale devices each comprises an integrated circuit interconnected with at least two sensors and an antenna produced using the same wafer-level metallization. In certain embodiments, the method further comprises: micro transfer printing the micro-scale devices onto a reeled tape; and applying the micro-scale devices to a destination substrate using a tape-fed high-speed chip shooter.

[0025] In certain embodiments, the method further comprises: pre-molding the micro-scale devices using a wafer-fed die-attach tool, thereby forming package-on-lead-frames.

[0026] In certain embodiments, the method further comprises: forming package-in-package devices of the micro-scale devices using a wafer-fed die-attach tool.

[0027] In certain embodiments, the method further comprises: forming wafer-level-packages from the micro-scale devices using a wafer-fed die-attach tool or a wafer-fed micro-transfer printer.

[0028] In another aspect, the invention is directed to a method of fabricating a printable component array, the method comprising: forming a sacrificial layer comprising sacrificial material on a process side of a source substrate; forming a plurality of releasable micro objects at least in part on the sacrificial layer; forming an anchor structure on the source substrate that remains rigidly attached to the source substrate in the absence of the sacrificial material; forming a plurality of tethers, wherein each tether of the plurality of tethers connects a releasable micro object of the plurality of releasable micro objects to one of the anchor structures, each

tether of the plurality of tethers is located on an off-center, anchor-facing edge of the respective releasable micro object of the plurality of releasable micro objects, and each tether is shaped to fracture in response to movement of the releasable micro object, so that in the absence of the sacrificial material: the releasable micro objects move with respect to the anchor structures; the tethers deform and are mechanically stressed; and each tether of the plurality of tethers remains rigidly attached to both a respective anchor and a respective releasable micro object of the plurality of micro objects, thereby preserving the spatial configuration of the plurality of releasable micro objects with respect to the source substrate; removing at least a portion of the sacrificial material underneath the plurality of releasable micro objects so that the releasable micro objects move with respect to the anchor structures and the tethers deform and are mechanically stressed.

[0029] In certain embodiments, the removal process progresses rapidly under the plurality of releasable micro objects relative to the rate at which the anchor structure is released. In certain embodiments, each tether of the plurality of tethers has a narrow shape with a width of 10 μm to 40 μm , thereby inhibiting the formation of locally-concave or internal corners.

[0030] In certain embodiments, the sacrificial layer has an anisotropic crystal structure for which the removal process progresses faster in some directions and slower in other directions.

[0031] In certain embodiments, each tether of the plurality of tethers comprises one or more notches, the notch providing a point of fracture for a releasable micro object when the releasable micro object is moved.

[0032] In certain embodiments, the removal process reaches completion at areas near a given tether.

[0033] In certain embodiments, the source substrate is a material selected from the group consisting of Silicon (1 1 1), silicon, indium phosphide, gallium arsenide, and sapphire.

[0034] In certain embodiments, each of the plurality of tethers has an aspect ratio of less than 1.732.

[0035] In another aspect, the invention is directed to a method of fabricating a plurality of transferable micro objects, comprising: forming a sacrificial layer comprising sacrificial material on a process side of a source substrate; forming a plurality of releasable micro objects (e.g., printable electronic components, printable active component, micro devices, micro-scale devices) at least in part on the sacrificial layer; applying a polymer layer (e.g., photoresist materials, photodefinable materials) over the plurality of releasable micro objects and at least a portion of the source substrate, wherein the polymer layer encapsulates the plurality of releasable micro objects (e.g., the portion of the plurality of releasable micro objects other than portions in contact with the sacrificial layer); treating the polymer layer to form: (i) a plurality of anchor structures on the source substrate for the plurality of transferable micro objects, (ii) at least one tether between each transferable micro object and a pre-determined anchor structure of the plurality of anchor structures, and (iii) for each of the releasable micro objects, a port of ingress in the polymer layer to a portion of the sacrificial layer underneath a respective transferable micro object; and removing (e.g., by an undercutting etch or ablation) at least a portion of the sacrificial layer underneath the plurality of releasable micro objects.

[0036] In certain embodiments, the one or more anchor structures remains rigidly attached to the substrate when the transferable micro object is moved.

[0037] In certain embodiments, at least a portion of the sacrificial layer underneath the plurality of releasable micro objects causes each of the plurality of releasable micro objects to move and apply stress on a respective subset of the plurality of tethers.

[0038] In certain embodiments, the respective subset of the plurality of tethers comprises a single tether.

[0039] In certain embodiments, the method further comprises transferring the releasable micro objects and removing at least a portion of the polymer from the micro objects. In certain embodiments, the method further comprises removing at least a portion of the polymer from the micro objects comprises at least one of dissolution, etching, and ashing of the polymer. In certain embodiments, the method further comprises transferring the releasable micro objects by contacting at least a portion of a printing stamp to a corresponding portion of the polymer.

[0040] In certain embodiments, single-tether designs are used to control the relaxation of built-in stress in releasable structures on a substrate, such as Si (1 1 1). Single-tether designs offer, among other things, the added benefit of easier breaking upon removal from a native substrate in micro-assembly processes. In certain embodiments, narrow-tether designs (e.g., tethers with a width of 1 μm to 5 μm , 5 μm to 10 μm , 10 μm to 15 μm , 15 μm to 20 μm , or 20 μm to 40 μm) are used to avoid pinning of an undercutting etch front when etching the sacrificial material from the sacrificial layer.

[0041] The disclosed technology, in certain embodiments, includes a method of fabricating a printable component array. The method can include forming a sacrificial layer having sacrificial material on a process side of a source substrate; forming a plurality of releasable micro objects (e.g., printable electronic components, printable active component) at least in part on the sacrificial material; forming an anchor structure on the source substrate that remains rigidly attached to the substrate in the absence of the sacrificial material when the sacrificial material is at least partially removed; performing a removal process (e.g., etch or ablation undercutting the micro objects) to remove at least a portion of the sacrificial material from the sacrificial layer underneath the plurality of releasable micro objects, thereby causing each of the plurality of releasable micro objects to relax and apply mechanical stress on a respective subset (e.g., a single tether) of a plurality of tethers when the micro objects move with respect to the anchor structures so that the tethers deform and are mechanically stressed, for example in response to contact with an elastomer stamp.

[0042] In certain embodiments, a single tether of the plurality of tethers physically secures each of the plurality of micro objects to the anchor structure, thereby controlling the relaxation of built-in stress in the plurality of releasable micro objects after the undercut removal process is performed. Each tether of the plurality of tethers can be shaped to fracture responsive to pressure applied thereto (e.g., during transfer/printing). Each tether of the plurality of tethers can remain rigidly attached to both a respective anchor and a respective releasable micro object of the plurality of micro objects, thereby preserving the spatial configuration of remaining micro objects upon transfer of at least a portion of the plurality of micro objects from the source substrate (e.g., via micro transfer printing).

[0043] The disclosed technology, in certain embodiments, includes an array of micro objects. The array can include a source substrate; a sacrificial layer on a process side of the source substrate; a plurality of releasable micro objects (e.g., printable electronic components, printable active components) formed at least in part on top of the sacrificial layer material; an anchor structure located on the process side of the source substrate, wherein the anchor structure remains rigidly attached to the substrate when the sacrificial layer is removed, thereby preserving the spatial configuration of the plurality of releasable micro objects with respect to the source substrate; a plurality of tethers, wherein a subset (e.g., a single tether) of the plurality of tethers connects each of the plurality of releasable micro objects to the anchor structure, thereby controlling relaxation of built-in stress in the plurality of releasable micro objects after a removal process removes at least a portion of the sacrificial layer underneath the plurality of releasable micro objects (e.g., an undercutting etch or ablation).

[0044] The anchor structure can remain rigidly attached to the substrate when the sacrificial layer is removed by the removal process (e.g., an undercutting etch or ablation), thereby causing the plurality of releasable micro objects to move and apply additional stress on at least a portion of the plurality of tethers, each of which connects one of the plurality of releasable micro objects to the substrate via the anchor structure after the sacrificial material removal is performed.

[0045] The disclosed technology, in certain embodiments, includes a method of making transfer-ready integrated circuits using a silicon-on-insulator source wafer with a (1 1 1) handle wafer. The method can include forming a silicon-on-insulator wafer comprising a handle wafer with a (1 1 1) orientation; forming a plurality of transfer-ready integrated circuits on the silicon-on-insulator wafer; patterning the device silicon layer (e.g., thereby physically defining the shape of the integrate circuits); patterning and etching through dielectric layers around the perimeter of each of the transfer-ready integrated circuits, thereby defining a plurality of micro devices; and depositing an inorganic dielectric to passivate the exposed device silicon.

[0046] The disclosed technology, in certain embodiments, includes a method of generating thin and low-cost wafer-packaged micro-scale devices suitable for micro transfer printing using a (1 1 1) system. The method can include providing a plurality of micro-scale devices and assembling the micro-scale devices onto a carrier wafer using micro-assembly techniques, wherein the carrier wafer comprises (1 1 1) oriented silicon and a first dielectric layer (e.g., an organic material, for example polyimide, or an inorganic material, for example silicon dioxide); embedding the assembled micro devices within a second layer of dielectric (e.g., an organic material, for example a spin-coated polyimide, or a deposited inorganic material); patterning the first and second dielectric layers, to define a perimeter of the micro-scale devices with anchors and tethers that preserve the spatial configuration of the micro-scale devices with respect to the carrier wafer when the micro-scale devices are moved with respect to the carrier wafer, thereby providing a wafer-level thin wafer package having micro-scale devices suitable for micro transfer printing to other substrates (e.g., using vacuum collets or using a transfer element that physically contacts the devices).

[0047] The disclosed technology, in certain embodiments, includes a method of fabricating a plurality of transferable micro objects. The method includes forming a sacrificial layer including sacrificial material on a process side of a source substrate; forming a plurality of releasable micro objects (e.g., printable electronic components, printable active component, micro devices, micro-scale devices) at least in part on the sacrificial layer; applying a polymer layer (e.g., photoresist materials, photodefinable materials) over the plurality of releasable micro objects and at least a portion of the source substrate, wherein the polymer layer encapsulates the plurality of releasable micro objects (e.g., the portion of the plurality of releasable micro objects other than portions in contact with the sacrificial layer); treating the polymer layer to form: (i) a plurality of anchor structures on the source substrate for the plurality of transferable micro objects, the one or more anchor structures remaining rigidly attached to the substrate when the sacrificial layer of the transferable micro object is moved, (ii) at least one tether between each transferable micro object and a pre-determined anchor structure of the plurality of anchor structures, and (iii) for each of the releasable micro objects, a port of ingress in the polymer layer to a portion of the sacrificial layer underneath a respective transferable micro object; and performing a removal process (e.g., an undercutting etch or ablation) to remove at least a portion of the sacrificial layer underneath the plurality of releasable micro objects (e.g., thereby causing each of the plurality of releasable micro objects to move and apply stress on a respective subset (e.g., a single tether) of the plurality of tethers).

[0048] The disclosed technology, in certain embodiments, allows for a single polymer layer (e.g., a photoresist or photo-sensitive material) to be employed during the fabrication of the array of micro devices. The single layer (e.g., encapsulation structure) can serve as an anchor structure, a tether structure, or an encapsulation structure or all three. The encapsulation structure, in some embodiments, serves to protect the array of micro devices (including any chemically-sensitive layers thereof) during the device fabrication and micro-printing process and to provide a contact and adhesion interface to the transferring elements employed in the micro-printing process. The encapsulation structure can provide electrical insulation and protection from contaminants, moisture, and oxidizers. The layer can further enable electrical contacts on the bottom, top, or side of a printable object.

[0049] In some embodiments, the single polymer layer improves the density of the printable, micro devices for a given wafer. The supporting, non-printable structures (e.g., the anchor and tether) can be fabricated such that distance between adjacent printable structures is small (e.g., less than half the width of the printable structures).

[0050] In some embodiments, polymers (e.g., photoresist or photo-sensitive materials) have fracture characteristics that are desirable as a tether, such as sufficient stiffness to maintain the spatial configurations of printable structures during a release process. The polymer that forms the anchoring, tethering, or encapsulation can also be selectively removed from the printable objects and the target substrate after transfer by dissolution, etching, ashing or other processes. In some embodiments, the polymer also has sufficient adhesion to serve as a contact interface with a transfer element of the micro-printing system to be picked up from native substrate and can be treated to serve as an interface

for separation between the transfer element and the micro devices once the micro devices have been transferred to a destination substrate. Thus, in an embodiment, the releasable micro objects are transferred by contacting at least a portion of a printing stamp to a corresponding portion of the polymer.

[0051] In another aspect, the disclosed technology includes an array of micro devices, the array including: a source substrate having a process side; a sacrificial layer comprising sacrificial material on the process side of the source substrate; a plurality of releasable micro objects formed at least in part on the sacrificial layer; a plurality of anchor structures located on the process side of the source substrate, wherein the anchor structures remain rigidly attached to the source substrate in the absence of the sacrificial material; and a plurality of tethers, wherein each tether of the plurality of tethers connects a releasable micro object of the plurality of releasable micro objects to one of the anchor structures and each tether of the plurality of tethers is located on an off-center, anchor-facing edge of the respective releasable micro object of the plurality of releasable micro objects, so that in the absence of the sacrificial material the releasable micro objects move with respect to the anchor structures and the tethers deform and are mechanically stressed.

[0052] In certain embodiments, each of the plurality of tethers is sized and shaped to break when a corresponding micro object is contacted by an elastomer stamp for micro transfer printing from the source substrate to a target substrate, different from the source substrate.

[0053] In certain embodiments, the sacrificial material is a portion of the source substrate.

[0054] In certain embodiments, the anchor structure forms a continuous structure, spanning more than one releasable micro object of the plurality of releasable micro objects in at least one dimension.

[0055] In certain embodiments, the anchor structure comprises a plurality of anchors.

[0056] In certain embodiments, each of the plurality of anchors are characterized by locally concave or internal corners and each of the plurality of releasable micro objects is characterized by locally convex or external corners.

[0057] In certain embodiments, each of the plurality of tethers is a tether with a width of 10 μm to 40 μm .

[0058] In certain embodiments, each of the plurality of tethers is a tether with a narrow shape and a width of 1 μm to 5 μm , 5 μm to 10 μm , 10 μm to 15 μm , 15 μm to 20 μm , or 20 μm to 40 μm .

[0059] In certain embodiments, the sacrificial layer has an anisotropic crystal structure. In certain embodiments, the sacrificial layer includes a material selected from the group consisting of Silicon (1 1 1), InAlP, InP, GaAs, InGaAs, AlGaAs, GaSb, GaAlSb, AlSb, InSb, InGaAlSbAs, InAlSb, and InGaP.

[0060] In certain embodiments, the sacrificial layer comprises Silicon (1 1 1).

[0061] In certain embodiments, each of the tethers comprises one or more notches that provide a point of fracture when a respective releasable micro object is moved with respect to the anchor structures.

[0062] In certain embodiments, the source substrate comprises a member selected from the group consisting of Silicon (1 1 1), silicon, indium phosphide, gallium arsenide, and sapphire.

[0063] In certain embodiments, each of the tethers has an aspect ratio of greater than 1.732.

[0064] In certain embodiments, the sacrificial layer comprises InAlP.

BRIEF DESCRIPTION OF THE FIGURES

[0065] The foregoing and other objects, aspects, features, and advantages of the present disclosure will become more apparent and better understood by referring to the following description taken in conjunction with the accompanying drawings, in which:

[0066] FIG. 1 is an illustration of an example native substrate with micro devices formed thereon;

[0067] FIG. 2 is an illustration of the process of undercut etching over time;

[0068] FIG. 3 is an illustration of the process of undercut etching a transferable semiconductor with a single tether;

[0069] FIG. 4 is an illustration of the process of undercut etching a transferable semiconductor with a single tether placed off-center;

[0070] FIGS. 5A and 5B are illustrations of an example structure with four tethers per releasable structure;

[0071] FIGS. 6A and 6B are example illustrations of a tether specific to (1 1 1) silicon;

[0072] FIGS. 7A and 7B illustrate additional designs for crystallographic selectivity in removing a sacrificial layer from underneath the releasable object and less underneath the anchoring structure;

[0073] FIG. 8 is an illustration of an example notch implemented in a tether;

[0074] FIG. 9 is a flowchart of an example method for providing ultra-thin low-cost packaged devices using (1 1 1) silicon;

[0075] FIGS. 10A through 10D illustrate a processor for making transfer-ready integrated circuits using a silicon-on-insulator wafer with a (1 1 1) handle wafer;

[0076] FIGS. 11A through 11C illustrate an example process of assembling a low-cost carrier wafer using micro-assembly techniques using elastomer stamp micro-transfer-printing to pick-up and place the thin micro devices onto another carrier wafer;

[0077] FIGS. 12A through 12C illustrate an example method for generating a touch, thin, and low-cost packaged device using the (1 1 1) system;

[0078] FIG. 13 is an illustration of an example of a substrate with released dielectric structures thereon;

[0079] FIG. 14 is an illustration of example adaptable assembly routes with wafer-level (1 1 1) silicon enabled packages;

[0080] FIG. 15 is an illustration of an example system in a package using the (1 1 1) release system;

[0081] FIG. 16 is an illustration of an example showing a releasable micro object with anchors, tethers and encapsulation;

[0082] FIG. 17 is an illustration of release and removal showing an example releasable micro object;

[0083] FIG. 18 is an illustration of crystal orientation for semiconductor devices; and

[0084] FIGS. 19 and 20 are illustrations of an example tether design.

[0085] The features and advantages of the present disclosure will become more apparent from the detailed description set forth below when taken in conjunction with the drawings, in which like reference characters identify corre-

sponding elements throughout. In the drawings, like reference numbers generally indicate identical, functionally similar, and/or structurally similar elements.

DETAILED DESCRIPTION

[0086] As used herein the expression “semiconductor element” and “semiconductor structure” are used synonymously and broadly refer to a semiconductor material, structure, device, or component of a device. Semiconductor elements include high-quality single crystalline and polycrystalline semiconductors, semiconductor materials fabricated via high-temperature processing, doped semiconductor materials, organic and inorganic semiconductors, and composite semiconductor materials and structures having one or more additional semiconductor components and/or non-semiconductor components, such as dielectric layers or materials and/or conducting layers or materials. Semiconductor elements include semiconductor devices and device components including, but not limited to, transistors, photovoltaics including solar cells, diodes, light-emitting diodes, lasers, p-n junctions, photodiodes, integrated circuits, and sensors. In addition, semiconductor element can refer to a part or portion that forms a functional semiconductor device or product.

[0087] “Semiconductor” refers to any material that is a material that is an insulator at a very low temperature, but which has an appreciable electrical conductivity at temperatures of about 300 Kelvin. The electrical characteristics of a semiconductor can be modified by the addition of impurities or dopants and controlled by the use of electrical fields. In the present description, use of the term semiconductor is intended to be consistent with use of this term in the art of microelectronics and electronic devices. Semiconductors useful in the present invention can include elemental semiconductors, such as silicon, germanium and diamond, and compound semiconductors, for example group IV compound semiconductors such as SiC and SiGe, group III-V semiconductors such as AlSb, AlAs, Aln, AlP, BN, GaSb, GaAs, GaN, GaP, InSb, InAs, InN, and InP, group III-V ternary semiconductors alloys such as AlxGal-xAs, group II-VI semiconductors such as CsSe, CdS, CdTe, ZnO, ZnSe, ZnS, and ZnTe, group I-VII semiconductors CuCl, group IV-VI semiconductors such as PbS, PbTe and SnS, layer semiconductors such as PbI₂, MoS₂ and GaSe, oxide semiconductors such as CuO and Cu₂O. The term semiconductor includes intrinsic semiconductors and extrinsic semiconductors that are doped with one or more selected materials, including semiconductor having p-type doping materials and n-type doping materials, to provide beneficial electronic properties useful for a given application or device. The term semiconductor includes composite materials comprising a mixture of semiconductors and/or dopants. Specific semiconductor materials useful for in some applications of the present invention include, but are not limited to, Si, Ge, SiC, AlP, AlAs, AlSb, GaN, GaP, GaAs, GaSb, InP, InAs, GaSb, InP, InAs, InSb, ZnO, ZnSe, ZnTe, CdS, CdSe, ZnSe, ZnTe, CdS, CdSe, CdTe, HgS, PbS, PbSe, PbTe, AlGaAs, AlInAs, AlInP, GaAsP, GaInAs, GaInP, AlGaAsSb, AlGaInP, and GaInAsP. Porous silicon semiconductor materials are useful for applications of the present invention in the field of sensors and light-emitting materials, such as light-emitting diodes (LEDs) and solid-state lasers. Impurities of semiconductor materials are atoms, elements, ions or molecules other than the semiconductor material(s) themselves or any

dopants provided in the semiconductor material. Impurities are undesirable materials present in semiconductor materials that can negatively impact the electronic properties of semiconductor materials, and include but are not limited to oxygen, carbon, and metals including heavy metals. Heavy-metal impurities include, but are not limited to, the group of elements between copper and lead on the periodic table, calcium, sodium, and all ions, compounds and/or complexes thereof

[0088] “Substrate” refers to a structure or material on which, or in which, a process is (or has been) conducted, such as patterning, assembly or integration of semiconductor elements. Substrates include, but are not limited to: (i) a structure upon which semiconductor elements are fabricated, deposited, transferred or supported (also referred to as a native substrate); (ii) a device substrate, for example an electronic device substrate; (iii) a donor substrate having elements, such as semiconductor elements, for subsequent transfer, assembly or integration; and (iv) a target substrate for receiving printable structures, such as semiconductor elements. A donor substrate can be, but is not necessarily, a native substrate.

[0089] “Destination substrate” as used herein refers to the target substrate (e.g., non-native substrate) for receiving printable structures, such as semiconductor elements. Examples of destination substrate materials include polymer, plastic, resin, polyimide, polyethylene naphthalate, polyethylene terephthalate, metal, metal foil, glass, flexible glass, a semiconductor, and sapphire.

[0090] The terms “micro” and “micro-device” as used herein refer to the descriptive size of certain devices or structures in accordance with embodiments of the invention. As used herein, the terms “micro” and “micro-device” are meant to refer to structures or devices on the scale of 0.5 to 250 μm (e.g., from 0.5 to 2 μm , 2 to 5 μm , 5 to 10 μm , 10 to 20 μm , 20 to 50 μm , 50 to 100 μm , or 100 to 250 μm). However, it is to be appreciated that embodiments of the present invention are not necessarily so limited, and that certain aspects of the embodiments can be applicable to larger or smaller size scales.

[0091] “Printable” relates to materials, structures, device components, or integrated functional devices that are capable of transfer, assembly, patterning, organizing, or integrating onto or into substrates without exposure of the substrate to high temperatures (i.e. at temperatures less than or equal to about 400, 200, or 150 degrees Celsius). In one embodiment of the present invention, printable materials, elements, device components, or devices are capable of transfer, assembly, patterning, organizing and/or integrating onto or into substrates via solution printing, micro-transfer printing, or dry transfer contact printing.

[0092] “Printable semiconductor elements” of the present invention comprise semiconductor structures that can be assembled or integrated onto substrate surfaces, for example by using dry transfer contact printing, micro-transfer printing, or solution printing methods. In one embodiment, printable semiconductor elements of the present invention are unitary single crystalline, polycrystalline or microcrystalline inorganic semiconductor structures. In the context of this description, a unitary structure is a monolithic element having features that are mechanically connected. Semiconductor elements of the present invention can be undoped or doped, can have a selected spatial distribution of dopants and can be doped with a plurality of different dopant

materials, including p- and n-type dopants. The present invention includes microstructured printable semiconductor elements having at least one cross-sectional dimension greater than or equal to about 1 micron and nanostructured printable semiconductor elements having at least one cross-sectional dimension less than or equal to about 1 micron. Printable semiconductor elements useful in many applications comprise elements derived from “top down” processing of high-purity bulk materials, such as high-purity crystalline semiconductor wafers generated using conventional high-temperature processing techniques. In one embodiment, printable semiconductor elements of the present invention comprise composite structures having a semiconductor operationally connected to at least one additional device component or structure, such as a conducting layer, dielectric layer, electrode, additional semiconductor structure, or any combination of these. In one embodiment, printable semiconductor elements of the present invention comprise stretchable semiconductor elements or heterogeneous semiconductor elements.

[0093] The term “flexible” refers to the ability of a material, structure, device or device component to be reversibly deformed into a curved shape, e.g., without undergoing a transformation that introduces significant strain, such as strain characterizing the failure point of a material, structure, device, or device component.

[0094] “Plastic” refers to any synthetic or naturally occurring material or combination of materials that can be molded or shaped, generally when heated, and hardened into a desired shape. Exemplary plastics useful in the devices and methods of the present invention include, but are not limited to, polymers, resins and cellulose derivatives. In the present description, the term plastic is intended to include composite plastic materials comprising one or more plastics with one or more additives, such as structural enhancers, fillers, fibers, plasticizers, stabilizers or additives which can provide desired chemical or physical properties. “Dielectric” and “dielectric material” are used synonymously in the present description and refer to a substance that is highly resistant to flow of electric current and can be polarized by an applied electric field. Useful dielectric materials include, but are not limited to, SiO₂, Ta₂O₅, TiO₂, ZrO₂, Y₂O₃, SiN₄, STO, BST, PLZT, PMN, and PZT.

[0095] “Polymer” refers to a molecule comprising a plurality of repeating chemical groups, typically referred to as monomers. Polymers are often characterized by high molecular masses. Polymers useable in the present invention can be organic polymers or inorganic polymers and can be in amorphous, semi-amorphous, crystalline or partially crystalline states. Polymers can comprise monomers having the same chemical composition or can comprise a plurality of monomers having different chemical compositions, such as a copolymer. Cross-linked polymers having linked monomer chains are particularly useful for some applications of the present invention. Polymers useable in the methods, devices and device components of the present invention include, but are not limited to, plastics, elastomers, thermoplastic elastomers, elastoplastics, thermostats, thermoplastics and acrylates. Exemplary polymers include, but are not limited to, acetal polymers, biodegradable polymers, cellulosic polymers, fluoropolymers, nylons, polyacrylonitrile polymers, polyamide-imide polymers, polyimides, polyarylates, polybenzimidazole, polybutylene, polycarbonate, polyesters, polyetherimide, polyethylene, polyethylene copolymers and

modified polyethylenes, polyketones, poly(methyl methacrylate), polymethylpentene, polyphenylene oxides and polyphenylene sulfides, polyphthalamide, polypropylene, polyurethanes, styrenic resins, sulphone based resins, vinyl-based resins or any combinations of these.

[0096] “Micro-transfer printing” as used herein refers to systems, methods, and techniques for the deterministic assembly of micro- and nano-materials, devices, and semiconductor elements into spatially organized, functional arrangements with two-dimensional and three-dimensional layouts. It is often difficult to pick up and place ultra-thin or small devices, however, micro-transfer printing permits the selection and application of these ultra-thin, fragile, or small devices, such as micro-LEDs, without causing damage to the devices themselves. Microstructured stamps (e.g., elastomeric, electrostatic stamps, or hybrid elastomeric/electrostatic stamps) can be used to pick up micro devices, transport the micro devices to a destination substrate, and print the micro devices onto the destination substrate.

[0097] In some embodiments, surface adhesion forces are used to control the selection and printing of these devices onto the destination substrate. This process can be performed massively in parallel. The stamps can be designed to transfer a single device or hundreds to thousands of discrete structures in a single pick-up-and-print operation. For a discussion of micro-transfer printing generally, see U.S. Pat. Nos. 7,622,367 and 8,506,867, each of which is hereby incorporated by reference in its entirety.

[0098] The disclosed technology relates generally to systems and methods for controlling the release of micro objects (devices) from a native substrate using tethers. In some embodiments, micro objects are designed or configured so that their orientation and spatial configuration are preserved when the micro objects are released from a substrate. Anchor structures that remain rigidly attached to the native substrate and tether structures that join the releasable micro object to the anchor serve to maintain the spatial configuration of the micro objects upon partial or full release of the micro object from the substrate. This can be accomplished by selective removal of a sacrificial layer (e.g., at least partially underneath the micro object) by undercutting, etching, ablation, or other means. In some embodiments, the sacrificial layer is a portion of the native substrate on which the active components are grown. This leaves each micro device supported on and connected to the native substrate by at least one anchor and at least one tether.

[0099] In some embodiments, the etching process to remove the sacrificial layer underneath the releasable micro object has a crystallographic dependence, etching faster in some directions of a crystal structure and slower in other directions of the crystal structure. Corner structures etch at different rates because of differences in the number of dangling bonds that are susceptible to different etch rates. For example, in a planar crystal structure, a crystal atom or molecule that is normally connected to four neighbors will only be connected to two neighbors at a convex corner but will be connected to three neighbors at a concave corner. A crystal atom normally connected to eight neighbors will only be connected to three neighbors at a convex corner but will be connected to seven neighbors at a concave corner. Therefore, convex or exterior corners of structures made of the sacrificial layer etch relatively quickly, progressively etching and producing etch fronts parallel to the fast etching planes in the crystal. Concave or internal corners of the

structures made of the sacrificial layer have fewer susceptible dangling bonds, and etch more slowly, forming a slowly moving or pinned/stopped etch front defined by the slowly etching planes, provided that the resulting etch fronts of the etchants can form and maintain a local shape characterized by the internal/concave corners. Some release layers (also referred to as a sacrificial layer) that exhibit this kind of crystallographic selectivity include Si (1 1 1), InAlP, InP, GaAs, InGaAs, AlGaAs, GaSb, GaAlSb, AlSb, InSb, InGaAlSbAs, InAlSb, and InGaP.

[0100] It is often convenient to provide a sacrificial layer that at least temporarily spans the entire area of the first substrate, both in the regions used to form releasable micro objects and in the regions used to form anchoring structures. In those applications, anchoring designs can be used in which the anchor forms a continuous structure, spanning more than one releasable micro object in at least one dimension or designs in which the anchor is positioned about the releasable micro objects. In some embodiments, the anchoring structures are designed with locally concave or internal corners and the releasable micro objects are designed with convex/external corners. In some embodiments, the sacrificial material removal etch progresses rapidly under the releasable micro object (e.g., relative to the rate at which the anchor structure is formed) These designs can be further benefited by tether designs that include fewer locally concave or internal corners, for example, by having a narrow shape that is narrower than the anchor structure to which the tether is attached. In some embodiments, narrow tethers means tethers with a width of 1 μm to 100 μm , 1 μm to 5 μm , 5 μm to 10 μm , 10 μm to 15 μm , 15 μm to 20 μm , or 20 μm to 40 μm . In some embodiments, the width of narrow tethers is 1 μm to 50 μm or 5 μm to 10 μm .

[0101] FIG. 1 is an illustration of an example native substrate 102 with micro devices (e.g., 106a, 106b, and 106c) formed in an active layer 106 thereon. The native substrate 102 will vary depending on the type of micro devices formed thereon. Example native substrates include semiconductor materials (e.g., an amorphous, polycrystalline, microcrystalline, or crystalline semiconductor), metal, polymer, or glass. The active layer 106 (including the active components 106a-106d) can include a semiconductor, such as crystalline Si, GaAs, GaN, or a III-V compound semiconductor.

[0102] A sacrificial layer 104 is formed on the native substrate 102. Active components 106 can be formed in the active layer 106 formed on the sacrificial layer 104. The active components 106a-106d are distributed over the native substrate 102 and are spatially separated from each other by anchors 108a-108b (collectively anchors 108). The anchors 108 are physically connected or secured to the native substrate 102 by portions of the sacrificial layer 104a, 104b. The active components 106a-106d are suspended above the native substrate 102 by tethers 110a-110d (collectively tethers 110) that physically secure each active component 106a-106d to one or more anchors 108. In some embodiments, a single anchor or tether (not shown) is used to secure each active component 106a-106d to the substrate 102. The tethers 110 and anchors 108 can be at least in part electrically conductive thereby electrically connecting each active component 106a-106d to one or more tethers 110 or anchors 108. In some embodiments, electrically functional anchors 108 include passive electrical elements such as electrical

conductors, resistors, capacitors, or contact pads, or active components such as transistors and capacitors.

[0103] The anchors 108 are connected to the substrate layer 102 by the sacrificial layer 104 beneath the electrically functional anchors 108. The sacrificial layer 104, in some embodiments, is absent in the areas 112a-112c (collectively 112) below the active components 106a-106d, thereby isolating the active components 106a-106d from the anchors 108. In some embodiments, the sacrificial layer 104 is absent in areas 112 below the active components 106a-106d after an etching process has been performed to remove the sacrificial layer 104 from those areas. For example, in some embodiments, transferable semiconductor structures are grown on a native substrate material, such as Si (1 1 1). The structures can be released by undercut etching the substrate materials or a sacrificial material formed between the native substrate material and the transferable semiconductor structures.

[0104] In some embodiments, the tethers 110 or anchors 108 are heterogeneous such that they are made of a material other than the base substrate material (e.g., a material other than the semiconductor material that forms the native substrate). For example, the tethers 110 or anchors 108 can be crystalline, polycrystalline, amorphous, or ductile.

[0105] The sacrificial layer 104 can be an oxide, such as silicon dioxide. The tethers 110 can include metal, semiconductors, or doped semiconductors, and/or metal layers thereby providing electrical conductivity between the anchors 108 and the printable active components 106a-106d. The tethers 110 or anchors 108 can include non-conductive dielectrics or resins.

[0106] FIG. 2 illustrates the process of undercut etching the sacrificial layer over time. The dotted lines in FIG. 2 indicate the extent of the etchant beneath the semiconductor device 202 (corresponding to the active components 106a-106d). The semiconductor device 202 is shown at $t=0$ before the etching process to release the semiconductor structure 202 has begun.

[0107] In some embodiments, anchor structures 108 are formed perpendicular to the (1 2 2) family of directions of crystalline silicon 111. In some embodiments, the anchor structures 108 form structures that are at least twice as wide as the device 202 to be released. The anchor structures 108, in some embodiments, encircle the device 202 structure to be released so that the anchor structures 108 are not released by the undercut etch. In some embodiments, orientation of the sacrificial layer 104 is selected to allow the undercut etch progression to occur according to FIG. 2, as shown from $t=0$ to $t=6$ with a vertical fast-etch direction corresponding to the progression of the dotted-line etch front under the device 202. In some embodiments, the sacrificial layer 104 is of sufficient thickness to allow the etchant to flow within the sacrificial layer 104 once the sacrificial material is removed.

[0108] In some embodiments, the device 202 structure to be released holds residual stress, for example due to epitaxial growth of active materials (e.g. active layer 106) or buffers. Upon release by undercut etching, the device 202 structure can partially or fully relax, deform, or move and therefore apply additional stress on the portions of the structure still attached to the substrate (e.g., the tethers 204 corresponding to the tethers 110 of FIG. 1). In some embodiments, if the stress applied to the tethers 204 is great enough to fracture the tethers 204, then the device 202 structure can be prematurely lost in the release chemistry before the micro

devices **202** are employed in the micro-printing process (e.g., picked up by a conformable transfer element).

[0109] FIG. 3 is an illustration of the process of undercut etching a transferable semiconductor **302** (corresponding to the active components **106a-106d**) with a single tether **304** (corresponding to a tether **110** of FIG. 1). Undercut etch progression beneath the semiconductor devices **302** occurs according to the progression shown in FIG. 3 with the dotted lines. In some embodiments, the device **302** structure to be released holds residual stress, for example, due to epitaxial growth of active materials (e.g. active layer **106**) or buffers. Upon release by undercut etching, the device **302** structure can partially or fully relax, deform, or move, and therefore apply additional stress on the portions of the structure still attached to the substrate (e.g., tether **304** corresponding to the tethers **110** of FIG. 1). If the device **302** structure is held by a single tether **304** located at the center point of an anchor-facing edge device **302** structure, the undercut completes along a line at the center of the structure, and free expansion or contraction of the non-tethered edge can accommodate the deformation that occurs upon release without applying stress to the tether **304**.

[0110] FIG. 4 is an illustration of the process of undercut etching a transferable semiconductor device **402** (corresponding to the active components **106a-106d**) with a single tether **404** (corresponding to the tethers **110** of FIG. 1) placed off-center relative to the edge of the device **402**, for example by at least 5%, 10%, 20%, 50% or more. In some embodiments, the single tether **404** of a releasable structure, for example, on Si (1 1 1), is placed off-center **406** with respect to the edge of the device **402** on the anchor-facing edge **408** e.g., the tether **404** is not located at the mid-point or along a center line of the device **402**. The undercut etch progression reaches completion with the areas **410** near the tether **404** releasing last. In this configuration, the design offers, among other things, added surety that the relaxation of residual stress in the releasable structure is accommodated by free expansion/contraction of the non-tethered edges and does not break the tether **404** and cause yield loss during the release process. Off-center tethers **404**, in some embodiments, are more likely to finish with less unreleased regions under a device **402** (e.g., perfectly or near perfectly). As shown in the illustrations in FIG. 4, there is no arrest (stopping) of the etch planes due to the location of the tether **404** in an off-center position.

[0111] FIGS. 5A-B are illustrations of an example structure with four tethers **502A-502D** (collectively tethers **502** corresponding to the tethers **110** of FIG. 1) per releasable structure **504** (corresponding to the active components **106a-106d**). In some embodiments of producing releasable structures **504** on substrates **102** (shown in FIG. 1), such as Si (1 1 1), tethers **502A-D** are off-center and are placed at locations on the perimeter of the chip **504** to arrest the etch front **506** by producing concave vertices at the intersection of the slow-etching planes before the structure is released. In some embodiments, pinning from the slow-etching plane is avoided.

[0112] In some embodiments, the tethers **502** are designed (e.g., in their placement) such that they do not support concave vertices at the intersection of slow-etching planes, thereby avoiding the arrest of the etch front. Such tethers **502** can, for example, have an aspect ratio of 1.732, for example, for (1 1 1) Silicon. In some embodiments, the aspect ratio is from 1.3 to 1.5, 1.5 to 1.7, 1.7 to 1.9, or 1.9

to 2.1. In some embodiments, the critical aspect ratio of the tether **502** is dependent on the crystal orientation of the etched material. The critical aspect ratio can be determined empirically by etching tethers of different aspect ratios to determine a useful aspect ratio or calculated by comparing the etch rates in the different directions under the preferred etch conditions.

[0113] FIGS. 6A and 6B are example illustrations of tethers specific to (1 1 1) Silicon. FIG. 18 is a prior-art illustration of crystal orientation for semiconductor devices. The aspect ratio of a tether **602** (corresponding to the tethers **110** of FIG. 1) can be set to avoid pinning from slow-etching planes. Different crystals can have different critical aspect ratios. The tethers **602** shown in FIG. 6A and 6B have two different aspect ratios since the width of the tether **602** in FIG. 6A is less than the width of the tether **602** in FIG. 6B and the aspect ratio is defined by dividing the width by the height of the tether **602**. The tether **602** shown in FIG. 6A has an aspect ratio less than 1.732, and the tether shown in FIG. 6B has an aspect ratio greater than 1.732, respectively. As shown in FIG. 6A, a tether **602** with an aspect ratio less than 1.732 can form vertices (the facing corners of the triangles delineated by dotted lines) that arrest the undercut. In contrast, as shown in FIG. 6B, a tether **604** with an aspect ratio greater than 1.732 does not arrest undercut.

[0114] FIGS. 7A and 7B illustrate additional designs for crystallographic selectivity in removing a sacrificial layer **702a** and **702b** (collectively **702**) from underneath the releasable objects **704a-704d** (collectively **704** and e.g., such as active components **106a-106d** of FIG. 1) while reducing the amount of the sacrificial layer **702** removed from underneath the anchoring structure. In micro assembly, in certain embodiments, it is useful to release micro objects **704a-704d** delineated, for example, by trenches **706a-706d** (collectively **706**) from a first substrate while preserving their orientation and spatial configuration until they are selected (e.g., picked up) by a conformable transfer element, such as an elastomer stamp.

[0115] Anchor structures that remain rigidly attached to the first substrate and tether structures **708a-708h** (collectively **708**) that join the releasable micro object to the anchor can serve to maintain the spatial configuration of the micro objects upon the partial or full release of the micro objects **704** from the first substrate. For example, this can be accomplished by the selective removal of a sacrificial layer **702** by etching or ablation or other means. In this example, object **704a** is secured to an anchor structure with a single tether **708a**, object **704b** is secured to an anchor structure with two tethers **708b** and **708c**, object **704c** is secured to an anchor structure with four tethers **708d**, **708e**, **708f**, and **708g**, and object **704d** is secured to an anchor structure with two tethers **708h** and **708i**. In some embodiments, each object **704** on a native-substrate is secured with the same number of tethers.

[0116] In some embodiments, the etching process to remove the sacrificial layer underneath the releasable micro object has crystallographic dependence in which etching occurs faster in some directions of the crystal structure and slower in other directions of the crystal structure. In those cases, convex or exterior corners of structures (e.g., of the sacrificial layer) etch quicker to progressively produce etch fronts that are parallel to the fast etching planes, as described above. In such instances, concave or internal corners of the structures (e.g., of the sacrificial layer) etch slower, thereby

forming a slowly moving or pinned/stopped etch front, which is defined by the slowly etching planes (provided that the resulting etch fronts of the etchants can form and maintain a local shape characterized by the internal/concave corners). Certain release layers (e.g., sacrificial layer) having crystallographic dependence that exhibit this kind of crystallographic selectivity include Si (1 1 1), InAlP, InP, GaAs, InGaAs, AlGaAs, GaSb, GaAlSb, AlSb, InSb, InGaAlSbAs, InAlSb, and InGaP.

[0117] To address this effect, in some embodiments, a sacrificial layer is provided that at least temporarily spans the entire area of the first substrate, both in the regions used to form releasable micro objects and in the regions used to form anchoring structures. In addition, in those applications, a continuous structure, spanning more than one releasable micro object in at least one dimension is employed. Alternatively, in some embodiments, the anchor is positioned about the releasable micro objects.

[0118] In such embodiments, the anchoring structure is characterized by locally concave or internal corners and the releasable micro objects are characterized locally by convex or external corners. In such configurations, the etch progresses rapidly (e.g., relative to the rate at which the anchoring structures are released) under the releasable micro object.

[0119] In some embodiments, the tethers are designed to not support the establishment of locally-concave or internal corners. In such embodiments, the tethers are configured, for example, with a narrow shape (e.g., a width of from 10 nm to 100 nm, 100 nm to 500 nm, 500 nm to 1 micron, or 1 micron to 10 microns).

[0120] To promote a controlled release of the printable micro devices from the fabrication substrate, the tether can be shaped to provide a consistent point of separation. FIG. 8 is an illustration of an example notch 802 implemented in a tether 804 corresponding to the tethers 110 of FIG. 1. Notches 802 in tethering structures can be used to facilitate controlling the point of fracture when a released micro object is retrieved by a transfer element such as a structured elastomer stamp. The width of the notch 802 can be used to control the force required to fracture a tether 804 when a released micro object (e.g., partially released) is removed by a transfer element.

[0121] In another aspect of the disclosure, the disclosed technology enables the fabrication and manufacturing of ultra-thin low-cost packaged micro-scale devices using (1 1 1) silicon. FIG. 9 is a flowchart of an example method 900 for providing ultra-thin low-cost packaged micro-scale devices using (1 1 1) silicon. Transfer-ready micro-scale devices, such as micro-scale integrated circuits or LEDs, are first fabricated (step 902). The micro-scale devices are assembled, for example, onto a (1 1 1) silicon wafer with a dielectric layer (step 904). In some embodiments, other types of wafers can be used as a destination substrate for the micro devices, for example glass, plastic, or metal. In some embodiments, thin-film metallization processes can be used to interconnect the assembled micro devices with other functional elements (step 906). The assembled micro-scale devices and metallization layer can be fully embedded within a dielectric layer (step 908). The dielectric layer can be patterned (step 910) and the packaged micro-scale devices can be released from the underlying wafer (step 912) and transferred to another substrate. Various processes can

be used to release the micro-scale devices from the underlying wafer such as those disclosed herein (e.g., see above).

[0122] FIGS. 10A through 10D illustrate a process for making transfer-ready integrated circuits using a silicon-on-insulator wafer. In some embodiments, a (1 1 1) handle wafer is employed. As shown in FIG. 10A, the source substrate, in this example, is a silicon-on-insulator wafer 1002. In some embodiments, other types of wafers such as semiconductor or metal wafers can be used. The starting wafer includes a handle wafer with (1 1 1) orientation. A buried oxide layer 1004 (e.g., 1 μ m thick) is directly on a top surface of the source substrate 1006. A device silicon layer 1008 is provided directly on the top surface of the buried oxide layer 1004.

[0123] As shown in FIG. 10B, one or more integrated circuits 1010 (collectively devices 1010) are fabricated (directly or indirectly) on the device silicon layer 1008. The device silicon layer 1008 can be thick enough to behave like bulk silicon, can be partially depleted, or can be fully depleted and can have, for example, a thickness of less than a micron, one micron, or a few microns (e.g. 2 microns), 10 microns, 50 microns, 100 microns, or 1000 microns. The process can include providing multiple wiring levels. In some embodiments, a terminal inorganic dielectric passivation layer is provided such that none of the wiring metallization of device silicon is exposed.

[0124] As shown in FIG. 10C, the micro device is defined by patterning and etching trenches 1014 through the dielectric layers around the perimeter of the device 1010. The device silicon layer is also patterned. If there is device silicon exposed at the perimeter of the device, an inorganic dielectric layer can be deposited to passivate this exposed silicon. The passivation layer is then patterned forming inorganic dielectric portions 1012a, 1012b, and 1012c. In some embodiments, the silicon is etched to an appropriate depth 1016 to release the device 1010 (FIG. 10D). As shown in FIG. 10D, the device 1010 is released from the source substrate 1006 by undercutting a sacrificial layer 1018 using techniques such as those disclosed herein (e.g., as described above). After performing the undercutting process, the devices 1010 are held in place by anchors and/or tethers (not shown in FIG. 10D) as described above.

[0125] FIGS. 11A through 11C illustrate an example process of assembling a low-cost carrier wafer using micro-assembly techniques using elastomer-stamp micro-transfer-printing to pick up and place the thin micro-scale devices onto another carrier wafer. FIG. 11A illustrates a transfer-stamp 1102 as it approaches one or more transfer-ready micro-scale devices (e.g. integrated circuits) 1010 on a source wafer 1006. FIG. 11B illustrates the transfer-stamp 1102 picking up the devices 1010 from the source wafer 1006. The devices 1010 are transferred to a low-cost carrier wafer 1112 as shown in FIG. 11C. In some embodiments, a layer 1106 is formed on the carrier wafer 1112, such as an insulation layer or polymer layer (e.g., a tacky polymer layer). Example transfer techniques are described in U.S. Pat. Nos. 7,622,367, 7,943,491, and 8,506,867, each of which is hereby incorporated by reference.

[0126] FIGS. 12A through 12C illustrate an example method for generating thin and low-cost packaged micro-scale devices using the (1 1 1) system. As shown in FIG. 12A, micro-scale devices 1010a and 1010b (collectively 1010) are assembled onto the carrier wafer 1112 using micro assembly techniques. The carrier wafer 1112, in some

embodiments, is (1 1 1) oriented silicon and includes a dielectric layer **1206**. The dielectric layer **1206** can be organic (e.g., polyimide) or inorganic (e.g., silicon dioxide). In some embodiments, the assembled micro-scale devices **1010** are embedded within a second layer **1202** of dielectric as shown in FIG. **12B**. This second embedding dielectric **1202** can be organic (e.g., a spin coated polyimide) or can be a deposited inorganic material. Referring to FIG. **12C**, the dielectric layers **1202** and **1206** can be then patterned in a manner that defines the desired micro-scale device packages **1204a** and **1204b** that each include a micro-scale device **1010** and also defines the anchors **108a-108b** and tethers **110a-110d** (as described above). In some embodiments, the micro-scale device **1010** packages are then released from the wafer **1112** using the undercut removal process as described above, for example. The resulting wafer-level thin and low-cost micro-scale device **1010** packages are suitable for transfer to other substrates using, for example, vacuum collets. In some embodiments, pad structures are formed on top or bottom surfaces of the embedded micro-scale devices **1010**, thereby forming a surface-mountable device.

[**0127**] FIG. **13** is an illustration of an example destination substrate with micro-scale devices printed into a structure. The destination substrate can be made of an inorganic material, such as silicon dioxide, glass, or a metal. Printed micro-scale devices can be embedded within the structures as shown in FIG. **13**.

[**0128**] FIG. **14** is an illustration of example adaptable assembly processes with wafer-level (1 1 1) silicon-enabled packages. Micro-scale devices on a packaged wafer **1402** can be transfer printed to a tape-and-reel **1404**. The tape-and-reel **1404** can be provided to a tape-fed high-speed chip shooter **1406** for assembly. The tape-fed high-speed chip shooter **1406** can package the micro-scale devices on the tape-and-reel **1404** as, for example, a package-in-package molded package **1408** or a package-on-lead-frame that is subsequently molded into a package **1410**.

[**0129**] In some embodiments, the package wafer **1402** is provided to a wafer-fed die-attach tool **1412**. The wafer-fed die-attach tool **1412** can package the micro-scale devices into wafer-level-packages **1402**. The wafer-fed die-attach tool **1412** can package the micro-scale devices on package-on-lead frames that are subsequently molded into a package **1410**. The wafer-fed die attach tool **1412** can package the micro-scale devices into package-in-package devices **1408** or into a wafer-level package (WLP) **1414**.

[**0130**] In some embodiments, the package wafer is provided to a wafer-fed micro-transfer printer **1416** which packages the micro-scale devices in wafer-level-packages **1414**. FIG. **15** is an illustration of an example system **1504** in a package using the (1 1 1) release system. The illustrated example device **150** can include a small integrated circuit **1514** that is interconnected with two different types of sensors **1508**, **1510** and also interconnected with an antenna **1512** made using a common wafer-level metallization. This system can be entirely embedded in a dielectric material and can be released from the underlying (1 1 1) wafer as described above. The device **1504** can be coupled to anchors **1506a** and **1506b** by tethers **1502a-1502d**. This provides a small package that can be assembled onto other substrates using, for example, micro-assembly techniques.

[**0131**] In another aspect of the disclosure, the anchor **108** and tether **110** are formed of a single polymer layer. The polymer layer further serves as protection for the fabricated

micro-scale devices by encapsulating the micro-scale devices after they are fabricated on the native substrate and during the micro-printing process. To this end, the encapsulation serves to protect any chemical-sensitive layers within fabricated micro devices. The encapsulating polymer layer, for example, provides electrical insulation and protection from contaminants, moisture, and oxidizers. The encapsulating polymer layer further allows for electrically contactable structures to be employed on the bottom side, top side, or lateral side of a printable object.

[**0132**] The polymer layer, in some embodiments, can be made of a photoresist or photo-sensitive material with sufficient stiffness to maintain the spatial configurations of printable structures during a release process. The polymer that forms the anchor, tether, or encapsulation of the micro-scale device can also be selectively removed from the printable objects and the target substrate after transfer by dissolution, etching or other processes. The polymer can have sufficient adhesion to serve as a contact interface with a transfer element of the micro-printing system so that it can be picked up from a native substrate and can be treated to serve as an interface for separation between the transfer element and the micro-scale devices once the micro-scale devices have been transferred to a destination substrate.

[**0133**] In some embodiments, the single polymer layer improves the density of the printable, micro devices for a given wafer. The supporting, non-printable structures (e.g., the anchor and tether) can be fabricated such that the distance between adjacent printable structures is miniaturized, for example less than 500 microns, less than 100 microns, less than 50 microns, less than 25 microns, or less than 10 microns.

[**0134**] FIG. **16** illustrates an embodiment of a releasable micro object **106** comprising anchors **108**, tethers (not shown) and encapsulating layer **1602** formed of a single polymer layer **1601**. As shown in the figure, the releasable micro object **106** is a printable active component having an emitter **1604**, a collector **1606**, a sub-collector **1608**, and electrical pads **1610**. The releasable micro object **106** is fabricated over a sacrificial layer **104**, referred to in the figure as a release layer.

[**0135**] The polymer layer **1601** is applied over the releasable micro object **106** and over the native source substrate **102**. As shown, the polymer layer **1601** encapsulates the exposed top and side regions of the micro object **106**. The polymer layer **1601** also encapsulates a portion of the sacrificial layer **104**.

[**0136**] To separate the releasable micro objects **106** from the native substrate **102**, the polymer layer **1601** is treated to form the anchor structure **108** on the source substrate **102** and the tether structure **110** (not shown). As illustrated in the figure, the anchor structures **108** are formed over the native substrate **102** (or a substantial portion thereof) to remain rigidly attached to the substrate **102** as the sacrificial material within the sacrificial layer **104** is fully or partially removed. The tether **110** (not shown) connects the anchor structure **108** to the printable micro object **106** and the encapsulating layer **1602** of the polymer layer **1601**. The treatment, in some embodiments, also forms ports of ingress (not shown in FIG. **16**) in the polymer layer **1601** that exposes a portion of the sacrificial layer **104**. The ports of ingress **1612** (FIG. **17**) allows access to the sacrificial layer **104** to, for example, perform the undercutting removal process (e.g., by chemical etching).

[0137] In some embodiments, the treatment includes forming a photo-sensitive layer (as the polymer layer) on the releasable micro objects 106, then selectively exposing portions of the photo-sensitive layer to an energized beam (e.g., electromagnetic-radiation beam or electron beam) to alter solubility of the photo-sensitive layer to a photoresist developer. The photo-sensitive layer (or the entire device) can be exposed to heat to solidify the photo-sensitive layer. Subsequently, the portions of the photo-sensitive layer (e.g., soluble or insoluble to the photoresist developer) are then removed to define breakable tethers.

[0138] Photodefinable materials (such as photoresists or cross-linkable resins) can be used for making anchoring, tethering, or encapsulating structures, offering ease of formation, and in many cases ease of removal by dissolution in wet chemicals, organic solvents, or aqueous mixtures, or by ashing in oxygen and/or fluorine compounds.

[0139] The undercutting removal process can employ chemical reactants to etch the sacrificial layer 104 (shown as the release layer in FIG. 16), gaining access through ports of ingress formed in the anchoring, tethering, and/or encapsulation structures. Etch reaction products can exit the space under the releasable micro objects through ports of egress. In some embodiments, the ports of egress are the same as the ports of ingress (e.g., 1612 in FIG. 17). When the release layer is fully or partially removed, the releasable micro object is said to be at least partially released and ready for removal by a transfer element. The transfer element contacts and adheres to the partially released object. In some embodiments, it is advantageous for the transfer element to be conformable to make intimate contact with at least a portion of the topography of the releasable object. For example, the transfer element can include a conformable material, such as PDMS.

[0140] FIG. 17 is an illustration of release and removal of example releasable micro objects 106. As shown, the releasable micro objects 106 are in contact with a transferring element 1702. In some embodiments multiple posts 1704 contact the releasable micro object 106. In other embodiments a single post contacts a releasable micro object 106. After adhering to the released object 106, the transferring element 1702 moves away from the native substrate 102 while maintaining adhesion to the released micro object 106, thereby retrieving, removing, separating, or picking the object 106 from its native substrate 102. In the process of removal, the anchor 108 or tether 110 structures fracture or otherwise lose connection to the native substrate 102 or the released object 106. In some embodiments, the tether 110 fractures upon contact by the transferring element 1702. In certain embodiments, the tether 110 fractures when the transferring element 1702 pulls the micro object 106 from the native substrate 102.

[0141] Materials selected for specific fracture properties, adhesion properties, or definition of geometries with stress concentration features in the anchoring and tethering structures are beneficial for controlling the points of separation or fracture. In some embodiments, the tether 110 is formed of a narrow structure (or shaped with a notch in certain embodiments) to provide a point of fracture and allow the printable micro object 106 to separate from the native structure 102. As noted above, tethers 110 can be made of organic materials, such as polymers, or inorganic materials such as silicon, silicon dioxide, or silicon nitride.

[0142] Referring still to FIG. 17, the polymer layer 1601, in particular, the encapsulation region 1602, serves as the point of contact with the transferring element 1702. In other embodiments, the transferring element 1702 contacts the micro object 106 itself.

[0143] As illustrated in FIG. 19, in one embodiment, a tether design includes tethers 1902 that are oriented in such a way that the slow-etching planes are not allowed to arrest the lateral undercut. The tethers 1902 separate the trenches 1908 and connected to the chipset 1904 and anchors 1906. A key parameter, as illustrated in FIG. 20 is to ensure that $d > 0$ so that the tether 1902 is angled. Such a design is useful, for example with InAlP release layers.

[0144] In some embodiments, the transferring element 1702 includes one or more posts, for example, organized in an array, to make contact with a given printable micro object 106. In certain embodiments, the transferring element 1702 forms a single surface to make contact with the polymer layer 1601.

[0145] In view of the structure, functions and apparatus of the systems and methods described here, in some embodiments, a system and method for providing micro-scale devices are provided. Having described certain embodiments of methods and apparatus for providing micro-scale devices, it will now become apparent to one of skill in the art that other embodiments incorporating the concepts of the disclosure can be used. Therefore, the disclosure should not be limited to certain embodiments, but rather should be limited only by the spirit and scope of the following claims.

[0146] Throughout the description, where apparatus and systems are described as having, including, or comprising specific components, or where processes and methods are described as having, including, or comprising specific steps, it is contemplated that, additionally, there are apparatus, and systems of the disclosed technology that consist essentially of, or consist of, the recited components, and that there are processes and methods according to the disclosed technology that consist essentially of, or consist of, the recited processing steps.

[0147] It should be understood that the order of steps or order for performing certain action is immaterial so long as the disclosed technology remains operable. Moreover, two or more steps or actions can be conducted simultaneously.

1-29. (canceled)

30. A method of fabricating a plurality of transferable micro objects, comprising:

forming a sacrificial layer comprising sacrificial material on a process side of a source substrate;

forming a plurality of releasable micro objects at least in part on the sacrificial layer;

applying a polymer layer over the plurality of releasable micro objects and at least a portion of the source substrate, wherein the polymer layer encapsulates the plurality of releasable micro objects;

treating the polymer layer to form:

(i) a plurality of anchor structures on the source substrate for the plurality of transferable micro objects,

(ii) at least one tether between each transferable micro object and a pre-determined anchor structure of the plurality of anchor structures, and

(iii) for each of the releasable micro objects, a port of ingress in the polymer layer to a portion of the sacrificial layer underneath a respective transferable micro object; and

removing at least a portion of the sacrificial layer underneath the plurality of releasable micro objects.

31. The method of claim 30, wherein the one or more anchor structures remains rigidly attached to the substrate when the transferable micro object is moved.

32. The method of claim 30, wherein at least a portion of the sacrificial layer underneath the plurality of releasable micro objects causes each of the plurality of releasable micro objects to move and apply stress on a respective subset of the plurality of tethers.

33. The method of claim 32, wherein the respective subset of the plurality of tethers comprises a single tether.

34. The method of claim 30, comprising transferring the releasable micro objects and removing at least a portion of the polymer layer from the micro objects.

35. The method of claim 34, wherein removing at least a portion of the polymer from the micro objects comprises at least one of dissolution, etching, and ashing of the polymer layer.

36. The method of claim 30, comprising transferring the releasable micro objects by contacting at least a portion of a printing stamp to a corresponding portion of the polymer.

37-52. (canceled)

53. A source substrate and plurality of transferable micro objects, comprising:

a source substrate having a process side;

a sacrificial layer comprising sacrificial material on the process side of the source substrate;

a plurality of releasable micro objects formed at least in part on the sacrificial layer;

a polymer layer applied over the plurality of releasable micro objects and at least a portion of the source substrate, wherein the polymer layer encapsulates the plurality of releasable micro objects,

wherein the polymer layer has been treated such that the polymer layer comprises:

(i) a plurality of anchor structures on the source substrate for the plurality of transferable micro objects,

(ii) at least one tether between each transferable micro object and a pre-determined anchor structure of the plurality of anchor structures, and

(iii) for each of the releasable micro objects, a port of ingress in the polymer layer to a portion of the sacrificial layer underneath a respective transferable micro object.

54. The source substrate and plurality of transferable micro objects of claim 53, wherein the sacrificial layer underneath the plurality of releasable micro objects defines a gap between the source substrate and each of the plurality of releasable micro objects.

55. The source substrate and plurality of transferable micro objects of claim 54, wherein the one or more anchor structures remains rigidly attached to the source substrate when the releasable micro object is moved.

56. The source substrate and plurality of transferable micro objects of claim 53, wherein at least a portion of the

sacrificial layer underneath the plurality of releasable micro objects causes each of the plurality of releasable micro objects to move and apply stress on a respective subset of the plurality of tethers.

57. The source substrate and plurality of transferable micro objects of claim 56, wherein the respective subset of the plurality of tethers comprises a single tether.

58. The source substrate and plurality of transferable micro objects of claim 53, wherein the at least one tether has a narrow shape with a width of 10 μm to 40 μm , thereby inhibiting the formation of locally-concave or internal corners.

59. The source substrate and plurality of transferable micro objects of claim 53, wherein the sacrificial layer has an anisotropic crystal structure.

60. The source substrate and plurality of transferable micro objects of claim 53, wherein each tether of the plurality of tethers comprises one or more notches, the notch providing a point of fracture for a releasable micro object when the releasable micro object is moved.

61. The source substrate and plurality of transferable micro objects of claim 53, wherein the source substrate is a material selected from the group consisting of Silicon (1 1 1), silicon, indium phosphide, gallium arsenide, and sapphire.

62. The source substrate and plurality of transferable micro objects of claim 53, wherein the each of the plurality of tethers has an aspect ratio of less than 1.732.

63. The source substrate and plurality of transferable micro objects of claim 53, wherein the tether is sized and shaped to break when a corresponding micro object is contacted by an elastomer stamp for micro transfer printing from the source substrate to a target substrate, different from the source substrate.

64. The source substrate and plurality of transferable micro objects of claim 53, wherein the sacrificial material is a portion of the source substrate or wherein the sacrificial material comprises a material selected from the group consisting of Silicon (1 1 1), InAlP, InP, GaAs, InGaAs, AlGaAs, GaSb, GaAlSb, AlSb, InSb, InGaAlSbAs, InAlSb, and InGaP.

65. The source substrate and plurality of transferable micro objects of claim 53, wherein the anchor structure forms a continuous structure, spanning more than one releasable micro object of the plurality of releasable micro objects in at least one dimension or wherein each of the plurality of anchors are characterized by locally concave or internal corners and each of the plurality of releasable micro objects is locally characterized by convex or external corners.

66. The source substrate and plurality of transferable micro objects of claim 53, wherein each of the tethers has an aspect ratio of greater than 1.732.

* * * * *

专利名称(译)	用于控制可转移半导体结构的释放的系统和方法		
公开(公告)号	US20180204772A1	公开(公告)日	2018-07-19
申请号	US15/910809	申请日	2018-03-02
[标]申请(专利权)人(译)	艾克斯瑟乐普林特有限公司		
申请(专利权)人(译)	的X CELEPRINT有限公司		
当前申请(专利权)人(译)	的X CELEPRINT有限公司		
[标]发明人	BOWER CHRISTOPHER MEITL MATTHEW		
发明人	BOWER, CHRISTOPHER MEITL, MATTHEW		
IPC分类号	H01L21/78		
CPC分类号	H01L21/7813 B81C99/008 H01L21/561 H01L21/568 H01L21/6835 H01L24/83 H01L2221/68368 H01L21/6836		
优先权	62/029535 2014-07-27 US 62/014078 2014-06-18 US		
其他公开文献	US10347535		
外部链接	Espacenet USPTO		

摘要(译)

所公开的技术一般涉及用于控制微型器件的释放的方法和系统。在将微型器件转移到目标衬底之前，在其上形成具有微型器件的原生衬底。微型器件可以分布在天然衬底上并且通过锚结构在空间上彼此分离。锚固物连接/固定到天然基底。系绳将每个微型装置物理地固定到一个或多个锚固件上，从而将微型装置悬挂在原生基板上。在某些实施例中，单系绳设计用于控制衬底（例如Si（111））上的可释放结构中的内建应力的松弛。单链系统设计提供了在微装配过程中从原生基底取回时更容易破裂的附加益处。在某些实施例中，窄系绳设计用于避免底切蚀刻前沿的钉扎。

