

(19)



(11)

EP 2 970 318 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention of the grant of the patent:
21.11.2018 Bulletin 2018/47

(51) Int Cl.:
A61K 49/00 (2006.01) **C07D 487/22** (2006.01)
G01N 21/64 (2006.01) **C09K 11/06** (2006.01)
G01N 33/497 (2006.01) **A61B 5/00** (2006.01)

(21) Application number: **14775010.3**

(86) International application number:
PCT/US2014/026183

(22) Date of filing: **13.03.2014**

(87) International publication number:
WO 2014/160258 (02.10.2014 Gazette 2014/40)

(54) OXYGEN SENSORS COMPRISING A POLYMER AND A LUMINESCENT DYE

SAUERSTOFFSENSOREN MIT EINEM POLYMER UND EINEM LUMINESZENZFARBSTOFF
 CAPTEURS D'OXYGÈNE COMPRENANT UN POLYMÈRE ET UN COLORANT LUMINESCENT

(84) Designated Contracting States:
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

US-A- 5 487 885 US-A- 5 837 865
US-A1- 2007 110 672 US-A1- 2008 311 304
US-A1- 2010 303 772 US-A1- 2012 165 435
US-A1- 2012 265 034 US-A1- 2012 265 034
US-A1- 2013 004 785 US-A1- 2013 041 200
US-B1- 6 274 086 US-B1- 6 362 175

(30) Priority: **14.03.2013 US 201361784925 P**

(43) Date of publication of application:
20.01.2016 Bulletin 2016/03

(60) Divisional application:
18200504.1

(73) Proprietor: **Profusa, Inc.**
South San Francisco, CA 94080 (US)

(72) Inventors:
 • **GAMSEY, Soya**
South San Francisco, CA 94080 (US)
 • **WISNIEWSKI, Natalie**
South San Francisco, CA 94080 (US)
 • **HELTON, Kristen**
South San Francisco, CA 94080 (US)
 • **MCMILLAN, William**
South San Francisco, CA 94080 (US)

(74) Representative: **Gill Jennings & Every LLP**
The Broadgate Tower
20 Primrose Street
London EC2A 2ES (GB)

(56) References cited:
EP-A2- 0 352 610 WO-A1-2012/027593
US-A- 5 242 835 US-A- 5 371 122

- **YANQING TIAN ET AL: "A New Cross-Linkable Oxygen Sensor Covalently Bonded into Poly(2-hydroxyethyl methacrylate)-co-Polyacrylamide Thin Film for Dissolved Oxygen Sensing", CHEMISTRY OF MATERIALS, vol. 22, no. 6, 23 March 2010 (2010-03-23) , pages 2069-2078, XP055059199, ISSN: 0897-4756, DOI: 10.1021/cm903361y**
- **MICHELA QUARANTA ET AL: "Indicators for optical oxygen sensors", BIOANALYTICAL REVIEWS, vol. 4, no. 2-4, 24 November 2012 (2012-11-24), pages 115-157, XP055071464, ISSN: 1867-2086, DOI: 10.1007/s12566-012-0032-y**
- **S. M. BORISOV ET AL: "Red Light-Excitable Oxygen Sensing Materials Based on Platinum(II) and Palladium(II) Benzoporphyrins", ANALYTICAL CHEMISTRY, vol. 80, no. 24, 15 December 2008 (2008-12-15), pages 9435-9442, XP055303529, ISSN: 0003-2700, DOI: 10.1021/ac801521v**
- **SERGEI A. VINOGRADOV ; EVELYN KIM ; DAVID F. WILSON: "Pd tetrabenzoporphyrin-dendrimers: near-infrared phosphors for oxygen measurements by phosphorescence quenching", PROC. SPIE, vol. 4626, 2002, pages 193-200, XP002762041,**

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 2 970 318 B1

- L. H. HUTTER, B. J. MÜLLER, K. KOREN, S. M. BORISOV AND I. KLIMANT: "Robust optical oxygen sensors based on polymer-bound NIR-emitting platinum(II)-benzoporphyrins", J. MAT. CHEM. C, no. 36, 18 July 2014 (2014-07-18), pages 7589-7598, XP55303928,

Description

TECHNICAL FIELD

5 **[0001]** The present disclosure is in the field of luminescent dyes, polymers and biosensors.

BACKGROUND

10 **[0002]** Diagnosis, treatment and management of some medical conditions require monitoring of oxygen concentration in the afflicted organ or tissue. For example, Peripheral Arterial Disease (PAD), a disease that is characterized by plaque buildup in arteries that carry blood to the extremities, head, or organs, if left untreated, can lead to complete blockage of lower extremity arteries and requires either open bypass surgery or endo vascular intervention. Annually, at least 140,000 such revascularization procedures are conducted in the US alone to restore blood flow to ischemic tissues. Thus, ensuring that blood and oxygen flow are adequately restored and maintained during and after the revascularization technique is highly desirable. Current monitoring methods are expensive, cumbersome, time consuming, and do not provide accurate, continuous tissue oxygenation information. Thus, there is clearly a need for a better long-term oxygen tissue monitoring system. Doing so non-invasively with minimal user maintenance is essential, and sensor longevity of days to months is crucial in actual user environments.

20 **[0003]** Such real-time, continuous measurement of oxygen concentration (partial pressure) in tissues can be achieved by the use of sensors inserted or implanted into the tissue and measuring the signal generated by the sensor by a device located outside the body. Luminescence provides a useful tool for the design of such sensors. Luminescent oxygen sensors are based on the phenomenon that oxygen has a quenching effect on the molecular luminescence of various chemical compounds and that this effect can be employed for measuring oxygen concentrations (partial pressure) in vivo. The sensors, which are monitored optically through the skin, require
25 a highly stable dye with excitation and emission spectra in the near-infrared (NIR) optical window of the skin. These dye properties are crucial for the successful design of a luminescent oxygen sensor that can be implanted deep into tissue. Monitoring non-invasively through the skin requires the use of dyes with excitation and emission wavelengths in the optical window of the skin (approximately 550 to 1000 nm) to minimize light scattering and absorbance, and achieve a high signal-to-noise ratio. However, commercially available NIR dyes can be prone to photobleaching. Palladium porphyrins, such as tetracarboxyphenyl porphyrin (Pd-TCPP) have a very large Stokes shift and emission in the NIR.
30 However, they unfortunately require excitation with green light (525 nm), which is largely absorbed by the skin and the underlying tissue. Additionally, currently available sensors, made of rigid materials that vastly differ from the mechanical properties of tissue in which they are implanted, are bulky and inconvenient, and induce a series of biological events upon implantation that ultimately culminate in the formation of a fibrous capsule that walls it off from the body.
35 Tian et al (2010) Chemistry of Materials 22(6): 2069-78 describes a new crosslinkable oxygen sensor covalently bonded into poly(2-hydroxyethyl methacrylate)-co-Polyacrylamide thin film for dissolved oxygen sensing. US2012/0265034 describes tissue-integrating biosensors for the detection of one or more analytes. Quaranta et al (2012) Bioanalytical Reviews 4(2-4): 115-57 provides a review of the state of the art for optical oxygen sensors for particular industrial applications.

40 **[0004]** Thus, until the present invention there remains a clear need in the art to provide improved stable, near-IR luminescent compounds and sensors for direct, rapid and accurate measurement of oxygen levels in tissue, particularly *in vivo*.

SUMMARY

45 **[0005]** Disclosed herein are luminescent dyes, polymers comprising said dyes, and sensors comprising the polymers of the present invention. The invention is defined by the claims. Any subject-matter falling outside the scope of the claims is provided for information purposes only.


50 **[0006]** The present invention provides a sensor for detecting an analyte comprising a polymer, wherein said polymer comprises one or more residues of a luminescent dye, wherein the luminescent dye comprises polymerisable groups and wherein one or more of the polymerisable groups are co-polymerised with other monomers to form the polymer, and wherein the luminescent dye is a photostable porphyrin dye and has excitation and emission spectra in the NIR optical window of a mammalian skin wherein the luminescent dye is a compound having the formula:

55

5

10

15



(I)

20

wherein M is H, Pd, Zn, Pt, Gd or Yb;

each R¹ is same or different and, independently, C(O)X--(CH₂)_n--YC(O)C(R⁴)CH₂, C(O)X--(CH₂CH₂O)_mCH₂CH₂--YC(O)C(R⁴)CH₂ or COOH;

R⁷ is C(O)X--(CH₂)_n--YC(O)C(R⁴)CH₂, or C(O)X--(CH₂CH₂O)_mCH₂CH₂--YC(O)C(R⁴)CH₂;

R² and R³ are fused, in each case, to form a cycloalkenyl, aryl, or heteroaryl group; X is O or NR⁵;

25

Y is O or NH;

R⁵ and R⁴ are independently H or C₁-C₄ alkyl;

each R⁶ is same or different and, independently, H or F;

n is 1-10; and

m is 1-300.

30

[0007] The polymers provided herein can be luminescent biocompatible hydrogels.

[0008] The present invention relates to various luminescent sensors comprising the polymers provided herein for detecting an analyte, e.g., oxygen, in vivo or in vitro. The sensors can be in the form of a powder, fabric (e.g., wound dressing), sutures, needle, rod, disk or any other suitable form.

35

[0009] In another embodiment, the luminescent sensors provided herein are tissue-integrating or comprise a tissue-integrating scaffold and produce a detectable signal in the presence of the analyte; and further wherein the sensors provide detection of the analyte when placed (e.g., implanted) into the tissue of a subject. The tissue-integrating sensors as described herein can provide long-term detection of the analyte(s).

40

BRIEF DESCRIPTION OF THE DRAWINGS

[0010]

45

Figure 1 depicts Compound 2 (Pd-BP) absorption and emission spectra. Spectra were taken of covalently bound Pd-BP in pHEMA hydrogel. Excitation at 633 nm gave 805 nm emission, confirming shift into the NIR.

50

Figure 2 demonstrates that Compound 2 (Pd-BP) incorporated into a pHEMA hydrogel sensor enables brighter signals from deeper within the tissue. Images above show intensity of NIR Pd-BP (A) and green-ex Pd-TCP (B) subcutaneous hydrogel implants measured in a rat carcass. Pd-BP is significantly brighter than TCP due to the NIR excitation and emission wavelengths, which allow much greater light penetration into the skin, enabling deeper sensor placement.

Figure 3 depicts luminescence signal of pHEMA O₂ sensor implanted in a mouse brain.

55

Figure 4 depicts luminescence of oxygen sensors implanted in rat skin (170 days). Intensity varies as a function of implantation depth (data normalized to baseline fluorescence) and tissue oxygen concentration. Inhaled oxygen was modulated between 100% and 12% and images were collected every 30 s in a Caliper IVIS (Ex = 640 nm, Em=800 nm). Regions of interest (ROIs) were drawn around the sensors and the data plotted versus time. Data is

shown in Figure 6.

Figure 5 shows a SEM image of tissue-integrating porous hydrogel scaffold.

5 **Figure 6** demonstrates determination of photostability Pd-BP. Gels in PBS (pH 7.4, 37°C) were illuminated using a 525 nm LED at a 40% duty cycle. Both lifetime signal remains constant.

10 **Figure 7, panels A and B**, depicts that the response of the porous, tissue-integrated sensors (**A**) is rapid (~30 seconds), while the response of the solid sensor (**B**) response is much slower (plateau not even reached after 5 minutes). The solid sensors are the same rod-shape and material composition.

Figure 8, panels A and B, depicts dynamic response of Pd-BP hydrogels to O₂ (A) and a Stern-Vomer plot of O₂ quenching efficiency with Pd-BP (B). The response is linear with good sensitivity and rapid response time.

15 **Figure 9, panels A and B**, depicts dynamic response of GOx/Pd-BP gel to glucose (A) and normalized glucose dose-response curve (B).

20 **Figure 10, panels A and B**, depicts detectable modulating sensor signal from the O₂ sensor (A) and histological analysis of pig biopsy containing the sensor (B).

25 **Figure 11, panels A to D**, depicts solid sensor response to deoxygenation (0.12 FIO₂) and re-oxygenation (1.00 FIO₂) (A), fluorescent micrographs of solid sensors and surrounding tissue samples at 7 and 28 days after implantation, porous, tissue-integrating sensor response to deoxygenation (0.12 FIO₂) and re-oxygenation (1.00 FIO₂) (C), fluorescent micrographs of porous sensors and surrounding tissue samples at 7 and 28 days after implantation (D).

DETAILED DESCRIPTION

30 **[0011]** Described herein are polymerizable luminescent dyes useful for incorporation into polymers and polymers comprising as monomeric units residues of the dyes of the present invention. The dyes and the polymers are useful, for example, in sensing and imaging applications, for example, accurate and optionally long term measurements of oxygen *in vivo* and *in vitro*.

35 **[0012]** Additionally, described herein are sensors comprising the polymers of the present invention. The sensors can be implanted into a tissue of a subject and used for long-term or short-term continuous and semi-continuous collection of data of various biochemical analytes, optionally without the use of implantable hardware of any type and/or enzymatic and electrochemical detection methods. In one aspect, the sensors are tissue integrating, e.g., allow capillaries to grow in close proximity to all regions of the sensor (e.g., on the surface and inside), which results in accurate analyte measurements, including over long term. In another aspect, in addition to the luminescent dyes and/or the polymers of the present invention, the sensors comprise an oxidase, such as, but not limited to, glucose oxidase, and the luminescent dyes and/or their residues incorporated as monomeric units into the polymers measure the consumption of oxygen by the oxidase, thus, the sensors can provide detection of a number of analytes other than oxygen, such as, but not limited to, glucose.

40 **[0013]** Advantages of the dyes and luminescent polymers provided herein include, but are not limited to: (1) excitation and emission wavelengths in the optical window of the skin (approximately 550 nm to 1000 nm) allowing detection of analytes deep within a tissue or an organ; (2) high signal-to-noise ratio; (3) large Stokes shifts and emission; (4) photostability, e.g., the dyes and/or polymers do not undergo rapid photobleaching.

45 **[0014]** Advantages of the sensors described herein include, but are not limited to: (1) providing devices that generate stable signal over a long period of time (e.g., greater than a week, greater than a month, greater than 6 months), (2) providing devices that are placed or implanted and integrate into the subject's tissue (e.g., through tissue and/or capillary in-growth); (3) providing devices which can be implanted through syringe injection or trocar injection, meaning that no surgery is required to put the sensing media in place in the body; (4) providing devices that do not include sensor electronics in the body; (5) providing devices that accurately assess analyte (e.g., oxygen) concentration for long periods of time (e.g., greater than a week, typically weeks, months or years) and/or (6) providing devices of small dimensions which will give result in increased patient comfort and better acceptance by the body.

55 **[0015]** It must be noted that, as used in this specification and the appended claims, the singular forms "a", "an", and "the" include plural referents unless the content clearly dictates otherwise. Thus, for example, reference to a sensor comprising "a sensing moiety" includes devices comprising of two or more sensing moieties. Likewise, reference to "an analyte" refers to two or more analytes.

Definitions

[0016] The term "tissue integrating" refers to a material (e.g., scaffold) which, when integrated into living tissue remains in close proximity with the blood vessels of the tissue (e.g., capillaries).

[0017] By "long-term" is meant that the implant senses the analyte for greater than about 7 days, for example weeks, months, or years.


[0018] By "biodegradable" or "bioabsorbable" is meant that the material is capable of being broken down by the subject's body over a period of time, ranging from days to weeks to months or years.

[0019] By "hydrogel" is meant a material that absorbs a solvent (e.g. water), undergoes rapid swelling without discernible dissolution, and maintains three-dimensional networks capable of reversible deformation.

[0020] The term "stimuli-responsive" refers to substances, e.g., polymers, that change their physical state, e.g., undergo a phase transition, when exposed to an external stimulus or according to the environment they are in. Non-limiting examples of such polymers are "smart polymers" (Kumar A. et al., Smart polymers: Physical forms and bioengineering applications. Prog. Polym. Sci. 32 (2007) 1205-1237).

A. Luminescent NIR dyes

[0021] In one aspect, this invention provides a sensor for detecting an analyte comprising a polymer, wherein said polymer comprises one or more residues of a luminescent dye, wherein the luminescent dye comprises polymerisable groups and wherein one or more of the polymerisable groups are co-polymerised with other monomers to form the polymer, and wherein the luminescent dye is a photostable porphyrin dye and has excitation and emission spectra in the NIR optical window of a mammalian skin wherein the luminescent dye is a compound having the formula I:



(I)

wherein M is H, Pd, Zn, Pt, Gd or Yb;

each R¹ is same or different and, independently, C(O)X--(CH₂)_n-YC(O)C(R⁴)CH₂, C(O)X--(CH₂CH₂O)_mCH₂CH₂--YC(O)C(R⁴)CH₂ or COOH;

R⁷ is C(O)X--(CH₂)_n--YC(O)C(R⁴)CH₂, or C(O)X--(CH₂CH₂O)_mCH₂CH₂--YC(O)C(R⁴)CH₂;

R² and R³ are fused, in each case, to form a cycloalkenyl, aryl, or heteroaryl group;

X is O or NR⁵;

Y is O or NH;

R⁵ and R⁴ are independently H or C₁-C₄ alkyl;

each R⁶ is same or different and, independently, H or F;

n is 1-10; and

m is 1-300.

[0022] In one embodiment, M is Pd. In another embodiment, R¹ and R⁷ are both C(O)NH(CH₂)₂OC(O)C(CH₃)CH₂.

[0023] In another embodiment, R¹ and R⁷ are both C(O)X-(CH₂CH₂O)_mCH₂CH₂-YC(O)C(R⁴)CH₂.

[0024] In another embodiment, R¹ and R⁷ are both C(O)X-(CH₂)_n-YC(O)C(R⁴)CH₂.

[0025] In one embodiment, R² and R³ are fused to form a heteroaryl group. In one embodiment, R² and R³ are fused


to form a cycloalkenyl group. In one embodiment, R² and R³ are fused to form a tetracyclohexeno group. In one embodiment, R² and R³ are fused to form an aryl group. In one embodiment, the aryl group is perfluorinated. In one embodiment, R² and R³ are fused to form a benzo group. In another embodiment, R² and R³ are fused to form a naphtho group.

[0026] In one embodiment, R¹ comprises an oligoethylene glycol linker having 2-300 ethylene units. In another embodiment, R⁷ comprises an oligoethylene glycol linker having 2-300 ethylene units.

[0027] In one specific embodiment, M is Pd, R¹ and R⁷ are both C(O)NH(CH₂)₂OC(O)C(CH₃)CH₂, and R² and R³ are fused to form a benzene ring.

[0028] In one embodiment, the compound of Formula 1 is a near-IR luminescent dye. In one embodiment, the compound of Formula 1 has an absorption maximum between 500 nm and 800 nm. In one specific embodiment, the compound of Formula 1 has an absorption maximum between 500 nm and 700 nm. In one embodiment, the compound of Formula 1 has an emission maximum between 500 and 1000 nm. In one embodiment, the compound of Formula 1 has an emission maximum between 650 and 900 nm. In one specific embodiment, the compound of Formula 1 has an emission maximum between 800 and 900 nm. In one embodiment, the compound of Formula 1 of the present invention is photostable and has excitation and emission spectra in the NIR optical window of the skin.

[0029] For example, in a preferred embodiment, as illustrated by FIGURE 1, the Compound 2 of Formula 2 has an absorption maximum at 633 nm and an emission maximum at 805 nm when co-polymerized with HEMA into a hydrogel.



Formula 2

[0030] In some embodiments, the dyes of the present invention are encapsulated into a solid, oxygen-impermeable nanosphere. The nanospheres can be used for luminescent, non-oxygen sensitive applications.

B. Polymers

[0031] The fluorescent dyes of the present invention comprise polymerizable groups, e.g., residue of acrylic or methacrylic acid, and can be co-polymerized with other monomers to provide polymers comprising near-IR luminescent groups. When the compounds have 2 or more polymerizable groups, the polymers obtained from their co-polymerization with other monomers can be crosslinked. Alternatively, another crosslinking monomer can be added into the polymerization mixture to achieve a higher degree of crosslinking of the resulting polymer.

[0032] Polymers described herein can be prepared in any suitable manner. Suitable synthetic methods used to produce the polymers provided herein include, by way of non-limiting example, cationic, anionic and free radical polymerization. In certain embodiments, polymer synthesis is performed neat or in any suitable solvent. Suitable solvents include, but are not limited to, pentane, hexane, dichloromethane, chloroform, water, ethylene glycol, propylene glycol, DMSO or dimethyl formamide (DMF). In certain embodiments, the polymer synthesis is performed at any suitable reaction temperature, including, e.g., from about -50°C to about 100°C, or from about 0°C to about 70°C.

[0033] Preferably the polymers are prepared by the means of a free radical polymerization. When a free radical polymerization process is used, (i) the monomer, (ii) optionally, the co-monomer(s), and (iii) an optional source of free radicals are provided to trigger a free radical polymerization process. In some embodiments, the source of free radicals is optional because some monomers may self-initiate upon heating at high temperature. In certain instances, after forming the polymerization mixture, the mixture is subjected to polymerization conditions. Such conditions are optionally

varied to any suitable level and include, by way of non-limiting example, temperature, pressure, light, atmosphere, ratios of starting components used in the polymerization mixture and reaction time. The polymerization is carried out in any suitable manner, including, e.g., in solution, dispersion, suspension, emulsion or bulk.

5 **[0034]** In some embodiments, initiators are present in the reaction mixture. Any suitable initiator is optionally utilized if useful in the polymerization processes described herein. Such initiators include, by way of non-limiting example, one or more of alkyl peroxides, substituted alkyl peroxides, aryl peroxides, substituted aryl peroxides, acyl peroxides, alkyl hydroperoxides, substituted alkyl hydroperoxides, aryl hydroperoxides, substituted aryl hydroperoxides, heteroalkyl peroxides, substituted heteroalkyl peroxides, heteroalkyl hydroperoxides, substituted heteroalkyl hydroperoxides, heteroaryl peroxides, substituted heteroaryl peroxides, heteroaryl hydroperoxides, substituted heteroaryl hydroperoxides, alkyl peresters, substituted alkyl peresters, aryl peresters, substituted aryl peresters, or azo compounds. In specific embodiments, benzoylperoxide (BPO) and/or AIBN are used as initiators.

10 **[0035]** In some embodiments, polymerization processes are carried out in a controlled (living) mode. Preferred controlled (living) polymerization processes include reversible addition-fragmentation chain transfer (RAFT) polymerization processes and Atom Transfer Radical Polymerization (ATRP).

15 **[0036]** In certain embodiments, the polymer of the present invention is a hydrogel. For example, the hydrogel can be prepared by reacting hydroxyethyl methacrylate (HEMA), to form poly(hydroxyethyl methacrylate), pHEMA. Furthermore, various comonomers can be used in combination to alter the hydrophilicity, mechanical and swelling properties of the hydrogel (e.g. PEG, NVP, MAA). Non-limiting examples of polymers include 2-Hydroxyethyl methacrylate, polyacrylamide, N-vinylpyrrolidone, N,N-Dimethylacrylamide, poly(ethylene glycol) monomethacrylate (of varying molecular weights), diethylene glycol methacrylate, N-(2-hydroxypropyl)methacrylamide, glycerol monomethacrylate, 2,3-dihydroxypropyl methacrylate and combinations thereof. Non-limiting examples of cross-linkers include tetraethylene glycol dimethacrylate, poly(ethylene glycol) (n) diacrylate (of varying molecular weights), ethoxylated trimethylolpropane triacrylate, bisacrylamide and combinations thereof. Non-limiting examples of initiators include Irgacure Series (UV), Azobisisobutyronitrile (AIBN) (thermal), Ammonium Persulfate (APS) (thermal).

20 **[0037]** In a specific embodiment, the polymer is a luminescent hydrogel prepared by co-polymerization of HEMA and compound of Formula 1. In a preferred embodiment, the hydrogel is prepared by co-polymerization of various molar amounts of compound of Formula 2 mixed with 2-hydroxyethyl methacrylate (HEMA) monomer, tetraethylene glycol dimethacrylate (TEGDMA) crosslinker, Irgacure 651 initiator, water and co-solvent, followed by UV-initiated polymerization. In another embodiment, the polymer contains 1 mM final concentration of Compound of Formula 1. In a specific embodiment, the polymer is an oxygen sensing poly(2-hydroxyethyl methacrylate) (pHEMA) scaffold prepared by co-polymerization of HEMA (2-hydroxyethyl methacrylate) (50 Wt %), TEGDMA (triethyleneglycol-dimethacrylate) (1 Wt %1), ethylene glycol (20 Wt%), water (25.5 Wt %), the photoinitiator Irgacure 651 (0.5% vol/vol) and 3% of Compound 2.

25 **[0038]** The polymer of the present invention may be degradable, either by the body (biodegradable) or by the application of an external initiator to start or speed up the degradation process (e.g. UV, ultrasonics, radio frequency, temperature, or other exogenous sources to initiate degradation.). For example, the polymer may be biodegradable or bioresorbable or may comprised any biodegradable or bioresorbable segments, including but not limited to degradable forms of alginates, poly(lactic acid), poly(vinyl alcohol), polyanhydrides, poly(glycolic acid), microporous polyesters, microporous polyethers and cross-linked collagen. One specific example is UV-photopolymerization of poly(ethylene glycol)-diacrylate and acrylated protease-degradable peptides and VEGF as described by Phelps, et al (2010) Proc. Nat'l. Acad. Sci. USA 107(8):3323-3328

30 **[0039]** In one embodiment, polymers provided herein are biocompatible. In another aspect of the invention, the polymers are biodegradable. Degradable hydrogels can be synthesized using Atom Transfer Radical Polymerization (ATRP) through co-polymerization of the HEMA with polymerizable luminescent dyes of the present invention. Porous sensor scaffolds, based on non-degradable and degradable oxygen-sensing hydrogels, can be generated by using a sphere-templating fabrication technique. Degradable and non-degradable HEMA reagents and polymerizable dye will be polymerized over templating microspheres, which are subsequently dissolved away with solvent to generate desirable non-degradable and degradable scaffolds. Briefly, using controlled ATRP, HEMA will be polymerized in the presence of bifunctional degradable PCL-based ATRP initiator and cross-linker. In this synthesis scheme, pHEMA chains grow at the same rate from both sides of degradable initiator, resulting in degradation products with a MW that is half that of the parent polymer. By controlling the MW of the parent polymer and the PEG and PCL units in the initiator and/or crosslinker, the degradation rate of the polymers can be varied. Limiting the MW of the parent polymer to 10kDa results in degradation products that can be cleared by the body and an increased degradation rate while still preserving the hydrogel's mechanical strength.

35 **[0040]** In certain embodiments the polymers provided herein are stimuli-responsive, e.g., temperature or pH-sensitive polymers. One non-limiting example of such a stimuli-responsive polymer is a temperature-sensitive polymer derived from co-polymerization of NIPAM. Such polymers are useful for implantation of the sensor comprising said polymers in a desired location within tissue by first dissolving the polymer in a suitable for injection media at a lower than body temperature and then injecting the resulting solution into the tissue and/or at desired location of the body. As the polymer

is subjected to a higher (e.g., body) temperature, it precipitates in or near the site of the injection where monitoring of oxygen is required.

C. Sensors

5

[0041] The polymer of the present invention is incorporated into a sensor useful for detection of an analyte. The detection of the analyte can be in vitro or in vivo. The remaining sentences of this paragraph describe how the word "polymer" is used in section titled "C. Sensors". The polymer may have the molecules of Formula 1 and/or Formula 2 covalently bound to the polymer backbone. The molecules of Formula 1 and/or Formula 2 maybe attached to (e.g. via a covalent bond or other means) or contained within nanoparticle carriers or microparticle carriers or other carriers that are attached to or contained within the polymer. Such carriers may be covalently bound to the polymer backbone. The word polymer can be used interchangeably with the word sensor. According to the invention, the luminescent dye comprises polymerisable groups wherein one or more of the polymerisable groups are co-polymerised with other monomers to form the polymer.

10

[0042] In one non-limiting example, the polymer is incorporated into an oxygen-sensing wound dressing that can be used to monitor the process of wound healing, e.g. to constantly and non-invasively assess one of the critical factors of healing (i.e. oxygenation).

15

[0043] In another embodiment, the polymer is incorporated into a powder, which is used directly in the wound as a sensor for wound-healing monitoring. The sensor of the present invention can also be in the form of an injectable, implant, a mesh or sutures to be used in applications which benefit from monitoring of oxygenation of skin or the underlying tissue, including, but not limited to wound healing monitoring, skin closure, hernia repair, flap transfer surgeries, reconstructive surgery, and other plastic surgery applications. The sensor of the present invention can also be used for measurement for microcirculatory dysfunction and peripheral artery disease. Specifically in re-vascularization procedures or upon administration of drug, tissue oxygen may be directly monitored. The sensor of the present invention can also be used in oncology applications to determine the degree of hypoxia in a tissue or an organ. In one embodiment, the sensor is used to monitor tumor growth in animal, including but not limited to, mouse or rat models used in oncology pharmaceutical and diagnostic research and discovery, e.g., cancer therapy dosing or monitoring of tumor metabolism. The sensor of the present invention can also be used in monitoring the state of pulmonary function, for example in COPD and asthma disease states. In yet another embodiment, the sensor is used for exercise or training optimization, e.g., soldier and athlete performance or personal exercise programs. The sensor can also be in the form of an oxygen-sensing tattoo.

20

25

30

[0044] Yet in another embodiment, the sensors of the present invention are used in neuroscience monitoring applications, where currently there are no tools available for continuous monitoring of oxygen, for example, in subarachnoid hemorrhage monitoring.

35

[0045] In one embodiment, the sensor of the present invention is a solid material that could be in form of a slab, rod, cylinder, particle or powder. In a specific embodiment, the sensor is in the form of a rod. In another embodiment, the sensor is in the form of a cylinder.

40

[0046] In another embodiment, the polymer of the present invention is incorporated into a tissue-integrating scaffold to provide a tissue-integrating sensor (as described in the US patent application 2012/0265034). The sensors described herein typically comprise a tissue-integrating scaffold (also referred to as a matrix) material. Preferably, the tissue-integrating scaffold of the invention may be constructed with materials and/or micro-architecture such that the scaffold promotes tissue-integration and/or vascularization. For example, porous scaffolds provide tissue biomaterial anchoring and promote in-growth throughout the pores. The resulting "hallway" or "channel" pattern of tissue growth are healthy, space-filling masses that persist over time and promote host cell integration. Most or all of the pores of the biomaterials described herein are preferably interconnected (co-continuous). The co-continuous pore structure of the biomaterials promotes space-filling in-growth of cells in the implant, which in turn limits the foreign body response and leads to long-term (greater than one week and up to years) persistence of the implant's ability to act as a sensor. Alternative structures that provide tissue integrating scaffolds include fibers (e.g., 1 to 10 or more microns in diameter, such as 5, 6, 7, 8, 9, 10 or more microns), which may be arranged in non-random or random configuration. Tissue-integrating scaffolds (in any configuration) can also be formed by multiphoton polymerization techniques. Kaehr et al. (2008) Proc. Nat'l. Acad. Sci. USA 105(26):8850-8854; Nielson et al. (2009) Small 1:120-125; Kasprzak, Doctoral Dissertation, Georgia Institute of Technology, May 2009.

45

50

[0047] The polymer of the invention, preferably in the form of a tissue-integrating scaffold, may comprise any material in combination with the compound of Formula 1 or Formula 2, including but not limited to synthetic polymers, naturally-occurring substances, or mixtures thereof. Exemplary synthetic polymers include, but are not limited to polyethylene glycol (PEG), 2-hydroxyethyl methacrylate (HEMA), silicone rubber, poly([epsilon]-caprolactone) dimethylacrylate, polysulfone, (poly)methy methacrylate (PMMA), soluble Teflon-AF, (poly) ethylenetetraphthalate (PET, Dacron), Nylon, polyvinyl alcohol, polyacrylamide, polyurethane, and mixtures thereof. Exemplary naturally-occurring materials include,

55

but are not limited to, fibrous or globular proteins, complex carbohydrates, glycosaminoglycans, extracellular matrix, or mixtures thereof. Thus, the polymer scaffold may include collagens of all types, elastin, hyaluronic acid, alginate, desmin, versican, matricellular proteins such as SPARC (osteonection), osteopontin, thrombospondin 1 and 2, fibrin, fibronectin, vitronectin, albumin, chitosan etc. Natural polymers may be used as the scaffold or as an additive.

[0048] In certain embodiments, the polymer of the invention, preferably in the form of a tissue-integrating scaffold, comprises a hydrogel. For example, the polymer may comprise a hydrogel, for example by reacting hydroxyethyl methacrylate (HEMA), poly (hydroxyethyl methacrylate), pHEMA. Furthermore, various comonomers can be used in combination to alter the hydrophilicity, mechanical and swelling properties of the hydrogel (e.g. PEG, NVP, MAA). Non-limiting examples of polymers include 2-hydroxyethyl methacrylate, polyacrylamide, N-vinylpyrrolidone, N,N-dimethylacrylamide, poly(ethylene glycol) monomethacrylate (of varying molecular weights), diethylene glycol methacrylate, N-(2-hydroxypropyl)methacrylamide, glycerol monomethacrylate, 2,3-dihydroxypropyl methacrylate and combinations thereof. Non-limiting examples of cross-linkers include tetraethylene glycol dimethacrylate, poly(ethylene glycol) (n) diacrylate (of varying molecular weights), ethoxylated trimethylolpropane triacrylate, bisacrylamide and combinations thereof. Non-limiting examples of initiators include Irgacure Series (UV), Azobisisobutyronitrile (AIBN) (thermal), Ammonium Persulfate (APS) (thermal).

[0049] The polymer of the invention, preferably in the form of a tissue-integrating scaffold, may be a sphere-templated hydrogel, for instance an inverse colloid crystal, for example as described in U.S. Patent Publication No. 2008/0075752 to Ratner, et al. or other tissue integrating materials.

[0050] The polymer of the invention, preferably in the form of a tissue-integrating scaffold, may be degradable, either by the body (biodegradable) or by the application of an external initiator to start or speed up the degradation process (e.g. UV, ultrasonics, radio frequency, or other exogenous sources to initiate degradation.). For example, the polymer may be comprised of any biodegradable or bioresorbable polymers, including but not limited to degradable forms of alginates, poly(lactic acid), poly(vinyl alcohol), polyanhydrides, poly(glycolic acid), microporous polyesters, microporous polyethers and cross-linked collagen. One specific example is UV-photopolymerization of poly(ethylene glycol)-diacrylate and acrylated protease-degradable peptides and VEGF as described by Phelps, et al (2010) Proc. Nat'l. Acad. Sci. USA 107(8):3323-3328.

[0051] Other specific examples are polymers described by Kloxin et al (2009) Science 324:59-63 and U.S. Patent No. 6,013,122 whose degradation is controlled through exposure to exogenous energy forms, as well as by Alexeev et al. (2003) Anal. Chem. 75:2316-2323; Badylak et al. (2008) Seminars in Immunology 20:109-116; Bridges et al. (2010) 94(1):252-258; Isenath et al. (2007) Research 83A:915-922; Marshall et al. (2004) Polymer Preprints, American Chemical Society, Division of Polymer Chemistry 45:100-101; Phelps et al. (2010) Proc Nat'l Acad Sci U S A. 107(8):3323-8; Ostendorf and Chichkov (2006) Two Photon Polymerization: A New Approach to MicroMachining, Photonics Spectra; Ozdemir et al. (2005) Experimental and Clinical Research, Plast. Reconstr. Surg. 115:183; U.S. Patent Publication No. 20080075752; Sanders et al. (2003) Journal of Biomedical Materials Research Part A 67A(4):1181-1187; Sanders et al. (2002) Journal of Biomedical Materials Research 62(2):222-227; Sanders et al. (2003) Journal of Biomedical Materials Research 65(4):462-467; Sanders et al. (2005) Biomaterials 26:813-818; Sanders et al. (2005) Journal of Biomedical Materials Research Part A 72(3):335-342; Sanders (2003) Journal of Biomedical Materials Research 67(4):1412-1416; Sanders et al. (2000) Journal of Biomedical Materials Research 52(1):231-237; and Young Min Ju et al. (2008) J Biomed Mater Res 87A:136-146.

[0052] In certain embodiments, the polymer of the invention, preferably in the form of a tissue-integrating scaffold, is constructed such that tissue response modifiers are released from the scaffold material to promote or enhance tissue-integration and vascularization.

[0053] In addition, the polymer of the invention, preferably in the form of a tissue-integrating scaffold, may be constructed such that it has conduits, pores or pockets that are hollow or filled with degradable, angiogenic, or other substances (e.g. stem cells). As noted above, once in the body, the biodegradation of the material filling the conduits, pores or pockets, creates space for tissue, including capillaries to integrate with the material. The degradable material that initially fills the conduits, pores, or pockets may enhance vessel growth or tissue growth within the scaffold. This architecture promotes new vessel formation and maintains healthy viable tissue within and around the implant.

[0054] The polymer of the invention, preferably in the form of a tissue-integrating scaffold, may be constructed such that it is permeable to analytes of interest (e.g., oxygen can diffuse into a tissue-integrating hydrogel scaffold and reach the sensing moieties that are embedded within the hydrogel matrix).

[0055] The polymer of the invention, preferably in the form of a tissue-integrating scaffold, can be of any suitable form, including, but not limited to block-like (or any thickness), cube-like, disk-shaped, cylindrical, oval, round, random or non-random configurations of fibers and the like. In certain embodiments, the sensor comprises one or more fibers, which may be organized in a non-random fashion (e.g., grid, layered grid, etc.) or in a random fashion.

[0056] The polymer of the invention, preferably in the form of a tissue-integrating scaffold, described herein are typically combined with (or made up of) sensing moieties that detect one or more analytes. In one embodiment, the sensing moiety is the residue of compound of Formula 1 and/or 2 incorporated into the tissue-integrating scaffold.

[0057] In another embodiment, the polymer of the invention, preferably in the form of a tissue-integrating scaffold, comprises, in addition to the residue of compound of Formula 1 and/or Formula 2, a second sensing moiety that produces or consumes oxygen, e.g., an oxidase, and the residue of compound of Formula 1 and/or Formula 2 is used to detect the change in the oxygen concentration generated by the second sensing moiety. The second sensing moiety can comprise an enzyme, for example glucose oxidase (GOx), which is specific for the substrate glucose. The reaction of glucose via enzymatic interaction with glucose oxidase causes oxygen to be proportionally consumed and converted to H₂O₂. The reduction of O₂ in the vicinity of the enzyme can be measured by using an O₂-sensitive fluorescent dye, such as the molecules of Formula 1 and Formula 2. These dye molecules are quenched in the presence of O₂, so the reduction of O₂ by the action of GOx, causes an increase in fluorescence. The amount of fluorescence emitted from the O₂ calibration moieties is thus proportional to the concentration of glucose in the sensor. Oxidases besides glucose oxidase for detection of other analytes besides glucose may include bilirubin oxidase, ethanol oxidase, lactate oxidase, pyruvate oxidase, histamine oxidase or other oxidase to provide specificity to other analytes of interest.

[0058] The concentration of O₂ in the tissue can also vary physiologically, thereby changing or limiting the reaction of the oxidase enzyme in the sensing moieties. Therefore, the O₂ concentration in the sensor can be measured independent of the oxidase target concentration. This may be accomplished through physical separation on some nanometer, micro or mm scale of O₂ reference moieties from the enzyme-O₂ detection moieties to avoid cross talk. Such a reference measurement of O₂ would allow corrections to be made to the glucose-specific signal from the oxidase sensing moieties.

[0059] In another embodiment, the polymer of the invention, preferably in the form of a tissue-integrating scaffold, may be a multi-analyte sensor where oxygen is one of two or more analytes detected and reported. In this embodiment, the polymer comprises a residue of compound of Formula 1 and/or Formula 2 for detection of oxygen, and a second sensing moiety for detection of another substance. Non-limiting examples of analytes that may be detected by the sensing moieties include oxygen, reactive oxygen species, glucose, lactate, pyruvate, cortisol, creatinine, urea, sodium, magnesium, calcium, potassium, vasopressin, hormones (e.g., Luteinizing hormone), pH, cytokines, chemokines, eicosanoids, insulin, leptins, small molecule drugs, ethanol, myoglobin, nucleic acids (RNAs, DNAs), fragments, polypeptides, single amino acids and the like.

[0060] In another embodiment, the polymer of the invention, preferably in the form of a tissue-integrating scaffold, may be a sensor where the oxygen signal, as detected by Formula 1 and/or Formula 2, is used as a reference to correct or calibrate the signal for one or more other analytes. The oxygen signal may or may not be reported. It may be used only in internal algorithms to calibrate or correct the signal of the other analyte. The use of the oxygen signal as a reference in this embodiment helps to overcome physiological fluctuations, which may alter the analyte availability at the site of the sensor (e.g. blood flow variations).

[0061] In still further embodiments, the sensing moieties, in addition to the residue of compound of Formula 1 and/or Formula 2 comprise a second luminescent analyte sensing moiety, and the residue of the compound of Formula 1 and/or Formula 2 is used as a reference molecule. The non-oxygen sensing moieties may utilize analyte-specific moieties such as competitive binding assays (e.g. a ligand receptor moiety and an analyte analogue moiety such as Concanavalin A and dextran), reversible luminescent binding molecules (e.g. boronic acid based sensing chemistry for glucose detection), binding proteins such as glucose binding proteins. To measure an analyte such as glucose in the tissue, the polymer is illuminated from a patch reader on top of the skin above the implant with 650nm light at desired intervals over the long-term life of the implant (e.g., every 5-60 minutes over a period of 90 days or more). The amount of luminescent signal (e.g., from a molecule such as Alexafluor 647) detected is proportional to the concentration of analyte (e.g. glucose) in the tissue. The amount of luminescent signal (e.g. from Formula 1 or Formula 2 molecule) detected is proportional to the concentration of O₂ in the tissue. The concentration of O₂ in the tissue is indicative of acute and or chronic physiological changes around the sensor, and may be used to correct or adjust the glucose signal or other analyte signal through a proportionality algorithm.

[0062] In another embodiment, internal reference control materials can be employed that facilitate correcting for tissue optical variation. The tissue-integrating implanted biosensor typically resides 3-4 mm under the surface of the skin. It is well known that in skin excitation light and emitted fluorescent light in the near infrared range are highly scattered as the light traverses the tissue between the reader patch and the implant. The extent of absorption and scattering is affected by physical properties such as temperature or by tissue composition, including but not limited to variations in blood perfusion, hydration, and melanin concentration. Skin variations can occur between users or between different time points for a single patient, and these variations can affect the fluorescence excitation and emissions signals causing inaccurate signals for the analyte-specific signal. Accordingly, a separate fluorescence molecule with emission spectra distinguishable from the analyte-specific fluorescence can be immobilized into the scaffold. The fluorescence from the molecule can be measured separately from the analyte-specific fluorescence to measure a signal that informs about variations in tissue composition. The dye selected is based on having a similar response to tissue variations as the analyte-specific dye. Formula 1 or Formula 2 may have the oxygen sensing capabilities greatly reduced or eliminated, for example, by incorporation in a non-oxygen diffusive environment such as embedding in highly crosslinked PAN or inside a silica shell. In this format, the dye molecules of this invention may serve as the stable internal reference control

materials described above.

[0063] Tissue-integrating sensors comprised of one or more cylindrical shaped elements (e.g., fibers) eliminate or greatly reduce the foreign body response as compared to currently available implants. Moreover, the average diffusion distances from the capillary supply to all parts of the sensing media are comparable to native tissue, unlike other known sensors.

[0064] It will be apparent that the overall dimensions of the sensing media (implantable sensor) will vary according to the subject and/or the analyte(s) to be measured. Typically, the implant will be between about .001 mm to 2 mm in thickness (or any value therebetween) and between 1 mm and 1 cm in diameter (or an equivalent cross sectional area of a non-circular shape, for example length/width) and 15 mm in length or less, for example, a disk shaped sensor that is 2 mm or less thick and 10 mm or less in diameter. In certain embodiments, the approximate sensor size is approximately 100-1000 microns in diameter and has the length of between 0.25 mm and 10 mm. The size of the tissue-integrating sensing media in disk form is typically 2 mm or less thick and 10 mm or less in diameter.

[0065] Another aspect of the present invention is a tissue-integrating biosensor system for semi-continuous, continuous and/or long-term use within a mammalian body.

[0066] One advantageous property of the polymers of the present invention is their stability. In one aspect of the invention, the sensor is stable in a mammalian tissue for a long period of time, e.g., longer than a week, longer than a month, longer than 6 months. In one exemplary embodiment, as shown by the FIGURE 2, the sensor is stable and produces a stable signal when implanted into the rat skin for 170 days.


EXAMPLES

[0067] NMR spectroscopic data were recorded on a 300 MHz instrument at room temperature. NMR spectra were calibrated to the solvent signals of deuterated DMSO-d₆ or CDCl₃. The following abbreviations are used to indicate the signal multiplicity: s (singlet), d (doublet), t (triplet), q (quartet), br (broad), m (multiplet). Analytical HPLC-MS data were recorded on a HPLC system with a C18 reverse column coupled to an electrospray ionization (ESI) spectrometer. 2-Aminoethyl methacrylate hydrochloride and tetraethylene glycol dimethacrylate were purchased from Polysciences, Inc. All other chemicals were purchased from Sigma Aldrich.

Example 1: Synthesis of a polymerizable near-IR luminescent dye.

Scheme 1 describes the synthesis of one exemplary near-IR luminescent dye, Compound 2 (also referred to as Pd-BP):

[0068]



Scheme 1

Compound 3 was prepared as described in Niedermaier et al, J. Inorg. Chem., 2010, 49, p. 9333. Briefly, to 90 mL of anhydrous THF was added 1-nitrocyclohexene (2.66 mL), ethyl isocyanoacetate (2.6 mL), and DBU (3.53 mL). The reaction was refluxed at 70°C under argon for 18 hours. Brown precipitate formed as soon as heating began. THF was evaporated, the residue was dissolved in methylene chloride, and the product was purified by flash chromatography on silica gel in methylene chloride. Product-containing fractions were evaporated under vacuum to remove most of the solvent, and to the residual solution hexanes were added to facilitate crystallization of the product. After 48 hr at 4°C, the precipitate was collected to by filtration to yield 2 g of the product as fine yellow needles. The mother liquor was partially evaporated to yield additional 1.4 g of the product; 75% total yield.

Compound 5: Compound 3 (1.40 g, 7.2 mmol) was suspended in 30 mL of anhydrous ethylene glycol, and KOH pellets (0.73 g, 13.0 mmol) were added to the solution. The mixture was refluxed under argon for 1 hr. The resulting clear brown solution was cooled to 0°C, and 100 mL of dichloromethane was added to the solution. Dichloromethane layer was separated, washed with water (2X100 mL), and brine (2X100 mL) and dried over anhydrous sodium sulfate. The product was purified by flash chromatography on silica gel in dichloromethane. Fractions containing the fast-running component were pooled and diluted with dichloromethane to 1000 mL. To the resulting solution was added methyl-4-formyl benzoate, under argon, the solution was stirred at room temperature for 10 min, and $\text{BF}_3 \cdot \text{OEt}_2$ (0.19 mL, 1.3 mmol) was added. The mixture was stirred for 2 hr, then 1.73 g (7.6 mmol) of DDQ was added, and the mixture was allowed to stir overnight. The mixture was washed sequentially with 10% aq. Na_2CO_3 , 1M HCl, and brine, then dried over anhydrous sodium sulfate. After purification by silica gel chromatography using stepwise gradient of MeOH in dichloromethane (0-2%), 430 mg (24%) of the product as green powder.

Compound 6: Compound 5 as a free base (0.43 g, 0.40 mmol) was dissolved in 50 mL of benzonitrile. To the solution, PdCl_2 was added under argon, and the mixture was refluxed for 10 min. The color of the solution changed from


green to red. The mixture was cooled to room temperature, diluted with 200 mL of dichloromethane, and filtered through Celite. Dichloromethane was evaporated under vacuum, and benzonitrile was distilled off. The product was purified by flash chromatography on silica gel in dichloromethane, and the final purification was achieved by flash chromatography on silica gel in hexanes:ethyl acetate (1:1) to yield 0.109 mg (60%) of the product as a red powder.

Compound 7: Compound 6 (0.105 g, 0.09 mmol) was dissolved in 20 mL of anhydrous THF, and DDQ (0.327 g, 1.44 mmol) was added to the solution. The mixture was refluxed for 20 min, and the reaction was stopped when no starting material was detected in the mixture by TLC. THF was removed under vacuum, the residue was diluted with dichloromethane and washed sequentially with 10% Na₂SO₄, water, and brine.

Compound 8: The ester 7 was hydrolyzed as described in Finikova et al., J. Phys. Chem., 2007, 111, p. 6977. Briefly, 0.074 g (0.064 mmol) of Compound 7 were dissolved in 110 mL of THF. To the solution, MeOH (10 mL) was added, followed by a solution of 0.573 g of KOH in 2 mL of MeOH. Green precipitate formed in the solution, and the solution became almost colorless. The precipitate was collected by centrifugation and dissolved in 10 mL of water. The solution was acidified with 0.2 mL of concentrated HCl, and the resulting precipitate was collected by centrifugation. Yield: 0.070 g (86%).

Compound 2: Compound 8, 30 (70 mg, 63.9 μmol) in DMF (10 mL) and CH₂Cl₂ (10 mL) at 0°C was added 1-hydroxybenzotriazole hydrate (43.17 mg, 0.32 mmol), N-(3-dimethylaminopropyl)-N'-ethylcarbodiimide hydrochloride (61.25 mg, 0.32 mmol), and triethylamine (90 μL, 0.64 mmol). After 20 min., 2-aminoethyl methacrylate hydrochloride (53.23 mg, 0.3195 mmol) was added, and the reaction was stirred for 16 h at room temperature. The CH₂Cl₂ was evaporated under reduced pressure, and ethyl acetate/hexanes mixture was added to precipitate the crude product from residual DMF. The solvent was decanted, and the precipitated residue was dissolved in CH₂Cl₂, washed sequentially with sat. NaHCO₃ and brine, dried over Na₂SO₄, filtered, and concentrated in vacuo. The crude product was purified by flash chromatography on silica gel (gradient of 0 - 4% methanol in CH₂Cl₂) to yield Compound 2 as a green powder (16 mg, 16% yield). ¹H NMR (300 MHz, CDCl₃) δ 8.40 (d, J = 8.1 Hz, 8H), 8.32 (d, J = 8.1 Hz, 8H), 7.22 (br s, 8H), 7.10 (br s, 8H), 6.28 (s, 4H), 5.71 (s, 4H), 4.61 (t, J = 5.4 Hz, 8H), 4.03 (q, J = 5.1 Hz, 8H), 2.06 (s, 12H). LC-MS (ESI): calcd for C₈₈H₇₃N₈O₁₂Pd: 1539.4403 [M+H]⁺, found 1539.4405 [M+H]⁺, R_t = 11.8 min.

Compound 9 was synthesized analogously to Compound 2 by reacting commercially available tetracarboxyphenyl porphyrin with aminoethyl methacrylate in the presence of HOBt and EDC as shown in Scheme 2:



Scheme 2

Example 2: Production of an oxygen sensing media with oxygen sensitive luminescent dye immobilized in a tissue-integrating hydrogel scaffold

[0069] The following describes one method for making a tissue-integrating sensor as described herein. This method involves the use of non-crosslinked PMMA templating microspheres and pHEMA as the scaffold material. The PMMA microsphere template was prepared using monodispersed PMMA spheres (20-100 μm, preferably 80 μm) and placing the template beads between two glass slides with Teflon spacers. The sintering process included sonicating for at least

10 minutes (one or more times) to closely pack the beads. Following sonication, the template is heated to a sufficient temperature for a sufficient time to fuse the beads (typically, to 140-180°C for 20 - 32 hours, for example, heat to approximately 177°C for 24 hours). For each lot of the beads, the temperature and heating times are optimized.

5 [0070] The general preparation of an oxygen sensing poly(2-hydroxyethyl methacrylate) (pHEMA) scaffold was performed as follows: HEMA (2-hydroxyethyl methacrylate) (50 Wt %), TEGDMA (triethyleneglycol-dimethacrylate) (1 Wt %), ethylene glycol (20 Wt%), water (25.5 Wt %), the photoinitiator Irgacure 651 (0.5% vol/vol) and 3% of Palladium-tetramethacrylate-benzoporphyrin (Compound 2, polymerizable O₂ sensitive dye) were mixed, yielding a final concentration of 1 mM Compound 2 in the polymer precursor solution. Polymer, solvents and sensing reagents were mixed to achieve sufficiently high sensing chemistry concentration to measurably detect a change in signal through tissue.

10 [0071] The pre-mixed monomer solution was filled into the PMMA mold. The solution was placed under vacuum to remove any bubbles and to completely infiltrate the PMMA-mold. Polymerization was initiated by exposing the mold to UV light (280 - 320 nm, 10 - 300 mW/cm²) for 5-10 minutes. Next, the PMMA microspheres were dissolved out of the resulting polymer by frequent exchange of dichloromethane or other solvent system for 24-48 hours using a Soxhlet extractor by manual volume changes.

15 [0072] The following describes preparation of the rod hydrogel sensors. 100 μL of a 10 mM solution of Compound 2 in DMSO, was added to a polymer precursor solution [2-hydroxyethyl methacrylate (0.5 mL, 4.1 mmol), tetraethyleneglycol dimethacrylate (10 μL, 34 μmol), ethylene glycol (0.2 mL), water (185 μL) and 2,2-dimethoxy-2-phenylacetophenone (5 mg, 2 μmol)], yielding a final concentration of 1 mM Compound 2. The dye and polymer precursor mixture was injected into a poly(methyl methacrylate) (PMMA) bead-containing glass mold, as previously described by Marshall, A.J. et al. (Biomaterials with Tightly Controlled Pore Size that Promote Vascular In-Growth. ACS Polymer Preprints 45, 100-101 (2004)). The mold was placed under vacuum to remove any bubbles and to ensure complete filling. Polymerization was initiated by exposing the mold to UV light (280-320 nm) using a Dymax 2000-EC Flood Curing System equipped with a 400 Watt Mercury bulb for 2 minutes per side at a distance of approximately 6". The glass plates were removed and the hydrogel was soaked in 50 mL of CH₂Cl₂ (exchanged twice) with shaking for 24 hours to extract out the PMMA beads.

20 The hydrogel was transferred into water and placed under vacuum for 5 minutes to fully hydrate the porous scaffold. For implantation, the hydrogels were cut into rods (10 mm in length with a 750 μm X 750 μm cross-section), disinfected by exposure to 70% ethanol, and then stored in sterile pH 7.4 PBS at 4 °C before use. Non-porous (i.e., solid) hydrogel sensors were prepared analogously but without the use of templating beads.

25 [0073] Hydrogels comprising Glucose oxidase (GOx) were also prepared as described above except GOx was also included in the polymerization mixture used to prepare the scaffold (FIGURE 5).

Example 3: Determination of excitation and emission wavelengths of Compound 2 incorporated into a hydrogel.

35 [0074] The absorption and emission spectra of the dye-containing hydrogels generated in Example 2 were measured in pH 7.4 PBS at ambient atmosphere using a fluorescence plate reader (FIGURE 1). The absorption spectra contained a Soret band at 445 nm and a Q band at 633 nm. Excitation at 633 nm gave an emission peak at 805 nm, thus confirming that Pd-BP (Compound 2) exhibits both absorption and emission in the NIR.

Example 4: Determination of optimal dye concentration in hydrogel.

40 [0075] To determine the minimum dye concentration required to achieve a maximum intensity signal, a series of pHEMA hydrogels containing various concentrations of Pd-BP (Compound 2) were made. Solid and porous pHEMA hydrogels containing covalently-bound Pd-BP (Compound 2) at 0.01, 0.1, 1, 2, and 3 mM dye concentrations were prepared. All gels were ~1 mm thick; porous gels contained an average pore size of ~ 70 μm. While in pH 7.4 PBS in ambient air, the fluorescence emission of each gel was measured at 805 nm (633 nm excitation) using a fluorescence plate reader. From these data, the optimal dye concentration was determined to be 1 mM, since signal saturation was observed at higher concentrations.

Example 5: Characterization of photobleaching of NIR benzoporphyrin.

50 [0076] Hydrogels containing covalently-bound Compound 2 were used in photobleaching studies to determine the photostability of Compounds 2 and 9. The hydrogels were tested in a custom-built flow-through system intended to simulate physiological conditions (pH 7.4 PBS, 37°C, 21% O₂) while being illuminated by LED. The excitation light was directly delivered to the bottom face of the gel samples via 1 mm diameter fiber optic cables. Hydrogels containing Compound 9 were excited with a 525 nm LED source (power = 127 mW/cm²) having a pulse duration (LED "on time") of 2 seconds and a pulse period of 5 seconds to achieve an overall duty cycle of 40% , while Compound 2 containing hydrogels were excited with a 630 nm LED source (power = 143 mW/cm²) with the same duty cycle. The experiment was run for 15 continuous hours under these conditions. However, less than 5% change in the lifetime signal of Compound

55

2 was observed. The resulting data from this experiment is used to estimate the expected degree and rate of photobleaching which can occur during long-term *in vivo* use.

[0077] Gels containing the dye were extremely photostable when tested under simulated use conditions (FIGURE 6). These data indicate that measurement of the lifetime signal is a preferable strategy to achieve long-term (5 months) stability *in vivo*. Photostability of the Pd-BP compound may be further improved using techniques elsewhere disclosed, e.g. changing the metal core, or fluorinating or perfluorinating the base compound.

Example 6: Implantation

[0078] A tissue integrating sensor produced in rods that are 300-500 μm in diameter and 5 mm long are placed in a 19-23 Gauge insertion needle, trochar, modified biopsy device or other devices engineered for injection under the skin. The sensor is optionally dehydrated or compressed before insertion to allow for the use of a smaller insertion needle.

[0079] Upon insertion, skin is pinched up so that the insertion needle is placed parallel to the surface of the skin up to 4 mm beneath the surface. Fluid or a reverse displacement plunger (or trochar) is used to leave the sensor in the tissue as the syringe is withdrawn. Insertion site may include any subcutaneous or dermal area, typically the abdomen, arm and thigh (FIGURE 4). In research models, the dorsal skin, abdomen, hindlimb and brain (FIGURE 3) have all been explored. The following describes an example of hydrogel implantation, *in-vivo* fluorescent imaging, and data analysis in a rat model.

[0080] **Hydrogel implantation and *in vivo* fluorescent imaging.** Hydrogel sensors ($n = 3$ to 4 porous and $n = 3$ to 4 solid), were injected into the subcutaneous tissue of 12 adult male CD rats (Charles River Labs, 150-250 g) for 1 week, 4 weeks, or 170 days. Rats were anesthetized with 2-3% isoflurane (v/v in oxygen) during sensor injection. Porous and solid hydrogel rods (10 mm long, 750 μm x 750 μm cross-section) were loaded into 18 gauge needles and then inserted into the dorsal subcutaneous space perpendicular to the midline. Sensors were ejected from the needle by inserting a stainless steel plunger through the cannula. Hydrogel sensors were implanted approximately 1.5 cm apart. Rats grew normally and showed no discomfort during the weeks following the sensor injection.

[0081] Oxygen sensors were fluorescently imaged once every 30 seconds *in vivo* with the IVIS Spectrum or Kinetic imaging system (Perkin Elmer, Waltham, MA, USA). Rats were anesthetized at 2% isoflurane in 1.00 FIO₂ for 30 minutes prior to imaging. During *in vivo* imaging, the FIO₂ was at least twice modulated down to 0.12 (v/v balance N₂) for 5-10 minutes and then returned to 1.00 for 10-15 minutes. The relative response (intensity) of each sensor was quantified by identifying regions of interest (ROIs) surrounding the sensors and measuring the average radiant efficiency in the ROI using the Living Image Software included with the IVIS System.

[0082] On the day of implantation, the Oxford Optronics OxyLite system was used as a reference for tissue oxygenation. A needle-encased OxyLite probe was inserted subcutaneously in the dorsum of the rat on the day of sensor injection (D0) and was allowed 10-15 minutes for the signal to reach a steady-state before data collection as described by Braun, et. al. (Comparison of tumor and normal tissue oxygen tension measurements using OxyLite or microelectrodes in rodents. *Am J Physiol Heart Circ Physiol* 280, H2533-2544 (2001)).

[0083] **Data analysis and statistical tests.** The data for each sensor, as defined by the ROI, was normalized to the maximum and minimum average radiant efficiency and inverted to have a positive correlation between the fluorescence data and tissue oxygenation. This normalization ensured that data for every sensor for each separate experiment fell between 0 and 1, which were the maximum and minimum intensity of the sensor, respectively.

[0084] The sensors often did not reach a plateau during hypoxia testing because animal health concerns necessitated the short exposure times (5-10 min). Therefore, to calculate the response time of the sensors, the time to achieve 90% of the fluorescent intensity change (T_{90%}) during either the 10 min hypoxic (FIO₂ = 0.12) or the 15 min hyperoxic (FIO₂ = 1.00) event was determined. The sensors were declared to have reached a steady state if there was less than 10% of the total change over the last 3 minutes of the FIO₂ change event. Data was tested for statistical significance using the non-parametric Wilcoxon rank-sum test ($p < 0.05$).

[0085] **Histological analysis.** Rats were sacrificed and the sensors and surrounding tissue were explanted and frozen immediately in liquid nitrogen and stored at -80 C. Frozen tissue samples were cryosectioned at 10 μm thickness on a Leica CM1850 cryostat and mounted on poly L-lysine coated glass slides. Sections were immunostained for rat CD31 (BD Biosciences, San Jose, CA). Briefly, slides were fixed in acetone for 20 min at room temperature, rinsed in 1x PBS, blocked with staining buffer (5% normal donkey serum in 1x PBS) for 30 min, incubated with mouse-derived rat CD31 primary antibody at 1:200 in staining buffer for 1 h, and incubated with anti-mouse Alexa Fluor 488 (Jackson ImmunoResearch) for 30 min, and stained with Hoechst 33342 (Invitrogen) for 5 min at room temperature. Samples were fixed in 4% paraformaldehyde and imaged on the same day. Samples were fluorescently imaged using a Zeiss AxioSkop II+ fluorescence microscope equipped with a 12 bit CCD camera (QImaging) and an automated scanning stage (Marzhauser) driven by a Ludl Mac5000 driving unit (Ludl). An array of micrographs was acquired using a 5x objective (NA 0.25, Zeiss) and then stitched together to form a montage using Metamorph software. Exposures were set at low illumination intensities with 1x1 binning (pixel size of 1.36 μm x 1.36 μm) and a typical acquisition period of 100 ms. The results of the experiment

are depicted in FIGURE 11.

Example 7: Measurement

5 **[0086]** Data from the sensor is collected by a fluorescent reader placed on the surface of skin directly above the sensor location, and the data is processed and displayed on a smart phone, other hand-held device, computer screen or other visualization format, for example using commercially available data display devices. Raw data is converted to an analyte concentration or some non-quantitative representation of the analyte concentration (e.g. high, low, within range). Values at any given point in time or trends (graphs over time) or summary statistics over a period of time are provided. An indication of the quality of the data is optionally provided. Hydrogels prepared from co-polymerization of HEMA with NIR Pd-BP and green-ex Pd-TCPP were subcutaneously implanted in a rat carcass, and their emission was measured (FIGURE 2). Pd-BP was significantly brighter than Pd-TCPP due to the NIR excitation and emission wavelengths, which allow much greater light penetration into the skin, enabling deeper sensor placement. Deeper placement is desirable for better immunological response, but was not possible previously because the original green Pd-TCPP signal was largely blocked, e.g., scattered and/or absorbed, by the skin. Only shallow dermal implants were possible. Additionally, Pd-BP hydrogel sensors produced bright detectable signal when implanted deep under a mouse skull (inside mouse brain).

Example 8: Stability of sensors implanted in rat skin.

20 **[0087]** Oxygen sensors were implanted in rat skin and the intensity of their signal was monitored for 170 days. FIGURE 4 shows fluorescence of the sensor implanted in a mouse skin for 170 days. Intensity varied as a function of implantation depth (data was normalized to baseline fluorescence). Inhaled oxygen was modulated between 100% and 12% and images were collected every 30 s in a Caliper IVIS (Spectrum, Ex = 640 nm, Em=800 nm, 20 nm bandwidth). Regions of interest (ROIs) were drawn around the sensors and the data plotted versus time (FIGURE 6). This data illustrate that the sensors made with the dyes of the present invention maintain function for many months *in vivo*. Additionally, the tissue-integrating sensor was compared to a solid sensor. The tissue-integrating sensor produced a faster kinetic response to changes in oxygen levels than the solid sensor, which illustrates another advantageous property of the tissue-integrating sensor.

Example 9: In-vitro oxygen detection in low oxygen concentrations.

30 **[0088]** To characterize oxygen sensitivity of Pd-BP, the intensity and luminescence lifetime of the dye in a porous HEMA hydrogel at various O₂ levels (0%, 12%, and 20% O₂) was measured (FIGURE 8). The hydrogels were tested in a custom-built flow-through system (pH 7.4 PBS, 37°C) while being monitored with the TauTheta fiber-optic instrument. The dye showed good reversibility, as well as good O₂ sensitivity as indicated by the Stern-Volmer plot.

Example 10: Preparation and characterization of glucose sensor.

40 **[0089]** Glucose oxidase (GOx) was entrapped in a pHEMA hydrogel containing covalently bound Pd-BP as described above. The porous morphology of the resulting sensor was confirmed with SEM (FIGURE 5). The GOx-Pd-BP sensors were tested for glucose response in a flow-through system (PBS, 37°C). The luminescence intensity and lifetime of Pd-BP within the gel were monitored during a series of glucose excursions spanning the physiological range (FIGURE 9). The slight dip in intensity and lifetime during the plateaus (where glucose concentration was held constant) are due to consumption of glucose within the test reservoir by GOx.


Example 11: Implantation of O₂ sensor into pig skin

50 **[0090]** Explant specimens were obtained from acute pig experiment during which time the O₂ sensors prepared from the polymers comprising Compound 2 were injected into a pig. Sensor signals were obtained. Fluorescence lifetime and intensity measurements were collected. After sensor signal measurements were obtained, the pig was sacrificed and specimens were fixed in 10% Formalin and stained with Hematoxylin and Eosin (H&E). Images and depth measurements were obtained using a Nikon microscope at 40X magnification and the Infinityl microscopy camera and software (Version 6.1.0, Luminera Corp.) Sequential overlapping images were obtained to create the final composite images. FIGURE 10 depicts a sensor that was found to have been implanted at 8 mm in depth under the surface of the skin. FIGURE 10 shows that modulating sensor signal was still detectable at the depth of sensor implantation of 8 mm under the surface of the skin.

Claims

1. A sensor for detecting an analyte comprising a polymer, wherein said polymer comprises one or more residues of a luminescent dye, wherein the luminescent dye comprises polymerisable groups and wherein one or more of the polymerisable groups are co-polymerised with other monomers to form the polymer, and wherein the luminescent dye is a photostable porphyrin dye and has excitation and emission spectra in the NIR optical window of a mammalian skin

wherein the luminescent dye is a compound having the formula:



wherein M is H, Pd, Zn, Pt, Gd or Yb;

each R¹ is same or different and, independently, C(O)X--(CH₂)_n--YC(O)C(R⁴)CH₂, C(O)X--(CH₂CH₂O)_mCH₂CH₂--YC(O)C(R⁴)CH₂ or COOH;

R⁷ is C(O)X--(CH₂)_n--YC(O)C(R⁴)CH₂, or C(O)X--(CH₂CH₂O)_mCH₂CH₂--YC(O)C(R⁴)CH₂;

R² and R³ are fused, in each case, to form a cycloalkenyl, aryl, or heteroaryl group;

X is O or NR⁵;

Y is O or NH;

R⁵ and R⁴ are independently H or C₁-C₄ alkyl;

each R⁶ is same or different and, independently, H or F;

n is 1-10; and


m is 1-300.

2. The sensor of claim 1 wherein M is Pd.
3. The sensor of claim 1 wherein M is Pd, R² and R³ are fused to form a benzene ring, and R¹ and R⁷ are both C(O)NH(CH₂)₂OC(O)C(CH₃)CH₂.
4. The sensor of claim 1 wherein the luminescent dye has an absorption maximum between 500 nm and 900 nm and an emission maximum between 600 nm and 1000 nm.
5. The sensor of claim 1 wherein the residue of the luminescent dye is present at a concentration from 0.01 mM to 5 mM.
6. The sensor of claim 5 wherein the residue of the luminescent dye is present at the concentration of 1 mM.
7. The sensor of claim 1 wherein the polymer further comprises the residues of HEMA.
8. The sensor of claim 1 wherein the polymer is a hydrogel.
9. The sensor of claim 1 wherein the analyte is oxygen.
10. The sensor of claim 1 wherein the sensor is tissue-integrating.

11. The sensor of claim 10 wherein the sensor generates detectable luminescent signal when placed under the skin of a mammalian subject.
12. The sensor of claim 11 wherein the sensor generates detectable luminescent signal when placed more than 1 mm deep under the skin of a mammalian subject.
13. The sensor of either claim 11 or 12 wherein the sensor is stable in a mammalian tissue for longer than 1 week.
14. The sensor of claim 1 further comprising an oxidase.
15. The sensor of claim 14, wherein the oxidase is a glucose oxidase, ethanol oxidase, lactate oxidase, pyruvate oxidase, bilirubin oxidase, or histamine oxidase.

Patentansprüche

1. Sensor für die Detektion eines Analyten, der ein Polymer umfasst, wobei das Polymer ein oder mehrere Reste eines lumineszierenden Farbstoffs umfasst, wobei der lumineszierende Farbstoff polymerisierbare Gruppen umfasst und wobei eine oder mehrere der polymerisierbaren Gruppen mit anderen Monomeren copolymerisiert werden, um das Polymer zu bilden, und wobei der lumineszierende Farbstoff ein lichtbeständiger Porphyrin-Farbstoff ist und Anregungs- und Emissionsspektren in dem optischen NIR-Fenster einer Säugerhaut hat, wobei der lumineszierende Farbstoff eine Verbindung ist, die die folgende Formel aufweist:



wobei M H, Pd, Zn, Pt, Gd oder Yb ist;

jedes R¹ gleich oder verschieden und unabhängig C(O)X--(CH₂)_n--YC(O)C(R⁴)CH₂, C(O)X--(CH₂CH₂O)_mCH₂CH₂--YC(O)C(R⁴)CH₂ oder COOH ist;

R⁷ C(O)X--(CH₂)_n--YC(O)C(R⁴)CH₂ oder C(O)X--(CH₂CH₂O)_mCH₂CH₂--YC(O)C(R⁴)CH₂ ist;

R² und R³ in jedem Fall anelliert sind, um eine Cycloalkenyl-, Aryl- oder Heteroarylgruppe zu bilden;

X O oder NR⁵ ist;

Y O oder NH ist;

R⁵ und R⁴ unabhängig H oder C₁-C₄-Alkyl sind;

jedes R⁶ gleich oder verschieden und unabhängig H oder F ist;

n 1-10 ist; und


m 1-300 ist.

2. Sensor nach Anspruch 1, wobei M Pd ist.
3. Sensor nach Anspruch 1, wobei M Pd ist, R² und R³ anelliert sind, um einen Benzolring zu bilden, und R¹ und R⁷ beide C(O)NH(CH₂)₂OC(O)C(CH₃)CH₂ sind.
4. Sensor nach Anspruch 1, wobei der lumineszierende Farbstoff ein Absorptionsmaximum zwischen 500 nm und 900 nm und ein Emissionsmaximum zwischen 600 nm und 1000 nm hat.

5. Sensor nach Anspruch 1, wobei der Rest des lumineszierenden Farbstoffs in einer Konzentration von 0,01 mM bis 5 mM vorliegt.
6. Sensor nach Anspruch 5, wobei der Rest des lumineszierenden Farbstoffs in einer Konzentration von 1 mM vorliegt.
7. Sensor nach Anspruch 1, wobei das Polymer weiter die Reste von HEMA umfasst.
8. Sensor nach Anspruch 1, wobei das Polymer ein Hydrogel ist.
9. Sensor nach Anspruch 1, wobei der Analyt Sauerstoff ist.
10. Sensor nach Anspruch 1, wobei der Sensor in Gewebe integrierbar ist.
11. Sensor nach Anspruch 10, wobei der Sensor ein detektierbares Lumineszenzsignal erzeugt, wenn er unter der Haut eines Säugersubjekts positioniert ist.
12. Sensor nach Anspruch 11, wobei der Sensor ein detektierbares Lumineszenzsignal erzeugt, wenn er tiefer als 1 mm unter der Haut eines Säugersubjekts positioniert ist.
13. Sensor nach einem der Ansprüche 11 oder 12, wobei der Sensor in einem Säugergewebe für länger als 1 Woche stabil ist.
14. Sensor nach Anspruch 1, der weiter eine Oxidase umfasst.
15. Sensor nach Anspruch 14, wobei die Oxidase eine Glucoseoxidase, Ethanoloxidase, Lactatoxidase, Pyruvatoxidase, Bilirubinoxidase oder Histaminoxidase ist.

Revendications

1. Capteur permettant de détecter un analyte comprenant un polymère, où ledit polymère comprend un ou plusieurs résidus d'un colorant luminescent, où le colorant luminescent comprend des groupes polymérisables et où un ou plusieurs des groupes polymérisables sont copolymérisés avec d'autres monomères pour former le polymère, et où le colorant luminescent est un colorant à base de porphyrine photostable et a des spectres d'excitation et d'émission dans la fenêtre optique NIR d'une peau mammalienne, où le colorant luminescent est un composé ayant la formule :



où M est H, Pd, Zn, Pt, Gd ou Yb ;

chaque R¹ est le même ou différent et, indépendamment, C(O)X--(CH₂)_n--YC(O)C(R⁴)CH₂, C(O)X--(CH₂CH₂O)_mCH₂CH₂--YC(O)C(R⁴)CH₂ ou COOH ;

R⁷ est C(O)X--(CH₂)_n--YC(O)C(R⁴)CH₂ ou C(O)X--(CH₂CH₂O)_mCH₂CH₂--YC(O)C(R⁴)CH₂ ;

R² et R³ sont fusionnés, dans chaque cas, pour former un groupe cycloalcényle, aryle ou hétéroaryle ;

X est O ou NR⁵ ;

EP 2 970 318 B1

Y est O ou NH ;
R⁵ et R⁴ sont indépendamment H ou un alkyle C₁-C₄ ;
chaque R⁶ est le même ou différent et, indépendamment, H ou F ;
n est 1-10 ; et
m est 1-300.

5

2. Capteur selon la revendication 1, où M est Pd.

10

3. Capteur selon la revendication 1, où M est Pd, R² et R³ sont fusionnés pour former un cycle benzène, et R¹ et R⁷ sont tous les deux C(O)NH(CH₂)₂OC(O)C(CH₃)CH₂.

4. Capteur selon la revendication 1, où le colorant luminescent a un maximum d'absorption entre 500 nm et 900 nm et un maximum d'émission entre 600 nm et 1000 nm.

15

5. Capteur selon la revendication 1, où le résidu du colorant luminescent est présent à une concentration de 0,01 mM à 5 mM.

6. Capteur selon la revendication 5, où le résidu du colorant luminescent est présent à la concentration de 1 mM.

20

7. Capteur selon la revendication 1, où le polymère comprend en outre les résidus de HEMA.

8. Capteur selon la revendication 1, où le polymère est un hydrogel.

25

9. Capteur selon la revendication 1, où l'analyte est de l'oxygène.

10. Capteur selon la revendication 1, où le capteur s'intègre dans un tissu.

11. Capteur selon la revendication 10, où le capteur génère un signal luminescent détectable lorsque placé sous la peau d'un sujet mammalien.

30

12. Capteur selon la revendication 11, où le capteur génère un signal luminescent détectable lorsque placé à plus de 1 mm de profondeur sous la peau d'un sujet mammalien.

13. Capteur selon la revendication 11 ou 12, où le capteur est stable pendant plus de 1 semaine dans un tissu mammalien.

35

14. Capteur selon la revendication 1, comprenant en outre une oxydase.

15. Capteur selon la revendication 14, où l'oxydase est une glucose oxydase, éthanol oxydase, lactate oxydase, pyruvate oxydase, bilirubine oxydase ou histamine oxydase.

40

45

50

55




FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7A




FIG. 7B




FIG. 8A

Stern-Volmer Plot for Pd-BP




FIG. 8B




FIG. 9A

Normalized Intensity (F/F₀)




FIG. 9B





FIG. 10A

FIG. 10B




FIG. 11A




FIG. 11B




FIG. 11D

FIG. 11C

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- US 20120265034 A [0003] [0046]
- US 20080075752 A, Ratner [0049] [0051]
- US 6013122 A [0051]

Non-patent literature cited in the description

- **TIAN et al.** *Chemistry of Materials*, 2010, vol. 22 (6), 2069-78 [0003]
- **QUARANTA et al.** *Bioanalytical Reviews*, 2012, vol. 4 (2-4), 115-57 [0003]
- **KUMAR A. et al.** Smart polymers: Physical forms and bioengineering applications. *Prog. Polym. Sci.*, 2007, vol. 32, 1205-1237 [0020]
- **PHELPS et al.** *Proc. Nat'l. Acad. Sci. USA*, 2010, vol. 107 (8), 3323-3328 [0038] [0050]
- **KAEHR et al.** *Proc. Nat'l. Acad. Sci. USA*, 2008, vol. 105 (26), 8850-8854 [0046]
- **NIELSON et al.** *Small*, 2009, vol. 1, 120-125 [0046]
- **KASPRZAK.** Doctoral Dissertation. Georgia Institute of Technology, May 2009 [0046]
- **KLOXIN et al.** *Science*, 2009, vol. 324, 59-63 [0051]
- **ALEXEEV et al.** *Anal. Chem.*, 2003, vol. 75, 2316-2323 [0051]
- **BADYLAK et al.** *Seminars in Immunology*, 2008, vol. 20, 109-116 [0051]
- **ISENHATH et al.** *Research*, 2007, vol. 83A, 915-922 [0051]
- Division of Polymer Chemistry. **MARSHALL et al.** Polymer Preprints. American Chemical Society, 2004, vol. 45, 100-101 [0051]
- **PHELPS et al.** *Proc Nat'l Acad Sci U S A.*, 2010, vol. 107 (8), 3323-8 [0051]
- **OSTENDORF ; CHICHKOV.** *Two Photon Polymerization: A New Approach to MicroMachining, Photonics Spectra*, 2006 [0051]
- **OZDEMIR et al.** *Experimental and Clinical Research, Plast. Reconstr. Surg.*, 2005, vol. 115, 183 [0051]
- **SANDERS et al.** *Journal of Biomedical Materials Research*, 2003, vol. 67A (4), 1181-1187 [0051]
- **SANDERS et al.** *Journal of Biomedical Materials Research*, 2002, vol. 62 (2), 222-227 [0051]
- **SANDERS et al.** *Journal of Biomedical Materials Research*, 2003, vol. 65 (4), 462-467 [0051]
- **SANDERS et al.** *Biomaterials*, 2005, vol. 26, 813-818 [0051]
- **SANDERS et al.** *Journal of Biomedical Materials Research Part A*, 2005, vol. 72 (3), 335-342 [0051]
- **SANDERS.** *Journal of Biomedical Materials Research*, 2003, vol. 67 (4), 1412-1416 [0051]
- **SANDERS et al.** *Journal of Biomedical Materials Research*, 2000, vol. 52 (1), 231-237 [0051]
- **YOUNG MIN JU et al.** *J Biomed Mater Res*, 2008, vol. 87A, 136-146 [0051]
- **NIEDERMAIR et al.** *J. Inorg. Chem.*, 2010, vol. 49, 9333 [0068]
- **FINIKOVA et al.** *J. Phys. Chem.*, 2007, vol. 111, 6977 [0068]
- **MARSHALL, A.J. et al.** Biomaterials with Tightly Controlled Pore Size that Promote Vascular In-Growth. *ACS Polymer Preprints*, 2004, vol. 45, 100-101 [0072]
- **BRAUN.** Comparison of tumor and normal tissue oxygen tension measurements using OxyLite or micro-electrodes in rodents. *Am J Physiol Heart Circ Physiol*, 2001, vol. 280, H2533-2544 [0082]

专利名称(译)	氧传感器		
公开(公告)号	EP2970318A1	公开(公告)日	2016-01-20
申请号	EP2014775010	申请日	2014-03-13
[标]申请(专利权)人(译)	普罗菲尤萨股份有限公司		
申请(专利权)人(译)	PROFUSA INC.		
当前申请(专利权)人(译)	PROFUSA INC.		
[标]发明人	GAMSEY SOYA WISNIEWSKI NATALIE HELTON KRISTEN MCMILLAN WILLIAM		
发明人	GAMSEY, SOYA WISNIEWSKI, NATALIE HELTON, KRISTEN MCMILLAN, WILLIAM		
IPC分类号	C07D487/22 G01N21/64 A61K49/00 A61B5/00 C09K11/06 G01N33/497		
CPC分类号	A61B5/0059 A61B2503/40 A61K49/0036 A61K49/0054 A61K49/0073 C09K11/06 G01N33/497 A61B5/14532 A61B5/14552 C07F15/0066 C09K2211/185 C12Q1/54 G01N2333/904		
优先权	61/784925 2013-03-14 US		
其他公开文献	EP2970318B1 EP2970318A4		
外部链接	Espacenet		

摘要(译)

提供了氧传感发光染料，聚合物和包括这些传感器的传感器以及使用这些传感器和系统的方法。